

Department of Transportation
State of Georgia
Aggregate Rating System

For 1/1/2011 to 6/30/2011

Source Number and Name: 009V		Aggregates USA, Savannah, GA									
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: A - 500			Number of Reports: 67			
Screen Size	1 1/2" 1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100 95	0	25	0	0	0	0				
Upper Spec	100 100	100	60	100	10	5	100				
Lower Target			32		0	0					
Upper Target			48		5	1					
Mean	100.0 99.9	89.3	40.7	16.3	1.6	0.7					
StdDev	0.0 0.2	3.2	5.5	4.5	0.9	0.2					
No. of samples	67 67	67	67	67	67	67	0	0	0		
RFTB		0.0	0.0		0.0	0.0					
Factor		0.0	0.0		0.0	0.0					
Score		0.0	0.0		0.0	0.0		100.0			

Source Number and Name: 010C		LaFarge Aggregates Inc., Douglasville, GA									
Product: 0005	WU: Unwashed	Sampled From: Stockpile			Used In: B - 400			Number of Reports: 44			
Screen Size	1 1/2" 1"	3/4"	1/2"	3/8"	No. 4	No. 200					
Lower Spec	100 90	20	0	0	0	0					
Upper Spec	100 100	55	10	5	100	100					
Lower Target	100 93	23	0	0							
Upper Target		45	5	1							
Mean	100.0 86.6	30.2	3.5	2.1	1.6						
StdDev	0.0 5.0	7.5	1.9	1.0	0.8						
No. of samples	44 44	44	44	44	44	0	0	0	0		
RFTB											
Factor											
Score	0.0 5.0	7.5	1.9	1.0	0.8	0.0	0.0	0.0	0.0	89.2	

Source Number and Name: 010C		LaFarge Aggregates Inc., Douglasville, GA									
Product: 0006	WU: Unwashed	Sampled From: Stockpile			Used In: B - 400			Number of Reports: 39			
Screen Size	1" 3/4"	1/2"	3/8"	No. 4	No. 8	No. 200					
Lower Spec	100 90	20	0	0	0	0					
Upper Spec	100 100	55	15	5	100	100					
Lower Target		93	23	0	0						
Upper Target		100	40	7	1						
Mean	100.0 87.7	12.3	4.2	1.9	1.4						
StdDev	0.0 5.2	2.8	2.0	1.0	0.8						
No. of samples	39 39	39	39	39	39	0	0	0	0		
RFTB											
Factor											
Score	0.0 5.2	2.8	2.0	1.0	0.8	0.0	0.0	0.0	0.0	92.1	

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 010C		LaFarge Aggregates Inc., Douglasville,GA						Number of Reports: 44			
Product:0007	WU: Unwashed	Sampled From: Stockpile			Used In: B - 400						
Screen Size	3/4"	1/2"	3/8"	No. 4	No. 8	No. 16	No. 200				
Lower Spec	100	90	40	0	0	0	0				
Upper Spec	100	100	70	15	5	100	100				
Lower Target		93	45	0	0						
Upper Target		100	60	9	1						
Mean	100.0	74.9	19.9	2.7	2.0						
StdDev	0.0	4.7	5.2	1.5	1.0						
No. of samples	44	44	44	44	44	0	0	0	0	0	
RFTB											
Factor											
Score	0.0	4.7	5.2	1.5	1.0	0.0	0.0	0.0	0.0	0.0	91.7

Source Number and Name: 010C		LaFarge Aggregates Inc., Douglasville,GA						Number of Reports: 118			
Product:0057	WU: Washed	Sampled From: Belt			Used In: A - 500						
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target		97		32		0	0				
Upper Target		100		48		5	1				
Mean	100.0	98.1	83.0	36.4	14.5	2.1	0.8				
StdDev	0.0	0.5	3.2	1.4	4.0	0.7	0.2				
No. of samples	118	118	118	118	118	118	118	0	0	0	
RFTB											
Factor											
Score	0.0		0.0		0.0		0.0		0.0		100.0

Source Number and Name: 010C		LaFarge Aggregates Inc., Douglasville,GA						Number of Reports: 19			
Product:0067	WU: Washed	Sampled From: Belt			Used In: A - 500						
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	0	20	0	0	0				
Upper Spec	100	100	100	55	10	5	100				
Lower Target		93		23		0	0				
Upper Target		100		45		5	1				
Mean	100.0	95.5	50.1	25.1	2.2	0.7					
StdDev	0.0	1.9	7.7	2.2	0.9	0.2					
No. of samples	19	19	19	19	19	19	0	0	0	0	
RFTB											
Factor											
Score	0.0		0.1		0.0		0.0		0.0		99.5

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 010C		LaFarge Aggregates Inc., Douglasville,GA							Number of Reports: 22		
Product:0089	WU: Unwashed	Sampled From: Stockpile					Used In: B - 400				
Screen Size	1/2" 3/8"	No. 4	No. 8	No. 16	No. 50	No. 200					
Lower Spec	100	90	20	0	0	0					
Upper Spec	100	100	55	15	10	5	100				
Lower Target		93	23	0	0	0					
Upper Target		100	43	7	5	1					
Mean	100.0	89.9	18.1	5.5	4.2	3.1	1.6				
StdDev	0.0	3.5	5.3	2.9	1.6	1.1	0.7				
No. of samples	22	22	22	22	22	22	22	0	0	0	
RFTB Factor Score	0.0	3.5	5.3	2.9	1.6	1.1	0.7	0.0	0.0	0.0	89.9

Source Number and Name: 010C		LaFarge Aggregates Inc., Douglasville,GA							Number of Reports: 15		
Product:0M10	WU: Unwashed	Sampled From: Stockpile					Used In: B - 400				
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	99.1	82.5	63.4	48.2	32.0	17.8	8.4			
StdDev	0.0	1.1	3.4	3.2	3.4	2.3	2.6	0.8			
No. of samples	15	15	15	15	15	15	15	15	0	0	
RFTB Factor Score	0.0	1.1	3.4	3.9	4.1	2.8	3.2	1.0	0.0	0.0	87.1

Source Number and Name: 010C		LaFarge Aggregates Inc., Douglasville,GA							Number of Reports: 27		
Product:AW10	WU: Washed	Sampled From: Stockpile					Used In: B - 400				
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	99.0	78.8	57.8	42.6	27.2	13.2	5.3			
StdDev	0.0	0.8	3.0	2.7	2.7	2.3	2.3	1.3			
No. of samples	27	27	27	27	27	27	27	27	0	0	
RFTB Factor Score	0.0	0.8	3.0	3.4	3.4	2.9	2.9	1.6	0.0	0.0	87.9

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 011C

LaFarge Aggregates Inc., Lithonia,GA

Product:0057	WU: Washed		Sampled From: Belt			Used In: A - 500			Number of Reports: 102		
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target		97		32		0	0				
Upper Target		100		48		5	1				
Mean	100.0	99.2	83.1	40.0	21.0	3.1	1.1				
StdDev	0.0	0.6	4.6	3.1	3.1	0.6	0.3				
No. of samples	98	102	102	102	102	101	102	0	0	0	
RFTB		0.0		0.0		0.0	0.4				
Factor		0.0		0.0		0.0	0.0				
Score		0.0		0.0		0.0	0.0				100.0

Source Number and Name: 013C

Vulcan Materials Co., Dalton,GA

Product:0057	WU: Washed		Sampled From: Truck			Used In: A - 500			Number of Reports: 113		
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target		97		32		0	0				
Upper Target		100		48		5	1				
Mean	100.0	98.5	83.0	41.8	23.4	3.3	0.8	0.4			
StdDev	0.0	0.3	1.5	1.2	2.1	0.5	0.2	0.1			
No. of samples	113	113	113	113	113	113	113	16	0	0	
RFTB		0.0		0.0		0.0	0.0				
Factor		0.0		0.0		0.0	0.0				
Score		0.0		0.0		0.0	0.0				100.0

Source Number and Name: 013C

Vulcan Materials Co., Dalton,GA

Product:0067	WU: Washed		Sampled From: Truck			Used In: A - 500			Number of Reports: 101		
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	0	20	0	0	0				
Upper Spec	100	100	100	55	10	5	100				
Lower Target		93		23		0	0				
Upper Target		100		45		5	1				
Mean	100.0	98.2	67.1	34.4	3.3	0.8	0.4				
StdDev	0.0	0.3	1.0	1.4	0.4	0.2	0.2				
No. of samples	101	101	101	101	101	101	16	0	0	0	
RFTB		0.0		0.0		0.0	0.0				
Factor		0.0		0.0		0.0	0.0				
Score		0.0		0.0		0.0	0.0				100.0

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 013C		Vulcan Materials Co., Dalton,GA							Number of Reports: 44		
Product: 0M10	WU: Unwashed	Sampled From: Stockpile					Used In: B - 400				
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	98.9	76.5	47.5	28.8	22.2	17.3	14.0			
StdDev	0.0	0.3	5.7	5.1	1.8	1.3	0.7	0.4			
No. of samples	44	44	44	44	44	44	44	44	0	0	
RFTB Factor											
Score	0.0	0.3	5.7	6.7	2.4	1.7	0.9	0.5	0.0	0.0	87.9

Source Number and Name: 014C		Martin Marietta Aggregates, Tyrone,GA							Number of Reports: 15		
Product: 0007	WU: Washed	Sampled From: Belt					Used In: B - 400				
Screen Size	3/4"	1/2"	3/8"	No. 4	No. 8	No. 16	No. 200				
Lower Spec	100	90	40	0	0	0	0				
Upper Spec	100	100	70	15	5	100	100				
Lower Target											
Upper Target											
Mean	100.0	94.7	50.6	5.2	1.7						
StdDev	0.0	2.1	4.8	2.4	1.3						
No. of samples	15	15	15	15	15	0	0	0	0	0	
RFTB Factor											
Score	0.0	2.1	4.8	2.4	1.3	0.0	0.0	0.0	0.0	0.0	92.9

Source Number and Name: 014C		Martin Marietta Aggregates, Tyrone,GA							Number of Reports: 72	
Product: 0057	WU: Washed	Sampled From: Belt					Used In: A - 500			
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200		
Lower Spec	100	95	0	25	0	0	0	0		
Upper Spec	100	100	100	60	100	10	5	100		
Lower Target										
Upper Target										
Mean	100.0	98.3	86.5	39.5	18.7	2.7	1.4			
StdDev	0.0	0.8	4.0	5.8	4.5	1.0	0.5			
No. of samples	72	72	72	72	72	72	72	0	0	0
RFTB Factor										
Score	0.0		0.0		0.0		0.0		100.0	

Source Number and Name: 014C		Aggregate Rating for 1/1/2011 to 6/30/2011									
Product: 0089		WU: Washed		Sampled From: Belt				Used In: B - 400		Number of Reports: 26	
Screen Size	1/2"	3/8"	No. 4	No. 8	No. 16	No. 50	No. 200				
Lower Spec	100	90	20	0	0	0	0				
Upper Spec	100	100	55	15	10	5	100				
Lower Target		93	23	0	0	0					
Upper Target		100	43	7	5	1					
Mean	100.0	99.0	28.2	4.6	2.7	1.1					
StdDev	0.0	0.8	6.7	1.9	1.9	1.2					
No. of samples	26	26	26	26	26	26	0	0	0	0	
RFTB Factor Score	0.0	0.8	6.7	1.9	1.9	1.2	0.0	0.0	0.0	0.0	91.7

Source Number and Name: 014C		Martin Marietta Aggregates, Tyrone,GA									
Product: 0M10		WU: Unwashed		Sampled From: Stockpile				Used In: B - 400		Number of Reports: 19	
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	98.4	82.6	64.7	49.6	36.4	22.6	13.3			
StdDev	0.0	0.8	1.8	1.6	1.8	1.8	2.1	0.7			
No. of samples	19	19	19	19	19	19	19	19	0	0	
RFTB Factor Score	0.0	0.8	1.8	1.9	2.2	2.2	2.5	0.8	0.0	0.0	91.8

Source Number and Name: 014C		Martin Marietta Aggregates, Tyrone,GA									
Product: AW10		WU: Washed		Sampled From: Stockpile				Used In: B - 400		Number of Reports: 15	
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	98.2	78.4	55.0	36.4	19.2	7.1	2.4			
StdDev	0.0	0.9	1.7	1.5	1.4	1.3	0.6	0.3			
No. of samples	15	15	15	15	15	15	15	15	0	0	
RFTB Factor Score	0.0	0.9	1.7	1.9	1.8	1.7	0.8	0.4	0.0	0.0	93.9

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 015C			Vulcan Materials Co., Forest Park, GA					Number of Reports: 27			
Product:0007	WU: Washed		Sampled From: Belt			Used In: B - 400					
Screen Size	3/4"	1/2"	3/8"	No. 4	No. 8	No. 16	No. 200				
Lower Spec	100	90	40	0	0	0	0				
Upper Spec	100	100	70	15	5	100	100				
Lower Target		93	45	0	0						
Upper Target		100	60	9	1						
Mean	100.0	91.4	46.0	2.6	0.9	0.5	0.0				
StdDev	0.0	1.1	3.4	1.0	0.4	0.5					
No. of samples	27	27	27	27	27	27	1	0	0	0	
RFTB											
Factor											
Score	0.0	1.1	3.4	1.0	0.4	0.5	0.0	0.0	0.0	0.0	95.7

Source Number and Name: 015C			Vulcan Materials Co., Forest Park, GA					Number of Reports: 106			
Product:0057	WU: Washed		Sampled From: Belt			Used In: A - 500					
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target		97		32		0	0				
Upper Target		100		48		5	1				
Mean	100.0	98.7	84.8	38.5	18.4	1.8	0.6	0.1			
StdDev	0.0	0.6	3.8	3.2	2.6	0.7	0.1				
No. of samples	105	106	106	106	106	106	106	1	0	0	
RFTB											
Factor											
Score	0.0		0.0		0.0		0.0		100.0		

Source Number and Name: 015C			Vulcan Materials Co., Forest Park, GA					Number of Reports: 91			
Product:0067	WU: Washed		Sampled From: Belt			Used In: A - 500					
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	0	20	0	0	0				
Upper Spec	100	100	100	55	10	5	100				
Lower Target		93		23	0	0					
Upper Target		100		45	5	1					
Mean	100.0	97.1	61.6	30.6	2.1	0.6	0.2				
StdDev	0.0	1.3	4.1	2.5	0.5	0.1	0.1				
No. of samples	91	91	91	91	91	91	4	0	0	0	
RFTB											
Factor											
Score	0.0		0.0		0.0		0.0		100.0		

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 015C		Vulcan Materials Co., Forest Park, GA					Used In: B - 400		Number of Reports: 63		
Product: 0089	WU: Washed	Sampled From: Belt									
Screen Size	1/2" 3/8"	No. 4	No. 8	No. 16	No. 50	No. 200					
Lower Spec	100	90	20	0	0	0	0				
Upper Spec	100	100	55	15	10	5	100				
Lower Target		93	23	0	0	0					
Upper Target		100	43	7	5	1					
Mean	100.0	100.0	22.9	3.9	2.3	0.9					
StdDev	0.0	0.0	2.6	2.0	1.2	0.6					
No. of samples	63	63	63	63	63	63	0	0	0	0	
RFTB Factor Score	0.0	0.0	2.6	2.0	1.2	0.6	0.0	0.0	0.0	0.0	95.7

Source Number and Name: 015C		Vulcan Materials Co., Forest Park, GA					Used In: B - 400		Number of Reports: 26		
Product: 0M10	WU: Unwashed	Sampled From: Stockpile									
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	97.7	78.1	63.6	50.6	37.3	20.9	10.3			
StdDev	0.0	0.5	3.1	3.4	3.7	2.8	2.3	1.8			
No. of samples	26	26	26	26	26	26	26	26	0	0	
RFTB Factor Score	0.0	0.5	3.1	4.4	4.7	3.6	2.9	2.3	0.0	0.0	85.6

Source Number and Name: 015C		Vulcan Materials Co., Forest Park, GA					Used In: H - 310 Gab		Number of Reports: 44		
Product: 15CR-2	WU: Unwashed	Sampled From: Stockpile									
Screen Size	2" 1 1/2"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 10	No. 60	No. 200		
Lower Spec	100	97	60	0	0	0	0	25	5	4	
Upper Spec	100	100	90	100	100	100	100	45	30	11	
Lower Target		98	70					32	8	6	
Upper Target		100	86					40	25	9	
Mean	100.0	100.0	78.9	64.6	57.1	46.0		36.6	16.1	6.0	
StdDev	0.0	0.0	3.2	4.3	5.2	3.8		2.8	4.0	0.9	
No. of samples	44	44	44	44	44	44	0	44	22	22	
RFTB Factor Score		0.0	0.0					0.0	0.0	0.9	
		0.0	0.0					0.0	0.0	0.0	
		0.0	0.0					0.0	0.0	0.0	100.0

Source Number and Name: 015C		Aggregate Rating for 1/1/2011 to 6/30/2011									
Product: AW10		WU: Washed		Sampled From: Stockpile			Used In: B - 400		Number of Reports: 27		
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	97.8	79.6	64.6	51.9	33.2	14.7	4.6			
StdDev	0.0	0.6	3.7	3.7	4.4	1.7	1.5	1.0			
No. of samples	27	27	27	27	27	27	27	27	0	0	
RFTB											
Factor											
Score	0.0	0.6	3.7	4.6	5.5	2.1	1.9	1.3	0.0	0.0	86.8

Source Number and Name: 016F		LaFarge Aggregates Inc., Douglasville, GA									
Product: 10FM-2		WU: Washed		Sampled From: Stockpile			Used In: A - 500		Number of Reports: 66		
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	100	95	0	45	0	15	6	0			
Upper Spec	100	100	100	95	100	42	22	9			
Lower Target											
Upper Target											
Mean	100.0	99.3	79.2	57.8	42.7	26.9	13.2	5.1			
StdDev	0.0	0.7	2.3	2.4	2.7	2.9	2.4	1.3			
No. of samples	66	66	66	66	66	66	66	66	0	0	
RFTB											
Factor											
Score	0.0		0.0		0.0		0.0		100.0		

Source Number and Name: 017C		Vulcan Materials Company, Macon, GA									
Product: 0005		WU: Washed		Sampled From: Belt			Used In: B - 400		Number of Reports: 15		
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 200				
Lower Spec	100	90	20	0	0	0	0				
Upper Spec	100	100	55	10	5	100	100				
Lower Target	100	93	23	0	0						
Upper Target											
Mean	100.0	92.6	37.1	3.7	2.0	1.5					
StdDev	0.0	2.1	4.2	1.4	0.6	0.5					
No. of samples	15	15	15	15	15	15	0	0	0	0	
RFTB											
Factor											
Score	0.0	2.1	4.2	1.4	0.6	0.5	0.0	0.0	0.0	0.0	94.1

Source Number and Name: 017C		Aggregate Rating for 1/1/2011 to 6/30/2011						Vulcan Materials Company, Macon, GA			
Product: 0006	WU: Washed	Sampled From: Belt			Used In: B - 400			Number of Reports: 16			
Screen Size	1" 3/4"	1/2"	3/8"	No. 4	No. 8	No. 200					
Lower Spec	100 90	20	0	0	0	0					
Upper Spec	100 100	55	15	5	100	100					
Lower Target		93	23	0	0						
Upper Target		100	40	7	1						
Mean	100.0 88.8	16.2	1.8	1.3	0.8						
StdDev	0.0 1.2	2.5	0.5	0.4	0.3						
No. of samples	16 16	16	16	16	16	0	0	0	0		
RFTB Factor Score	0.0 1.2	2.5	0.5	0.4	0.3	0.0	0.0	0.0	0.0	0.0	96.7

Source Number and Name: 017C		Aggregate Rating for 1/1/2011 to 6/30/2011						Vulcan Materials Company, Macon, GA			
Product: 0007	WU: Washed	Sampled From: Belt			Used In: B - 400			Number of Reports: 61			
Screen Size	3/4" 1/2"	3/8"	No. 4	No. 8	No. 16	No. 200					
Lower Spec	100 90	40	0	0	0	0					
Upper Spec	100 100	70	15	5	100	100					
Lower Target		93	45	0	0						
Upper Target		100	60	9	1						
Mean	100.0 89.6	43.2	2.1	1.5	1.2						
StdDev	0.0 2.0	3.4	0.5	0.4	0.3						
No. of samples	61 61	61	61	61	61	0	0	0	0		
RFTB Factor Score	0.0 2.0	3.4	0.5	0.4	0.3	0.0	0.0	0.0	0.0	0.0	95.6

Source Number and Name: 017C		Aggregate Rating for 1/1/2011 to 6/30/2011						Vulcan Materials Company, Macon, GA			
Product: 0008	WU: Washed	Sampled From: Belt			Used In: B - 400			Number of Reports: 92			
Screen Size	1/2" 3/8"	No. 4	No. 8	No. 16	No. 50	No. 200					
Lower Spec	100 85	10	0	0	0	0					
Upper Spec	100 100	40	10	5	100	100					
Lower Target											
Upper Target											
Mean	100.0 98.8	25.1	2.4	1.7	1.7	0.5					
StdDev	0.0 0.6	3.0	0.5	0.5	0.5						
No. of samples	92 92	92	92	92	92	1	0	0	0		
RFTB Factor Score	0.0 0.6	3.0	0.5	0.5	0.5	0.0	0.0	0.0	0.0	0.0	96.6

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 017C		Vulcan Materials Company, Macon, GA							Number of Reports: 224		
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: A - 500						
Screen Size	1 1/2" 1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100 95	0	25	0	0	0	0				
Upper Spec	100 100	100	60	100	10	5	100				
Lower Target		97	32		0	0					
Upper Target		100	48		5	1					
Mean	100.0 99.9	93.6	36.2	15.2	1.5	0.8	0.4				
StdDev	0.0 0.5	3.5	3.5	2.4	1.1	0.3	0.1				
No. of samples	224 224	224	224	224	224	224	10	0	0		
RFTB		0.0	0.0		0.0	0.1					
Factor		0.0	0.0		0.0	0.0					
Score		0.0	0.0		0.0	0.0		100.0			

Source Number and Name: 017C		Vulcan Materials Company, Macon, GA							Number of Reports: 37		
Product: 0067	WU: Washed	Sampled From: Stockpile			Used In: B - 400						
Screen Size	1" 3/4"	1/2"	3/8"	No. 4	No. 8	No. 200					
Lower Spec	100 90	0	20	0	0	0					
Upper Spec	100 100	100	55	10	5	100					
Lower Target		93	23	0	0						
Upper Target		100	45	5	1						
Mean	100.0 96.1	66.1	27.4	1.6	0.8						
StdDev	0.0 1.0	4.8	3.2	0.7	0.4						
No. of samples	37 37	37	37	37	37	0	0	0	0		
RFTB											
Factor											
Score	0.0 1.0	4.8	3.2	0.7	0.4	0.0	0.0	0.0	0.0	0.0	93.3

Source Number and Name: 017C		Vulcan Materials Company, Macon, GA							Number of Reports: 19		
Product: 0M10	WU: Unwashed	Sampled From: Stockpile			Used In: B - 400						
Screen Size	3/8" No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200				
Lower Spec	0 0	0	0	0	0	0	0				
Upper Spec	100 100	100	100	100	100	100	100				
Lower Target											
Upper Target											
Mean	100.0 98.5	84.4	68.0	56.3	41.7	24.7	13.9				
StdDev	0.0 0.6	1.7	3.2	3.1	1.6	1.1	1.2				
No. of samples	19 19	19	19	19	19	19	19	0	0		
RFTB											
Factor											
Score	0.0 0.6	1.7	3.8	3.7	1.9	1.3	1.4	0.0	0.0	90.4	

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 017C		Vulcan Materials Company, Macon, GA									
Product: 15CR-2	WU: Unwashed	Sampled From: Stockpile					Used In: H - 310 Gab			Number of Reports: 83	
Screen Size	2" 1 1/2"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 10	No. 60	No. 200		
Lower Spec	100	97	60	0	0	0	25	5	4		
Upper Spec	100	100	90	100	100	100	45	30	11		
Lower Target		98	70				32	8	6		
Upper Target		100	86				40	25	9		
Mean	100.0	99.7	77.5	65.7	58.3	47.3	37.8	21.2	6.9		
StdDev	0.0	1.0	4.1	4.5	4.7	3.6	2.6	1.4	1.7		
No. of samples	83	83	82	82	82	83	0	83	19	20	
RFTB		0.0	0.0				0.4	0.0	0.8		
Factor		0.0	0.0				5.0	0.0	0.0		
Score		0.0	0.0				2.0	0.0	0.0	98.0	

Source Number and Name: 017C		Vulcan Materials Company, Macon, GA									
Product: AW10	WU: Washed	Sampled From: Stockpile					Used In: B - 400			Number of Reports: 35	
Screen Size	3/8" No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200				
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	98.3	80.1	61.1	47.2	25.6	7.7	2.0			
StdDev	0.0	0.5	2.4	2.5	3.0	1.6	1.0	0.4			
No. of samples	35	35	35	35	35	35	35	35	0	0	
RFTB											
Factor											
Score	0.0	0.5	2.4	3.1	3.7	2.0	1.2	0.5	0.0	0.0	91.0

Source Number and Name: 017F		LaFarge Aggregates Inc., Lithonia, GA									
Product: 10FM-2	WU: Washed	Sampled From: Stockpile					Used In: A - 500			Number of Reports: 109	
Screen Size	3/8" No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200				
Lower Spec	100	95	0	45	0	15	6	0			
Upper Spec	100	100	100	95	100	42	22	9			
Lower Target		97		51		19	7	2			
Upper Target		100		90		36	18	7			
Mean	100.0	99.2	86.9	66.1	47.2	26.9	11.4	3.7			
StdDev	0.0	0.4	2.0	2.4	2.3	2.5	1.7	0.7			
No. of samples	108	109	109	109	109	109	109	109	0	0	
RFTB		0.0		0.0		0.0	0.0	0.0			
Factor		0.0		0.0		0.0	0.0	0.0			
Score		0.0		0.0		0.0	0.0	0.0			100.0

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 018V		Martin Marietta Aggregates, Hinesville, GA							Number of Reports: 57		
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: A - 500						
Screen Size	1 1/2" 1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100 95	0	25	0	0	0	0				
Upper Spec	100 100	100	60	100	10	5	100				
Lower Target			32		0	0					
Upper Target			48		5	1					
Mean	100.0 97.7	82.4	39.8	16.4	2.0	0.7					
StdDev	0.0 1.2	7.7	4.3	6.2	1.1	0.2					
No. of samples	57 57	57	57	57	57	57	0	0	0		
RFTB			0.0		0.0	0.0					
Factor			0.0		0.0	0.0					
Score			0.0		0.0	0.0		97.5			

Source Number and Name: 018V		Martin Marietta Aggregates, Hinesville, GA							Number of Reports: 57		
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: B - 400						
Screen Size	1 1/2" 1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100 95	0	25	0	0	0	0				
Upper Spec	100 100	100	60	100	10	5	100				
Lower Target			32		0	0					
Upper Target			48		5	1					
Mean	100.0 97.7	82.4	39.8	16.4	2.0	0.7					
StdDev	0.0 1.2	7.7	4.3	6.2	1.1	0.2					
No. of samples	57 57	57	57	57	57	57	0	0	0		
RFTB											
Factor											
Score	0.0 1.2	7.7	4.3	6.2	1.1	0.2	0.0	0.0	0.0	86.2	

Source Number and Name: 023C		Hanson Aggregates, Athens, GA							Number of Reports: 80		
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: A - 500						
Screen Size	1 1/2" 1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100 95	0	25	0	0	0	0				
Upper Spec	100 100	100	60	100	10	5	100				
Lower Target			32		0	0					
Upper Target			48		5	1					
Mean	100.0 98.0	79.2	37.8	16.0	3.4	2.2	0.5				
StdDev	0.0 0.7	4.5	3.5	3.1	0.5	0.3	0.4				
No. of samples	80 80	80	80	80	80	80	2	0	0		
RFTB			0.0		0.0	1.5					
Factor			0.0		0.0	5.0					
Score			0.0		0.0	7.5		92.5			

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 023C		Hanson Aggregates, Athens,GA								Number of Reports: 89	
Product: 0M10	WU: Unwashed	Sampled From: Stockpile				Used In: B - 400					
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	99.4	83.3	64.6	48.0	30.5	18.1	8.5			
StdDev	0.0	0.4	2.0	2.9	2.8	2.1	1.5	0.7			
No. of samples	89	89	89	89	89	89	89	89	0	0	
RFTB Factor											
Score	0.0	0.4	2.0	3.5	3.4	2.5	1.8	0.8	0.0	0.0	90.4

Source Number and Name: 023C		Hanson Aggregates, Athens,GA								Number of Reports: 49	
Product: AW10	WU: Washed	Sampled From: Stockpile				Used In: B - 400					
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	99.7	83.3	61.2	40.8	20.0	8.1	2.6			
StdDev	0.0	0.2	3.4	4.5	4.3	3.1	1.3	0.5			
No. of samples	49	49	49	49	49	49	49	49	0	0	
RFTB Factor											
Score	0.0	0.2	3.4	5.4	5.2	3.7	1.6	0.6	0.0	0.0	86.6

Source Number and Name: 024C		Hanson Aggregates, Gainesville, GA								Number of Reports: 21	
Product: 0006	WU: Unwashed	Sampled From: Stockpile				Used In: B - 400					
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	20	0	0	0	0				
Upper Spec	100	100	55	15	5	100	100				
Lower Target											
Upper Target											
Mean	100.0	97.9	30.5	5.5	1.7	1.4	0.7				
StdDev	0.0	2.3	8.3	3.6	0.8	0.6					
No. of samples	21	21	21	21	21	21	1	0	0	0	
RFTB Factor											
Score	0.0	2.3	8.3	3.6	0.8	0.6	0.0	0.0	0.0	0.0	89.6

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 024C		Hanson Aggregates, Gainesville, GA						Number of Reports: 29			
Product: 0007	WU: Unwashed	Sampled From: Stockpile			Used In: B - 400						
Screen Size	3/4"	1/2"	3/8"	No. 4	No. 8	No. 16	No. 200				
Lower Spec	100	90	40	0	0	0	0				
Upper Spec	100	100	70	15	5	100	100				
Lower Target		93	45	0	0						
Upper Target		100	60	9	1						
Mean	100.0	93.6	50.0	4.9	1.2	1.1					
StdDev	0.0	3.1	3.6	2.7	0.3	0.4					
No. of samples	29	29	29	29	29	29	0	0	0	0	
RFTB Factor Score	0.0	3.1	3.6	2.7	0.3	0.4	0.0	0.0	0.0	0.0	93.3

Source Number and Name: 024C		Hanson Aggregates, Gainesville, GA						Number of Reports: 139			
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: A - 500						
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target		97		32		0	0				
Upper Target		100		48		5	1				
Mean	100.0	98.4	81.9	39.3	16.3	2.4	1.3	0.7			
StdDev	0.0	0.7	6.3	3.9	7.3	1.0	0.5	0.3			
No. of samples	139	139	139	139	139	139	139	14	0	0	
RFTB Factor Score		0.0		0.0		0.0	0.8				100.0
		0.0		0.0		0.0	0.0				
		0.0		0.0		0.0	0.0				

Source Number and Name: 024C		Hanson Aggregates, Gainesville, GA						Number of Reports: 29			
Product: 0089	WU: Washed	Sampled From: Stockpile			Used In: B - 400						
Screen Size	1/2"	3/8"	No. 4	No. 8	No. 16	No. 50	No. 200				
Lower Spec	100	90	20	0	0	0	0				
Upper Spec	100	100	55	15	10	5	100				
Lower Target		93	23	0	0	0					
Upper Target		100	43	7	5	1					
Mean	100.0	99.7	35.2	3.7	2.3	1.6	1.1				
StdDev	0.0	1.0	4.6	1.6	0.9	0.5	0.3				
No. of samples	29	29	29	29	29	29	4	0	0	0	
RFTB Factor Score	0.0	1.0	4.6	1.6	0.9	0.5	0.3	0.0	0.0	0.0	94.1

Source Number and Name: 024C		Aggregate Rating for 1/1/2011 to 6/30/2011 Hanson Aggregates, Gainesville, GA								Number of Reports: 21	
Product: AW10	WU: Washed	Sampled From: Stockpile				Used In: B - 400					
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	99.9	97.3	79.0	58.3	45.4	26.5	9.7	2.8			
StdDev	0.2	6.3	8.4	5.9	7.0	5.9	3.5	0.9			
No. of samples	21	21	21	21	21	21	21	21	0	0	
RFTB Factor											
Score	0.2	6.3	8.4	7.5	8.9	7.5	4.4	1.1	0.0	0.0	70.5

Source Number and Name: 028C		Aggregates USA, Postell, GA								Number of Reports: 52	
Product: 0007	WU: Unwashed	Sampled From: Stockpile				Used In: B - 400					
Screen Size	3/4"	1/2"	3/8"	No. 4	No. 8	No. 16	No. 200				
Lower Spec	100	90	40	0	0	0	0				
Upper Spec	100	100	70	15	5	100	100				
Lower Target											
Upper Target											
Mean	100.0	86.0	39.5	3.3	1.2						
StdDev	0.0	2.4	4.5	1.1	0.2						
No. of samples	52	52	52	52	52	0	0	0	0	0	
RFTB Factor											
Score	0.0	2.4	4.5	1.1	0.2	0.0	0.0	0.0	0.0	0.0	94.5

Source Number and Name: 028C		Aggregates USA, Postell, GA								Number of Reports: 374	
Product: 0057	WU: Washed	Sampled From: Belt				Used In: A - 500					
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target											
Upper Target											
Mean	100.0	99.9	88.4	37.0	13.1	1.8	0.9				
StdDev	0.0	0.2	2.5	2.7	2.3	0.5	0.2				
No. of samples	374	374	374	374	374	374	374	0	0	0	
RFTB Factor											
Score	0.0		0.0		0.0		0.0		100.0		

Source Number and Name: 028C		Aggregate Rating for 1/1/2011 to 6/30/2011										
Product: 0067		WU: Washed		Sampled From: Belt			Used In: A - 500		Number of Reports: 124			
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200					
Lower Spec	100	90	0	20	0	0	0					
Upper Spec	100	100	100	55	10	5	100					
Lower Target		93		23	0	0						
Upper Target		100		45	5	1						
Mean	100.0	94.7	62.4	28.4	2.7	1.1						
StdDev	0.0	1.1	3.4	3.1	0.6	0.2						
No. of samples	124	124	124	124	124	124	0	0	0	0		
RFTB		0.0		0.0	0.0	0.3						
Factor		0.0		0.0	0.0	0.0						
Score		0.0		0.0	0.0	0.0		100.0				

Source Number and Name: 028C		Aggregate Rating for 1/1/2011 to 6/30/2011										
Product: 0078		WU: Washed		Sampled From: Stockpile			Used In: B - 400		Number of Reports: 23			
Screen Size	3/4"	1/2"	3/8"	No. 4	No. 8	No. 16	No. 200					
Lower Spec	100	90	40	5	0	0	0					
Upper Spec	100	100	75	25	10	5	100					
Lower Target												
Upper Target												
Mean	100.0	92.8	58.6	10.1	2.2	1.5						
StdDev	0.0	2.1	2.9	1.5	0.3	0.4						
No. of samples	23	23	23	23	23	19	0	0	0	0		
RFTB												
Factor												
Score	0.0	2.1	2.9	1.5	0.3	0.4	0.0	0.0	0.0	0.0	95.2	

Source Number and Name: 028C		Aggregate Rating for 1/1/2011 to 6/30/2011										
Product: 0089		WU: Unwashed		Sampled From: Stockpile			Used In: B - 400		Number of Reports: 54			
Screen Size	1/2"	3/8"	No. 4	No. 8	No. 16	No. 50	No. 200					
Lower Spec	100	90	20	0	0	0	0					
Upper Spec	100	100	55	15	10	5	100					
Lower Target		93	23	0	0	0						
Upper Target		100	43	7	5	1						
Mean	100.0	96.2	26.7	1.7	0.9	0.5						
StdDev	0.0	0.9	2.1	0.7	0.5	0.3						
No. of samples	54	54	54	54	54	54	0	0	0	0		
RFTB												
Factor												
Score	0.0	0.9	2.1	0.7	0.5	0.3	0.0	0.0	0.0	0.0	97.0	

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 028C		Aggregates USA, Postell, GA								Number of Reports: 25	
Product: 0M10	WU: Unwashed	Sampled From: Stockpile				Used In: B - 400					
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	98.9	77.2	56.0	41.4	31.2	22.8	15.4			
StdDev	0.0	0.3	1.1	1.8	1.7	1.3	0.9	0.6			
No. of samples	25	25	25	25	25	25	25	25	0	0	
RFTB Factor											
Score	0.0	0.3	1.1	2.3	2.2	1.7	1.2	0.8	0.0	0.0	93.6

Source Number and Name: 028C		Aggregates USA, Postell, GA								Number of Reports: 161	
Product: 15CR-2	WU: Unwashed	Sampled From: Stockpile				Used In: H - 310 Gab					
Screen Size	2"	1 1/2"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 10	No. 60	No. 200	
Lower Spec	100	97	60	0	0	0	0	25	5	4	
Upper Spec	100	100	90	100	100	100	100	45	30	11	
Lower Target	98		70					32	8	6	
Upper Target	100		86					40	25	9	
Mean	100.0	100.0	84.4	71.4	60.9	47.9		34.4	16.0	8.5	
StdDev	0.0	0.0	0.9	1.7	1.6	1.4		1.6	1.7	0.5	
No. of samples	161	161	161	161	161	161	0	161	26	26	
RFTB Factor	0.0		0.0					0.0	0.0	0.0	
Score	0.0		0.0					0.0	0.0	0.0	100.0

Source Number and Name: 028C		Aggregates USA, Postell, GA								Number of Reports: 25	
Product: AW10	WU: Washed	Sampled From: Stockpile				Used In: B - 400					
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	97.9	73.5	47.1	29.9	18.5	9.6	4.2			
StdDev	0.2	4.1	4.4	3.6	2.4	1.8	1.2	0.4			
No. of samples	25	25	25	25	25	25	25	25	0	0	
RFTB Factor											
Score	0.2	4.1	4.4	4.9	3.3	2.4	1.6	0.5	0.0	0.0	85.7

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 030F		Martin Marietta Aggregates, Tyrone, GA							Number of Reports: 30	
Product: 10FM-2	WU: Washed	Sampled From: Stockpile			Used In: A - 500					
Screen Size	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	100	95	0	45	0	15	6	0		
Upper Spec	100	100	100	95	100	42	22	9		
Lower Target		97		51		19	7	2		
Upper Target		100		90		36	18	7		
Mean	100.0	98.0	78.5	55.4	37.3	20.4	7.8	2.6		
StdDev	0.0	0.9	1.9	2.5	2.3	1.8	0.9	0.4		
No. of samples	30	30	30	30	30	30	30	30	0	0
RFTB		0.0		0.0		0.4	0.1	0.0		
Factor		0.0		0.0		5.0	0.0	0.0		
Score		0.0		0.0		2.0	0.0	0.0		98.0

Source Number and Name: 031C		APAC Mid-South, Tiftonia, TN							Number of Reports: 20		
Product: 0M10	WU: Unwashed	Sampled From: Stockpile			Used In: B - 400						
Screen Size	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200				
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	94.1	64.9	40.4	27.4	21.1	13.9	10.1			
StdDev	0.0	1.9	1.7	2.7	3.2	2.3	1.4	1.2			
No. of samples	20	20	20	20	20	20	20	20	0	0	
RFTB											
Factor											
Score	0.0	1.9	1.7	4.2	4.9	3.5	2.2	1.8	0.0	0.0	86.5

Source Number and Name: 032C		McLanahan Crushed Stone Inc., Elberton, GA							Number of Reports: 114	
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: A - 500					
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200		
Lower Spec	100	95	0	25	0	0	0	0		
Upper Spec	100	100	100	60	100	10	5	100		
Lower Target		97		32		0	0			
Upper Target		100		48		5	1			
Mean	100.0	98.6	79.3	38.9	17.6	1.3	0.8			
StdDev	0.0	0.6	2.6	3.6	2.5	0.4	0.3			
No. of samples	114	114	114	114	114	114	114	0	0	0
RFTB		0.0		0.0		0.0	0.1			
Factor		0.0		0.0		0.0	0.0			
Score		0.0		0.0		0.0	0.0			100.0

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 034C		Hanson Aggregates, Toccoa, GA							Number of Reports: 10			
Product: 0007	WU: Unwashed	Sampled From: Stockpile			Used In: B - 400							
Screen Size	3/4" 1/2"	3/8"	No. 4	No. 8	No. 16	No. 200						
Lower Spec	100 90	40	0	0	0	0						
Upper Spec	100 100	70	15	5	100	100						
Lower Target		93	45	0	0							
Upper Target		100	60	9	1							
Mean	100.0 89.1	52.1	12.3	3.6	2.8							
StdDev	0.0 4.7	2.5	2.2	1.0	0.9							
No. of samples	10 10	10	10	10	10	0	0	0	0			
RFTB Factor Score	0.0 4.7	2.5	2.2	1.0	0.9	0.0	0.0	0.0	0.0	0.0	92.5	

Source Number and Name: 034C		Hanson Aggregates, Toccoa, GA							Number of Reports: 106			
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: A - 500							
Screen Size	1 1/2" 1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200					
Lower Spec	100 95	0	25	0	0	0	0					
Upper Spec	100 100	100	60	100	10	5	100					
Lower Target			97	32	0	0						
Upper Target			100	48	5	1						
Mean	100.0 99.7	86.1	37.1	16.6	3.1	1.9	0.4					
StdDev	0.0 0.4	3.1	4.0	2.9	0.8	0.5	0.2					
No. of samples	106 106	106	106	106	106	106	4	0	0			
RFTB Factor Score	0.0 0.0	0.0	0.0	0.0	0.0	1.4					93.0	
						5.0						
						7.0						

Source Number and Name: 034C		Hanson Aggregates, Toccoa, GA							Number of Reports: 15			
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: B - 400							
Screen Size	1 1/2" 1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200					
Lower Spec	100 95	0	25	0	0	0	0					
Upper Spec	100 100	100	60	100	10	5	100					
Lower Target			97	32	0	0						
Upper Target			100	48	5	1						
Mean	100.0 99.7	84.6	35.9	15.8	3.2	1.9	0.4					
StdDev	0.0 0.3	5.8	5.5	3.0	0.6	0.5						
No. of samples	15 15	15	15	15	15	15	1	0	0			
RFTB Factor Score	0.0 0.3	5.8	5.5	3.0	0.6	0.5	0.0	0.0	0.0	0.0	89.5	

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 034C		Hanson Aggregates, Toccoa, GA					Number of Reports: 17				
Product: 0089	WU: Unwashed	Sampled From: Stockpile			Used In: B - 400						
Screen Size	1/2"	3/8"	No. 4	No. 8	No. 16	No. 50	No. 200				
Lower Spec	100	90	20	0	0	0	0				
Upper Spec	100	100	55	15	10	5	100				
Lower Target		93	23	0	0	0					
Upper Target		100	43	7	5	1					
Mean	100.0	94.7	29.0	8.2	5.8	3.8					
StdDev	0.0	1.6	3.3	1.9	1.5	1.0					
No. of samples	17	17	17	17	17	17	0	0	0	0	
RFTB Factor Score	0.0	1.6	3.3	1.9	1.5	1.0	0.0	0.0	0.0	0.0	93.8

Source Number and Name: 036C		Vulcan Materials Co., Rabun Co., GA					Number of Reports: 22				
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: A - 500						
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target		97		32		0	0				
Upper Target		100		48		5	1				
Mean	100.0	98.5	81.1	39.9	19.2	3.0	1.0				
StdDev	0.0	0.7	6.1	3.1	4.9	0.9	0.4				
No. of samples	22	22	22	22	22	21	22	0	0	0	
RFTB Factor Score		0.0		0.0		0.0	0.4				100.0
		0.0		0.0		0.0	0.0				
		0.0		0.0		0.0	0.0				

Source Number and Name: 036C		Vulcan Materials Co., Rabun Co., GA					Number of Reports: 36				
Product: 0067	WU: Washed	Sampled From: Stockpile			Used In: A - 500						
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	0	20	0	0	0				
Upper Spec	100	100	100	55	10	5	100				
Lower Target		93		23		0	0				
Upper Target		100		45		5	1				
Mean	100.0	97.4	59.6	33.1	3.3	1.2					
StdDev	0.0	1.6	8.9	5.2	1.0	0.4					
No. of samples	36	36	36	36	36	36	0	0	0	0	
RFTB Factor Score		0.0		0.0		0.0	0.6				100.0
		0.0		0.0		0.0	0.0				
		0.0		0.0		0.0	0.0				

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 038C		LaFarge Aggregates Inc., Cumming, GA						Number of Reports: 18			
Product: 0089	WU: Unwashed	Sampled From: Stockpile			Used In: B - 400						
Screen Size	1/2" 3/8"	No. 4	No. 8	No. 16	No. 50	No. 200					
Lower Spec	100	90	20	0	0	0					
Upper Spec	100	100	55	15	10	5	100				
Lower Target		93	23	0	0	0					
Upper Target		100	43	7	5	1					
Mean	100.0	100.0	40.3	9.0	6.1	3.8	2.1				
StdDev	0.0	0.0	6.4	2.6	1.9	1.7	0.9				
No. of samples	18	18	18	18	18	18	18	0	0	0	
RFTB Factor Score	0.0	0.0	6.4	2.6	1.9	1.7	0.9	0.0	0.0	0.0	91.0

Source Number and Name: 038C		LaFarge Aggregates Inc., Cumming, GA						Number of Reports: 54			
Product: AW10	WU: Washed	Sampled From: Stockpile			Used In: B - 400						
Screen Size	3/8" No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200				
Lower Spec	0	0	0	0	0	0	0				
Upper Spec	100	100	100	100	100	100	100				
Lower Target											
Upper Target											
Mean	100.0	99.1	78.7	56.7	39.4	17.3	8.9	2.7			
StdDev	0.0	0.7	3.8	3.4	2.8	4.8	2.3	0.6			
No. of samples	54	54	54	54	54	54	54	54	0	0	
RFTB Factor Score	0.0	0.7	3.8	4.3	3.6	6.1	2.9	0.8	0.0	0.0	85.2

Source Number and Name: 040F		Hanson Aggregates, Gainesville, GA						Number of Reports: 143			
Product: 10FM-2	WU: Washed	Sampled From: Stockpile			Used In: A - 500						
Screen Size	3/8" No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200				
Lower Spec	100	95	0	45	0	15	6	0			
Upper Spec	100	100	100	95	100	42	22	9			
Lower Target		97		51		19	7	2			
Upper Target		100		90		36	18	7			
Mean	100.0	99.4	79.6	60.1	46.6	29.0	11.6	2.9			
StdDev	0.0	0.4	5.0	4.6	5.7	4.3	2.8	0.7			
No. of samples	143	143	143	143	143	143	143	143	0	0	
RFTB Factor Score		0.0		0.0		0.0	0.0	0.0			100.0

Source Number and Name: 041C			Aggregate Rating for 1/1/2011 to 6/30/2011					Martin Marietta Aggregates, Augusta, GA			
Product:0006	WU:	Washed	Sampled From: Belt			Used In: B - 400			Number of Reports: 11		
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	20	0	0	0	0				
Upper Spec	100	100	55	15	5	100	100				
Lower Target		93	23	0	0						
Upper Target		100	40	7	1						
Mean	100.0	95.8	30.5	7.7	1.1						
StdDev	0.0	1.2	6.0	4.4	0.7						
No. of samples	11	11	11	11	11	0	0	0	0	0	
RFTB Factor											
Score	0.0	1.2	6.0	4.4	0.7	0.0	0.0	0.0	0.0	0.0	91.8

Source Number and Name: 041C			Aggregate Rating for 1/1/2011 to 6/30/2011					Martin Marietta Aggregates, Augusta, GA			
Product:0008	WU:	Washed	Sampled From: Stockpile			Used In: B - 400			Number of Reports: 17		
Screen Size	1/2"	3/8"	No. 4	No. 8	No. 16	No. 50	No. 200				
Lower Spec	100	85	10	0	0	0	0				
Upper Spec	100	100	40	10	5	100	100				
Lower Target											
Upper Target											
Mean	100.0	95.0	18.0	1.4	0.4		0.3				
StdDev	0.0	2.5	5.7	0.9	0.5						
No. of samples	17	17	17	17	17	0	1	0	0	0	
RFTB Factor											
Score	0.0	2.5	5.7	0.9	0.5	0.0	0.0	0.0	0.0	0.0	93.6

Source Number and Name: 041C			Aggregate Rating for 1/1/2011 to 6/30/2011					Martin Marietta Aggregates, Augusta, GA			
Product:0057	WU:	Washed	Sampled From: Belt			Used In: A - 500			Number of Reports: 55		
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target		97		32		0	0				
Upper Target		100		48		5	1				
Mean	100.0	98.0	82.7	37.2	17.2	2.9	0.3	0.3			
StdDev	0.0	0.6	5.0	3.8	3.8	1.1	0.2				
No. of samples	55	55	55	55	55	55	55	1	0	0	
RFTB Factor		0.0		0.0		0.0	0.0				
Score		0.0		0.0		0.0	0.0				100.0

Source Number and Name: 041C		Aggregate Rating for 1/1/2011 to 6/30/2011									
Product: 0067		WU: Washed		Sampled From: Belt			Used In: A - 500		Number of Reports: 69		
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	0	20	0	0	0				
Upper Spec	100	100	100	55	10	5	100				
Lower Target		93		23	0	0					
Upper Target		100		45	5	1					
Mean	100.0	98.2	61.9	31.9	3.4	0.4	0.3				
StdDev	0.0	0.9	7.1	4.6	0.9	0.2	0.1				
No. of samples	69	69	69	69	69	69	11	0	0	0	
RFTB		0.0		0.0	0.0	0.0					
Factor		0.0		0.0	0.0	0.0					
Score		0.0		0.0	0.0	0.0		100.0			

Source Number and Name: 041C		Martin Marietta Aggregates, Augusta, GA									
Product: AW10		WU: Washed		Sampled From: Belt			Used In: B - 400		Number of Reports: 11		
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	96.1	73.2	42.3	23.8	13.1	6.8	3.5			
StdDev	0.0	3.8	5.5	3.1	2.3	2.0	1.2	0.9			
No. of samples	11	11	11	11	11	11	11	11	0	0	
RFTB											
Factor											
Score	0.0	3.8	5.5	4.2	3.1	2.7	1.6	1.2	0.0	0.0	85.1

Source Number and Name: 041C		Martin Marietta Aggregates, Augusta, GA									
Product: AW10		WU: Washed		Sampled From: Stockpile			Used In: B - 400		Number of Reports: 24		
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	97.7	72.1	41.5	23.6	13.0	6.9	3.4			
StdDev	0.0	1.2	3.9	4.4	2.8	2.1	1.3	0.9			
No. of samples	24	24	24	24	24	24	24	24	0	0	
RFTB											
Factor											
Score	0.0	1.2	3.9	6.1	3.9	2.9	1.8	1.2	0.0	0.0	86.0

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 043C			Vulcan Materials Co., Chattanooga, TN					Number of Reports: 22			
Product: 0067	WU: Washed		Sampled From: Stockpile			Used In: A - 500					
Screen Size	1" 3/4"		1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	0	20	0	0	0				
Upper Spec	100	100	100	55	10	5	100				
Lower Target		93		23	0	0					
Upper Target		100		45	5	1					
Mean	100.0	98.3	52.6	31.5	4.4	0.8					
StdDev	0.0	0.5	2.3	2.7	0.4	0.1					
No. of samples	22	22	22	22	22	22	0	0	0	0	
RFTB		0.0		0.0	0.0	0.0					
Factor		0.0		0.0	0.0	0.0					
Score		0.0		0.0	0.0	0.0		100.0			

Source Number and Name: 044C			Vulcan Materials Co., Barin, GA					Number of Reports: 16			
Product: 0005	WU: Washed		Sampled From: Truck			Used In: B - 400					
Screen Size	1 1/2" 1"		3/4"	1/2"	3/8"	No. 4	No. 200				
Lower Spec	100	90	20	0	0	0	0				
Upper Spec	100	100	55	10	5	100	100				
Lower Target	100	93	23	0	0						
Upper Target		100		45	5	1					
Mean	100.0	94.7	33.0	2.3	0.7						
StdDev	0.0	1.4	5.9	1.1	0.2						
No. of samples	16	16	16	16	16	0	0	0	0	0	
RFTB											
Factor											
Score	0.0	1.4	5.9	1.1	0.2	0.0	0.0	0.0	0.0	0.0	94.3

Source Number and Name: 044C			Vulcan Materials Co., Barin, GA					Number of Reports: 20			
Product: 0006	WU: Washed		Sampled From: Truck			Used In: B - 400					
Screen Size	1" 3/4"		1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	20	0	0	0	0				
Upper Spec	100	100	55	15	5	100	100				
Lower Target		93		23	0	0					
Upper Target		100		40	7	1					
Mean	100.0	96.6	29.2	4.5	0.7						
StdDev	0.0	1.5	4.6	2.0	0.2						
No. of samples	20	20	20	20	20	0	0	0	0	0	
RFTB											
Factor											
Score	0.0	1.5	4.6	2.0	0.2	0.0	0.0	0.0	0.0	0.0	94.5

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 044C			Vulcan Materials Co., Barin, GA				Number of Reports: 53				
Product: 0007	WU: Washed		Sampled From: Truck			Used In: B - 400					
Screen Size	3/4"	1/2"	3/8"	No. 4	No. 8	No. 16	No. 200				
Lower Spec	100	90	40	0	0	0	0				
Upper Spec	100	100	70	15	5	100	100				
Lower Target		93	45	0	0						
Upper Target		100	60	9	1						
Mean	100.0	95.4	51.6	2.6	0.6						
StdDev	0.0	1.4	4.3	1.0	0.1						
No. of samples	53	53	53	53	53	0	0	0	0	0	
RFTB											
Factor											
Score	0.0	1.4	4.3	1.0	0.1	0.0	0.0	0.0	0.0	0.0	95.5

Source Number and Name: 044C			Vulcan Materials Co., Barin, GA				Number of Reports: 118				
Product: 0057	WU: Washed		Sampled From: Belt			Used In: A - 500					
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target		97		32		0	0				
Upper Target		100		48		5	1				
Mean	100.0	98.7	81.8	39.9	16.1	2.0	0.8	0.5			
StdDev	0.0	0.6	5.4	2.3	4.8	0.7	0.1	0.2			
No. of samples	118	118	118	118	118	118	118	3	0	0	
RFTB		0.0		0.0		0.0	0.0				
Factor		0.0		0.0		0.0	0.0				
Score		0.0		0.0		0.0	0.0				100.0

Source Number and Name: 044C			Vulcan Materials Co., Barin, GA				Number of Reports: 118				
Product: 0057	WU: Washed		Sampled From: Belt			Used In: B - 400					
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target		97		32		0	0				
Upper Target		100		48		5	1				
Mean	100.0	98.7	81.8	39.9	16.1	2.0	0.8	0.5			
StdDev	0.0	0.6	5.4	2.3	4.8	0.7	0.1	0.2			
No. of samples	118	118	118	118	118	118	118	3	0	0	
RFTB											
Factor											
Score	0.0	0.6	5.4	2.3	4.8	0.7	0.1	0.2	0.0	0.0	90.6

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 044C			Vulcan Materials Co., Barin, GA					Number of Reports: 89			
Product:0067	WU: Washed		Sampled From: Belt			Used In: A - 500					
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	0	20	0	0	0				
Upper Spec	100	100	100	55	10	5	100				
Lower Target		93		23	0	0					
Upper Target		100		45	5	1					
Mean	100.0	99.0	63.6	30.1	2.2	0.9	0.5				
StdDev	0.0	0.9	8.7	3.7	0.6	0.1					
No. of samples	89	89	89	89	89	89	1	0	0	0	
RFTB		0.0		0.0	0.0	0.0					
Factor		0.0		0.0	0.0	0.0					
Score		0.0		0.0	0.0	0.0		100.0			

Source Number and Name: 044C			Vulcan Materials Co., Barin, GA					Number of Reports: 89			
Product:0067	WU: Washed		Sampled From: Belt			Used In: B - 400					
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	0	20	0	0	0				
Upper Spec	100	100	100	55	10	5	100				
Lower Target		93		23	0	0					
Upper Target		100		45	5	1					
Mean	100.0	99.0	63.6	30.1	2.2	0.9	0.5				
StdDev	0.0	0.9	8.7	3.7	0.6	0.1					
No. of samples	89	89	89	89	89	89	1	0	0	0	
RFTB											
Factor											
Score	0.0	0.9	8.7	3.7	0.6	0.1	0.0	0.0	0.0	0.0	90.7

Source Number and Name: 044C			Vulcan Materials Co., Barin, GA					Number of Reports: 71			
Product:0089	WU: Washed		Sampled From: Truck			Used In: B - 400					
Screen Size	1/2"	3/8"	No. 4	No. 8	No. 16	No. 50	No. 200				
Lower Spec	100	90	20	0	0	0	0				
Upper Spec	100	100	55	15	10	5	100				
Lower Target		93		23	0	0					
Upper Target		100		43	7	5	1				
Mean	100.0	99.4	32.5	3.4	0.7	0.1					
StdDev	0.0	0.1	4.2	1.2	0.3	0.2					
No. of samples	71	71	71	71	71	71	0	0	0	0	
RFTB											
Factor											
Score	0.0	0.1	4.2	1.2	0.3	0.2	0.0	0.0	0.0	0.0	96.0

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 044C		Vulcan Materials Co., Barin, GA									
Product: 15CR-2	WU: Unwashed	Sampled From: Stockpile					Used In: H - 310 Gab			Number of Reports: 175	
Screen Size	2" 1 1/2"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 10	No. 60	No. 200		
Lower Spec	100	97	60	0	0	0	0	25	5	4	
Upper Spec	100	100	90	100	100	100	100	45	30	11	
Lower Target		98	70					32	8	6	
Upper Target		100	86					40	25	9	
Mean	100.0	100.0	82.1	67.0	59.5	46.5		35.8	16.6	6.5	
StdDev	0.0	0.0	3.1	5.0	5.6	5.2		4.1	2.3	1.9	
No. of samples	172	175	175	175	175	175	0	175	17	18	
RFTB		0.0	0.0					0.3	0.0	1.4	
Factor		0.0	0.0					5.0	0.0	5.0	
Score		0.0	0.0					1.5	0.0	7.0	91.5

Source Number and Name: 044C		Vulcan Materials Co., Barin, GA									
Product: AW10	WU: Washed	Sampled From: Stockpile					Used In: B - 400			Number of Reports: 21	
Screen Size	3/8" No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200				
Lower Spec	0	0	0	0	0	0	0	0	0		
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	99.6	86.0	63.1	39.3	19.6	5.9	2.4			
StdDev	0.0	0.2	4.2	9.5	5.7	7.6	3.5	2.4			
No. of samples	21	21	21	21	21	21	21	21	0	0	
RFTB											
Factor											
Score	0.0	0.2	4.2	11.0	6.6	8.8	4.1	2.8	0.0	0.0	74.8

Source Number and Name: 044C		Vulcan Materials Co., Barin, GA									
Product: M810	WU: Unwashed	Sampled From: Stockpile					Used In: B - 400			Number of Reports: 14	
Screen Size	3/8" No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200				
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	81.3	62.4	49.2	37.6	25.9	16.6	10.7			
StdDev	0.0	1.4	2.4	2.4	2.2	2.1	2.0	2.4			
No. of samples	14	14	14	14	14	14	14	14	0	0	
RFTB											
Factor											
Score	0.0	1.4	2.4	3.8	3.5	3.4	3.2	3.8	0.0	0.0	85.6

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 046C		Vulcan Materials Co., Kennesaw, GA							Number of Reports: 182		
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: A - 500						
Screen Size	1 1/2" 1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100 95	0	25	0	0	0	0				
Upper Spec	100 100	100	60	100	10	5	100				
Lower Target			97		0	0					
Upper Target			100		5	1					
Mean	100.0 97.5	83.9	37.0	17.4	2.2	1.0					
StdDev	0.0 0.8	2.7	2.9	2.5	0.7	0.5					
No. of samples	173 173	173	173	173	173	173	0	0	0		
RFTB			0.3		0.0	0.5					
Factor			5.0		0.0	0.0					
Score			1.5		0.0	0.0		98.5			

Source Number and Name: 046C		Vulcan Materials Co., Kennesaw, GA							Number of Reports: 66		
Product: 0089	WU: Washed	Sampled From: Stockpile			Used In: B - 400						
Screen Size	1/2" 3/8"	No. 4	No. 8	No. 16	No. 50	No. 200					
Lower Spec	100 90	20	0	0	0	0					
Upper Spec	100 100	55	15	10	5	100					
Lower Target			93		23	0	0				
Upper Target			100		43	7	5	1			
Mean	100.0 98.4	27.8	5.9	3.0	0.5						
StdDev	0.0 1.4	3.7	1.6	1.0	0.9						
No. of samples	64 64	64	64	64	6	0	0	0	0	0	
RFTB											
Factor											
Score	0.0 1.4	3.7	1.6	1.0	0.9	0.0	0.0	0.0	0.0	94.3	

Source Number and Name: 046C		Vulcan Materials Co., Kennesaw, GA							Number of Reports: 89		
Product: 15CR-2	WU: Unwashed	Sampled From: Stockpile			Used In: H - 310 Gab						
Screen Size	2" 1 1/2"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 10	No. 60	No. 200		
Lower Spec	100 97	60	0	0	0	0	25	5	4		
Upper Spec	100 100	90	100	100	100	100	45	30	11		
Lower Target			98		70		32	8	6		
Upper Target			100		86		40	25	9		
Mean	100.0 98.4	76.7	63.2	58.9	48.4		38.4	16.9	6.1		
StdDev	0.0 0.8	2.8	3.3	3.4	2.6		1.8	1.7	1.7		
No. of samples	85 85	85	85	85	85	0	85	12	12		
RFTB			0.4		0.0		0.2	0.0	1.6		
Factor			3.0		0.0		5.0	0.0	20.0		
Score			1.2		0.0		1.0	0.0	32.0	65.8	

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 046C		Vulcan Materials Co., Kennesaw, GA							Number of Reports: 59	
Product:	WU:	Sampled From: Stockpile					Used In: B - 400			
Screen Size	3/8" No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0 0	0	0	0	0	0	0			
Upper Spec	100 100	100	100	100	100	100	100			
Lower Target										
Upper Target										
Mean	100.0 99.4	80.0	63.1	47.3	28.9	13.5	3.6			
StdDev	0.0 0.4	1.8	2.7	2.2	1.9	1.7	0.7			
No. of samples	57 57	57	57	57	57	57	57	0	0	
RFTB Factor										
Score	0.0 0.4	1.8	3.4	2.8	2.4	2.1	0.9	0.0	0.0	90.9

Source Number and Name: 046C		Vulcan Materials Co., Kennesaw, GA							Number of Reports: 57	
Product:	WU:	Sampled From: Stockpile					Used In: B - 400			
Screen Size	3/8" No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0 0	0	0	0	0	0	0			
Upper Spec	100 100	100	100	100	100	100	100			
Lower Target										
Upper Target										
Mean	100.0 81.6	64.3	53.0	42.0	29.3	18.4	9.8			
StdDev	0.0 1.5	1.9	2.0	1.9	1.6	1.2	0.7			
No. of samples	54 54	54	54	54	54	54	54	0	0	
RFTB Factor										
Score	0.0 1.5	1.9	3.1	3.0	2.5	1.9	1.1	0.0	0.0	90.1

Source Number and Name: 047C		Vulcan Materials Co., Lithia Springs, GA							Number of Reports: 64	
Product:	WU:	Sampled From: Stockpile					Used In: A - 500			
Screen Size	1 1/2" 1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100 95	0	25	0	0	0	0			
Upper Spec	100 100	100	60	100	10	5	100			
Lower Target			32		0	0				
Upper Target			48		5	1				
Mean	100.0 97.6	79.9	38.0	17.9	1.8	0.8	0.0			
StdDev	0.0 0.6	3.1	3.2	3.6	0.6	0.2				
No. of samples	62 62	62	62	62	62	62	1	0	0	
RFTB Factor										
Score										100.0

Source Number and Name: 047C		Aggregate Rating for 1/1/2011 to 6/30/2011									
Product: 0067		Vulcan Materials Co., Lithia Springs, GA									
WU: Washed		Sampled From: Stockpile			Used In: A - 500			Number of Reports: 33			
Screen Size	1" 3/4"	1/2"	3/8"	No. 4	No. 8	No. 200					
Lower Spec	100 90	0	20	0	0	0					
Upper Spec	100 100	100	55	10	5	100					
Lower Target			93	23	0	0					
Upper Target			100	45	5	1					
Mean	100.0 96.9	62.8	31.4	2.8	0.7						
StdDev	0.0 1.2	8.2	5.3	1.0	0.1						
No. of samples	30 30	30	30	30	30	0	0	0	0		
RFTB				0.0	0.0	0.0					
Factor				0.0	0.0	0.0					
Score				0.0	0.0	0.0	100.0				

Source Number and Name: 047C		Vulcan Materials Co., Lithia Springs, GA									
Product: 0089		Vulcan Materials Co., Lithia Springs, GA									
WU: Washed		Sampled From: Stockpile			Used In: B - 400			Number of Reports: 27			
Screen Size	1/2" 3/8"	No. 4	No. 8	No. 16	No. 50	No. 200					
Lower Spec	100 90	20	0	0	0	0					
Upper Spec	100 100	55	15	10	5	100					
Lower Target			93	23	0	0					
Upper Target			100	43	7	5	1				
Mean	100.0 98.1	33.4	4.3	2.3	0.7						
StdDev	0.0 1.7	4.1	1.6	1.0	0.1						
No. of samples	24 24	24	24	24	24	0	0	0	0		
RFTB											
Factor											
Score	0.0 1.7	4.1	1.6	1.0	0.1	0.0	0.0	0.0	0.0	0.0	94.3

Source Number and Name: 048C		Vulcan Materials Co., Norcross, GA									
Product: 0007		Vulcan Materials Co., Norcross, GA									
WU: Washed		Sampled From: Stockpile			Used In: B - 400			Number of Reports: 32			
Screen Size	3/4" 1/2"	3/8"	No. 4	No. 8	No. 16	No. 200					
Lower Spec	100 90	40	0	0	0	0					
Upper Spec	100 100	70	15	5	100	100					
Lower Target			93	45	0	0					
Upper Target			100	60	9	1					
Mean	100.0 92.0	54.8	6.3	1.6							
StdDev	0.0 1.2	3.7	1.4	0.7							
No. of samples	32 32	32	32	32	0	0	0	0	0		
RFTB											
Factor											
Score	0.0 1.2	3.7	1.4	0.7	0.0	0.0	0.0	0.0	0.0	0.0	95.3

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 048C		Vulcan Materials Co., Norcross, GA							Number of Reports: 41	
Product: 0057	WU: Washed	Sampled From: Belt			Used In: A - 500					
Screen Size	1 1/2" 1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100 95	0	25	0	0	0	0			
Upper Spec	100 100	100	60	100	10	5	100			
Lower Target			32		0	0				
Upper Target			48		5	1				
Mean	100.0 98.0	81.5	40.2	20.4	2.4	0.6	0.6			
StdDev	0.0 0.8	2.1	2.1	2.1	0.7	0.5	0.3			
No. of samples	41 41	41	41	41	41	41	4	0	0	
RFTB			0.0		0.0	0.1				
Factor			0.0		0.0	0.0				
Score			0.0		0.0	0.0		100.0		

Source Number and Name: 048C		Vulcan Materials Co., Norcross, GA							Number of Reports: 137	
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: A - 500					
Screen Size	1 1/2" 1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100 95	0	25	0	0	0	0			
Upper Spec	100 100	100	60	100	10	5	100			
Lower Target			32		0	0				
Upper Target			48		5	1				
Mean	100.0 98.0	80.4	38.3	18.4	2.3	0.9	0.9			
StdDev	0.0 0.8	3.2	2.2	2.1	0.9	0.5	0.4			
No. of samples	137 137	137	137	137	137	137	12	0	0	
RFTB			0.0		0.0	0.4				
Factor			0.0		0.0	0.0				
Score			0.0		0.0	0.0		100.0		

Source Number and Name: 048C		Vulcan Materials Co., Norcross, GA							Number of Reports: 30	
Product: 0067	WU: Washed	Sampled From: Stockpile			Used In: A - 500					
Screen Size	1" 3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100 90	0	20	0	0	0				
Upper Spec	100 100	100	55	10	5	100				
Lower Target			23		0	0				
Upper Target			45		5	1				
Mean	100.0 94.9	55.0	29.5	3.7	1.0					
StdDev	0.0 2.1	5.9	5.3	1.3	0.5					
No. of samples	30 30	30	30	30	30	0	0	0	0	
RFTB			0.0	0.0	0.5					
Factor			0.0	0.0	0.0					
Score			0.0	0.0	0.0		99.0			

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 048C		Vulcan Materials Co., Norcross, GA						Number of Reports: 30			
Product: 0067	WU: Washed	Sampled From: Stockpile			Used In: B - 400						
Screen Size	1" 3/4"	1/2"	3/8"	No. 4	No. 8	No. 200					
Lower Spec	100	90	0	20	0	0					
Upper Spec	100	100	100	55	10	5	100				
Lower Target		93		23	0	0					
Upper Target		100		45	5	1					
Mean	100.0	94.9	55.0	29.5	3.7	1.0					
StdDev	0.0	2.1	5.9	5.3	1.3	0.5					
No. of samples	30	30	30	30	30	30	0	0	0	0	
RFTB Factor Score	0.0	2.1	5.9	5.3	1.3	0.5	0.0	0.0	0.0	0.0	89.9

Source Number and Name: 048C		Vulcan Materials Co., Norcross, GA						Number of Reports: 103			
Product: 0089	WU: Washed	Sampled From: Stockpile			Used In: B - 400						
Screen Size	1/2" 3/8"	No. 4	No. 8	No. 16	No. 50	No. 200					
Lower Spec	100	90	20	0	0	0					
Upper Spec	100	100	55	15	10	5	100				
Lower Target		93	23	0	0	0					
Upper Target		100	43	7	5	1					
Mean	100.0	99.2	37.2	8.0	4.3	0.0					
StdDev	0.0	0.4	4.7	2.0	1.5	0.0					
No. of samples	103	103	103	103	103	103	0	0	0	0	
RFTB Factor Score	0.0	0.4	4.7	2.0	1.5	0.0	0.0	0.0	0.0	0.0	94.3

Source Number and Name: 048C		Vulcan Materials Co., Norcross, GA						Number of Reports: 42			
Product: 15CR-2	WU: Unwashed	Sampled From: Stockpile			Used In: H - 310 Gab						
Screen Size	2" 1 1/2"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 10	No. 60	No. 200		
Lower Spec	100	97	60	0	0	0	25	5	4		
Upper Spec	100	100	90	100	100	100	45	30	11		
Lower Target		98	70				32	8	6		
Upper Target		100	86				40	25	9		
Mean	100.0	100.0	81.9	66.3	58.9	46.8	37.1	18.6	7.5		
StdDev	0.0	0.0	2.7	4.2	4.4	3.3	2.4	1.3	0.9		
No. of samples	42	42	42	42	42	42	0	42	42	42	
RFTB Factor Score		0.0	0.0				0.0	0.0	0.0		100.0

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 048C		Vulcan Materials Co., Norcross, GA								Number of Reports: 102	
Product: M810	WU: Unwashed	Sampled From: Stockpile				Used In: B - 400					
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	79.7	61.7	50.7	41.0	30.4	20.1	11.3			
StdDev	0.0	2.4	2.9	2.7	2.4	2.0	1.4	1.0			
No. of samples	102	102	102	102	102	102	102	102	0	0	
RFTB Factor											
Score	0.0	2.4	2.9	4.4	3.9	3.2	2.3	1.6	0.0	0.0	86.2

Source Number and Name: 049C		Martin Marietta Aggregates, Red Oak, GA								Number of Reports: 50	
Product: 0007	WU: Washed	Sampled From: Belt				Used In: B - 400					
Screen Size	3/4"	1/2"	3/8"	No. 4	No. 8	No. 16	No. 200				
Lower Spec	100	90	40	0	0	0	0				
Upper Spec	100	100	70	15	5	100	100				
Lower Target											
Upper Target											
Mean	100.0	95.5	52.7	2.6	1.0						
StdDev	0.0	1.7	4.0	0.9	0.1						
No. of samples	50	50	50	50	50	0	0	0	0	0	
RFTB Factor											
Score	0.0	1.7	4.0	0.9	0.1	0.0	0.0	0.0	0.0	0.0	95.5

Source Number and Name: 049C		Martin Marietta Aggregates, Red Oak, GA								Number of Reports: 64	
Product: 0057	WU: Washed	Sampled From: Belt				Used In: A - 500					
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target											
Upper Target											
Mean	100.0	98.9	87.7	40.0	17.1	1.5	1.0				
StdDev	0.0	0.6	2.8	3.4	2.8	0.4	0.1				
No. of samples	64	64	64	64	64	64	64	0	0	0	
RFTB Factor											
Score	0.0		0.0		0.0		0.0		100.0		

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 049C		Martin Marietta Aggregates, Red Oak, GA							Number of Reports: 49		
Product: 0057	WU: Washed	Sampled From: Belt			Used In: B - 400						
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target		97		32		0	0				
Upper Target		100		48		5	1				
Mean	100.0	98.8	87.5	39.6	16.9	1.5	1.0				
StdDev	0.0	0.7	2.9	3.0	2.3	0.3	0.1				
No. of samples	49	49	49	49	49	49	49	0	0	0	
RFTB Factor											
Score	0.0	0.7	2.9	3.0	2.3	0.3	0.1	0.0	0.0	0.0	93.8

Source Number and Name: 049C		Martin Marietta Aggregates, Red Oak, GA							Number of Reports: 53		
Product: 0067	WU: Washed	Sampled From: Belt			Used In: A - 500						
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	0	20	0	0	0				
Upper Spec	100	100	100	55	10	5	100				
Lower Target		93		23	0	0					
Upper Target		100		45	5	1					
Mean	100.0	97.0	63.0	30.6	1.9	1.0					
StdDev	0.0	1.0	5.6	4.3	0.5	0.1					
No. of samples	53	53	53	53	53	53	0	0	0	0	
RFTB Factor		0.0		0.0	0.0	0.1					
Score		0.0		0.0	0.0	0.0					
											100.0

Source Number and Name: 049C		Martin Marietta Aggregates, Red Oak, GA							Number of Reports: 51		
Product: 0089	WU: Washed	Sampled From: Belt			Used In: B - 400						
Screen Size	1/2"	3/8"	No. 4	No. 8	No. 16	No. 50	No. 200				
Lower Spec	100	90	20	0	0	0	0				
Upper Spec	100	100	55	15	10	5	100				
Lower Target		93	23	0	0	0					
Upper Target		100	43	7	5	1					
Mean	100.0	99.4	40.3	4.5	2.4	1.4					
StdDev	0.0	0.5	7.1	1.6	0.9	0.4					
No. of samples	51	51	51	51	51	51	0	0	0	0	
RFTB Factor											
Score	0.0	0.5	7.1	1.6	0.9	0.4	0.0	0.0	0.0	0.0	93.0

Source Number and Name: 049C		Aggregate Rating for 1/1/2011 to 6/30/2011									
Product: AW10		WU: Washed		Sampled From: Stockpile				Used In: B - 400		Number of Reports: 49	
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	99.8	84.4	63.2	47.0	28.1	11.0	2.8			
StdDev	0.0	0.1	1.6	2.0	2.1	2.0	1.6	0.5			
No. of samples	49	49	49	49	49	49	49	47	0	0	
RFTB Factor											
Score	0.0	0.1	1.6	2.4	2.5	2.4	1.9	0.6	0.0	0.0	92.4

Source Number and Name: 049C		Aggregate Rating for 1/1/2011 to 6/30/2011									
Product: M810		WU: Unwashed		Sampled From: Stockpile				Used In: B - 400		Number of Reports: 50	
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	80.1	59.9	47.7		28.8	19.2	11.6			
StdDev	0.0	3.4	3.7	3.4		2.4	1.6	1.0			
No. of samples	50	50	50	50	0	50	50	50	0	0	
RFTB Factor											
Score	0.0	3.4	3.7	5.7	0.0	4.0	2.7	1.7	0.0	0.0	85.9

Source Number and Name: 050C		Aggregate Rating for 1/1/2011 to 6/30/2011									
Product: 0007		WU: Washed		Sampled From: Stockpile				Used In: B - 400		Number of Reports: 26	
Screen Size	3/4"	1/2"	3/8"	No. 4	No. 8	No. 16	No. 200				
Lower Spec	100	90	40	0	0	0	0				
Upper Spec	100	100	70	15	5	100	100				
Lower Target											
Upper Target											
Mean	100.0	95.0	48.4	2.0	0.9		0.3				
StdDev	0.0	1.4	2.6	0.6	0.3						
No. of samples	26	26	26	26	26	0	1	0	0	0	
RFTB Factor											
Score	0.0	1.4	2.6	0.6	0.3	0.0	0.0	0.0	0.0	0.0	96.7

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 050C		Vulcan Materials Co., Stockbridge, GA							Number of Reports: 128		
Product: 0057	WU: Washed	Sampled From: Belt			Used In: A - 500						
Screen Size	1 1/2" 1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100 95	0	25	0	0	0	0				
Upper Spec	100 100	100	60	100	10	5	100				
Lower Target			97		0	0					
Upper Target			100		5	1					
Mean	100.0 98.6	85.0	37.7	17.7	1.6	0.7	0.6				
StdDev	0.0 0.5	2.5	3.1	2.9	0.4	0.2					
No. of samples	128 128	128	128	128	128	128	1	0	0		
RFTB			0.0		0.0	0.0					
Factor			0.0		0.0	0.0					
Score			0.0		0.0	0.0		100.0			

Source Number and Name: 050C		Vulcan Materials Co., Stockbridge, GA							Number of Reports: 71		
Product: 0089	WU: Washed	Sampled From: Belt			Used In: B - 400						
Screen Size	1/2" 3/8"	No. 4	No. 8	No. 16	No. 50	No. 200					
Lower Spec	100 90	20	0	0	0	0					
Upper Spec	100 100	55	15	10	5	100					
Lower Target			93		23	0	0				
Upper Target			100		43	7	5	1			
Mean	100.0 99.0	27.6	1.3	0.9	0.6	0.8					
StdDev	0.0 0.4	2.0	0.8	0.5	0.4						
No. of samples	71 71	71	71	71	71	71	1	0	0	0	
RFTB											
Factor											
Score	0.0 0.4	2.0	0.8	0.5	0.4	0.0	0.0	0.0	0.0	97.3	

Source Number and Name: 050C		Vulcan Materials Co., Stockbridge, GA							Number of Reports: 101		
Product: 15CR-2	WU: Unwashed	Sampled From: Stockpile			Used In: H - 310 Gab						
Screen Size	2" 1 1/2"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 10	No. 60	No. 200		
Lower Spec	100 97	60	0	0	0	0	25	5	4		
Upper Spec	100 100	90	100	100	100	100	45	30	11		
Lower Target			98		70		32	8	6		
Upper Target			100		86		40	25	9		
Mean	100.0 100.0	82.9	67.2	59.3	45.7		35.2	16.7	7.1		
StdDev	0.0 0.0	2.0	2.7	2.8	2.4		1.6	1.0	0.5		
No. of samples	101 101	101	101	101	101	0	101	37	37		
RFTB			0.0				0.0	0.0	0.0		
Factor			0.0				0.0	0.0	0.0		
Score			0.0				0.0	0.0	0.0	100.0	

Source Number and Name: 050C		Aggregate Rating for 1/1/2011 to 6/30/2011 Vulcan Materials Co., Stockbridge, GA								Number of Reports: 32	
Product: AW10	WU: Washed	Sampled From: Stockpile			Used In: B - 400						
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	99.8	81.3	53.7	35.9	18.9	6.5	1.8			
StdDev	0.0	0.2	2.0	2.0	2.4	2.1	1.1	0.5			
No. of samples	32	32	32	32	32	32	32	32	0	0	
RFTB Factor											
Score	0.0	0.2	2.0	2.5	3.0	2.6	1.4	0.6	0.0	0.0	91.9

Source Number and Name: 052C		Martin Marietta Aggregates, Camak, GA								Number of Reports: 88	
Product: 0057	WU: Washed	Sampled From: Belt			Used In: A - 500						
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target											
Upper Target											
Mean	100.0	97.8	83.5	37.3	15.0	1.4	0.4				
StdDev	0.0	0.6	3.4	3.9	2.8	0.4	0.1				
No. of samples	88	88	88	88	88	88	88	0	0	0	
RFTB Factor											
Score	0.0		0.0		0.0		0.0		100.0		

Source Number and Name: 052C		Martin Marietta Aggregates, Camak, GA								Number of Reports: 88	
Product: 0057	WU: Washed	Sampled From: Belt			Used In: B - 400						
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target											
Upper Target											
Mean	100.0	97.8	83.5	37.3	15.0	1.4	0.4				
StdDev	0.0	0.6	3.4	3.9	2.8	0.4	0.1				
No. of samples	88	88	88	88	88	88	88	0	0	0	
RFTB Factor											
Score	0.0	0.6	3.4	3.9	2.8	0.4	0.1	0.0	0.0	0.0	92.5

Source Number and Name: 052C			Aggregate Rating for 1/1/2011 to 6/30/2011					Number of Reports: 87			
Product:0067	WU: Washed		Sampled From: Belt			Used In: A - 500					
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	0	20	0	0	0				
Upper Spec	100	100	100	55	10	5	100				
Lower Target		93		23	0	0					
Upper Target		100		45	5	1					
Mean	100.0	98.2	63.3	29.5	1.8	0.6	0.0				
StdDev	0.0	1.0	5.4	3.7	0.5	0.2	0.1				
No. of samples	87	87	87	87	87	87	87	0	0	0	
RFTB		0.0		0.0	0.0	0.0					
Factor		0.0		0.0	0.0	0.0					
Score		0.0		0.0	0.0	0.0		100.0			

Source Number and Name: 052C			Martin Marietta Aggregates, Camak, GA					Number of Reports: 87			
Product:0067	WU: Washed		Sampled From: Belt			Used In: B - 400					
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	0	20	0	0	0				
Upper Spec	100	100	100	55	10	5	100				
Lower Target		93		23	0	0					
Upper Target		100		45	5	1					
Mean	100.0	98.2	63.3	29.5	1.8	0.6	0.0				
StdDev	0.0	1.0	5.4	3.7	0.5	0.2	0.1				
No. of samples	87	87	87	87	87	87	87	0	0	0	
RFTB											
Factor											
Score	0.0	1.0	5.4	3.7	0.5	0.2	0.1	0.0	0.0	0.0	92.7

Source Number and Name: 052C			Martin Marietta Aggregates, Camak, GA					Number of Reports: 15			
Product:0078	WU: Washed		Sampled From: Belt			Used In: B - 400					
Screen Size	3/4"	1/2"	3/8"	No. 4	No. 8	No. 16	No. 200				
Lower Spec	100	90	40	5	0	0	0				
Upper Spec	100	100	75	25	10	5	100				
Lower Target											
Upper Target											
Mean	100.0	92.7	59.4	9.3	1.4	0.4	0.2				
StdDev	0.0	1.7	4.2	1.6	0.5	0.5	0.3				
No. of samples	15	15	15	15	15	15	15	0	0	0	
RFTB											
Factor											
Score	0.0	1.7	4.2	1.6	0.5	0.5	0.3	0.0	0.0	0.0	94.1

Source Number and Name: 052C		Aggregate Rating for 1/1/2011 to 6/30/2011									
Product: 0089		WU: Washed		Sampled From: Belt			Used In: B - 400		Number of Reports: 41		
Screen Size	1/2"	3/8"	No. 4	No. 8	No. 16	No. 50	No. 200				
Lower Spec	100	90	20	0	0	0	0				
Upper Spec	100	100	55	15	10	5	100				
Lower Target		93	23	0	0	0					
Upper Target		100	43	7	5	1					
Mean	100.0	99.5	38.1	3.1	1.2	0.6	0.3				
StdDev	0.0	0.5	4.8	1.1	0.6	0.2	0.1				
No. of samples	41	41	41	41	41	41	41	0	0	0	
RFTB Factor Score	0.0	0.5	4.8	1.1	0.6	0.2	0.1	0.0	0.0	0.0	95.1

Source Number and Name: 052C		Aggregate Rating for 1/1/2011 to 6/30/2011									
Product: 0M10		WU: Unwashed		Sampled From: Stockpile			Used In: B - 400		Number of Reports: 55		
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	99.4	84.7	64.1	50.0	36.7	24.1	14.3			
StdDev	0.0	0.7	1.2	2.4	2.3	1.8	1.2	0.6			
No. of samples	55	55	55	55	55	55	55	55	0	0	
RFTB Factor Score	0.0	0.7	1.2	2.8	2.7	2.1	1.4	0.7	0.0	0.0	92.2

Source Number and Name: 052C		Aggregate Rating for 1/1/2011 to 6/30/2011									
Product: 15CR-2		WU: Unwashed		Sampled From: Stockpile			Used In: H - 310 Gab		Number of Reports: 121		
Screen Size	2"	1 1/2"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 10	No. 60	No. 200	
Lower Spec	100	97	60	0	0	0	0	25	5	4	
Upper Spec	100	100	90	100	100	100	100	45	30	11	
Lower Target		98	70					32	8	6	
Upper Target		100	86					40	25	9	
Mean	100.0	99.8	81.6	69.0	62.0	48.0		35.2	16.7	7.5	
StdDev	0.0	0.3	2.8	3.7	3.7	3.3		2.2	1.2	0.6	
No. of samples	121	121	121	121	121	121	0	121	27	27	
RFTB Factor Score		0.0	0.0					0.0	0.0	0.0	100.0

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 052C		Martin Marietta Aggregates, Camak, GA							Number of Reports: 27			
Product:	AW10	WU:	Washed			Sampled From: Stockpile		Used In: B - 400				
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200				
Lower Spec	0	0	0	0	0	0	0	0				
Upper Spec	100	100	100	100	100	100	100	100				
Lower Target												
Upper Target												
Mean	100.0	99.5	82.9	57.7	40.7	24.8	11.2	4.5				
StdDev	0.0	0.3	1.6	2.9	2.5	1.5	0.5	0.4				
No. of samples	27	27	27	27	27	27	27	27	0	0		
RFTB Factor Score	0.0	0.3	1.6	3.5	3.0	1.8	0.6	0.5	0.0	0.0	92.5	

Source Number and Name: 052T		Martin Marietta Aggregates, Cayce, SC							Number of Reports: 11			
Product:	0067	WU:	Washed			Sampled From: Belt		Used In: A - 500				
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200					
Lower Spec	100	90	0	20	0	0	0					
Upper Spec	100	100	100	55	10	5	100					
Lower Target	93		23		0		0					
Upper Target	100		45		5		1					
Mean	100.0	96.6	57.0	26.3	2.3	1.3	1.0					
StdDev	0.0	1.4	4.3	3.7	0.8	0.5	0.7					
No. of samples	11	11	11	11	11	11	8	0	0	0		
RFTB Factor Score	0.0		0.4		0.0		0.8					
	0.0		5.0		0.0		0.0					
	0.0		2.0		0.0		0.0		98.0			

Source Number and Name: 052V		Martin Marietta Aggregates, Savannah, GA							Number of Reports: 66			
Product:	0057	WU:	Washed			Sampled From: Stockpile		Used In: A - 500				
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	95	0	25	0	0	0	0				
Upper Spec	100	100	100	60	100	10	5	100				
Lower Target	97		32		0		0					
Upper Target	100		48		5		1					
Mean	100.0	98.4	85.7	42.0	21.8	2.3	0.7					
StdDev	0.0	1.1	8.2	5.3	6.5	1.2	0.3					
No. of samples	66	66	66	66	66	66	66	0	0	0		
RFTB Factor Score	0.0		0.0		0.0		0.0					
	0.0		0.0		0.0		0.0		100.0			

Source Number and Name: 052V		Aggregate Rating for 1/1/2011 to 6/30/2011									
Product:0067		WU: Washed		Sampled From: Stockpile		Used In: A - 500		Number of Reports: 61			
Screen Size		1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	90		0	20	0	0	0			
Upper Spec	100	100		100	55	10	5	100			
Lower Target		93			23	0	0				
Upper Target		100			45	5	1				
Mean	100.0	99.0		69.1	35.3	3.1	0.7				
StdDev	0.0	0.6		6.4	5.1	1.4	0.3				
No. of samples	61	61		61	61	61	61	0	0	0	0
RFTB		0.0			0.0	0.0	0.0				
Factor		0.0			0.0	0.0	0.0				
Score		0.0			0.0	0.0	0.0	100.0			

Source Number and Name: 052V		Martin Marietta Aggregates, Savannah, GA									
Product:0067		WU: Washed		Sampled From: Stockpile		Used In: B - 400		Number of Reports: 61			
Screen Size		1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	90		0	20	0	0	0			
Upper Spec	100	100		100	55	10	5	100			
Lower Target		93			23	0	0				
Upper Target		100			45	5	1				
Mean	100.0	99.0		69.1	35.3	3.1	0.7				
StdDev	0.0	0.6		6.4	5.1	1.4	0.3				
No. of samples	61	61		61	61	61	61	0	0	0	0
RFTB		0.0			0.0	0.0	0.0				
Factor		0.0			0.0	0.0	0.0				
Score	0.0	0.6		6.4	5.1	1.4	0.3	0.0	0.0	0.0	0.0

Source Number and Name: 052V		Martin Marietta Aggregates, Savannah, GA									
Product:0078		WU: Washed		Sampled From: Stockpile		Used In: B - 400		Number of Reports: 13			
Screen Size		3/4"	1/2"	3/8"	No. 4	No. 8	No. 16	No. 200			
Lower Spec	100	90		40	5	0	0	0			
Upper Spec	100	100		75	25	10	5	100			
Lower Target											
Upper Target											
Mean	100.0	95.6		63.1	15.5	1.8	0.8				
StdDev	0.0	1.9		5.8	3.3	0.6	0.2				
No. of samples	13	13		13	13	13	13	0	0	0	0
RFTB		0.0			0.0	0.0	0.0				
Factor		0.0			0.0	0.0	0.0				
Score	0.0	1.9		5.8	3.3	0.6	0.2	0.0	0.0	0.0	0.0

Source Number and Name: 052V		Aggregate Rating for 1/1/2011 to 6/30/2011									
Product: 0089		Martin Marietta Aggregates, Savannah, GA									
WU:	Washed	Sampled From: Stockpile					Used In: B - 400			Number of Reports: 34	
Screen Size	1/2"	3/8"	No. 4	No. 8	No. 16	No. 50	No. 200				
Lower Spec	100	90	20	0	0	0	0				
Upper Spec	100	100	55	15	10	5	100				
Lower Target		93	23	0	0	0					
Upper Target		100	43	7	5	1					
Mean	100.0	99.2	38.9	5.8	2.4	0.9					
StdDev	0.0	0.4	4.0	1.5	0.6	0.4					
No. of samples	34	34	34	34	34	34	0	0	0	0	
RFTB Factor Score	0.0	0.4	4.0	1.5	0.6	0.4	0.0	0.0	0.0	0.0	95.4

Source Number and Name: 052V		Martin Marietta Aggregates, Savannah, GA									
Product: 0M10		Martin Marietta Aggregates, Savannah, GA									
WU:	Unwashed	Sampled From: Stockpile					Used In: B - 400			Number of Reports: 22	
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	99.3	84.5	64.2		35.3	23.8	13.4			
StdDev	0.0	0.5	2.3	3.6		4.4	4.0	3.1			
No. of samples	22	22	22	22	0	22	22	22	0	0	
RFTB Factor Score	0.0	0.5	2.3	4.3	0.0	5.2	4.7	3.7	0.0	0.0	86.2

Source Number and Name: 052V		Martin Marietta Aggregates, Savannah, GA									
Product: 15CR-2		Martin Marietta Aggregates, Savannah, GA									
WU:	Unwashed	Sampled From: Stockpile					Used In: H - 310 Gab			Number of Reports: 53	
Screen Size	2"	1 1/2"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 10	No. 60	No. 200	
Lower Spec	100	97	60	0	0	0	0	25	5	4	
Upper Spec	100	100	90	100	100	100	100	45	30	11	
Lower Target		98	70					32	8	6	
Upper Target		100	86					40	25	9	
Mean	100.0	100.0	83.8	70.7	63.4	48.6		35.3	17.1	7.4	
StdDev	0.0	0.1	2.6	4.8	6.1	5.8		3.0	1.7	0.9	
No. of samples	53	53	53	53	53	53	0	53	13	13	
RFTB Factor Score		0.0	0.4					0.0	0.0	0.0	
		0.0	5.0					0.0	0.0	0.0	
		0.0	2.0					0.0	0.0	0.0	98.0

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 054C		Martin Marietta Aggregates, Ruby, GA						Number of Reports: 124			
Product: 0007	WU: Washed	Sampled From: Belt				Used In: B - 400					
Screen Size	3/4"	1/2"	3/8"	No. 4	No. 8	No. 16	No. 200				
Lower Spec	100	90	40	0	0	0	0				
Upper Spec	100	100	70	15	5	100	100				
Lower Target		93	45	0	0						
Upper Target		100	60	9	1						
Mean	100.0	93.3	55.6	2.4	0.4			0.3			
StdDev	0.0	1.2	3.9	1.0	0.2			0.1			
No. of samples	124	124	124	124	124	0	11	0	0	0	
RFTB Factor											
Score	0.0	1.2	3.9	1.0	0.2	0.0	0.1	0.0	0.0	0.0	95.7

Source Number and Name: 054C		Martin Marietta Aggregates, Ruby, GA						Number of Reports: 196			
Product: 0057	WU: Washed	Sampled From: Belt				Used In: A - 500					
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target		97		32		0	0				
Upper Target		100		48		5	1				
Mean	100.0	98.3	86.0	41.1	18.9	1.2	0.2	0.2			
StdDev	0.0	0.9	2.9	3.6	3.0	0.5	0.1				
No. of samples	196	196	196	196	196	196	196	1	0	0	
RFTB Factor		0.0		0.0		0.0	0.0				
Score		0.0		0.0		0.0	0.0				100.0

Source Number and Name: 054C		Martin Marietta Aggregates, Ruby, GA						Number of Reports: 139			
Product: 0067	WU: Washed	Sampled From: Belt				Used In: A - 500					
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	0	20	0	0	0				
Upper Spec	100	100	100	55	10	5	100				
Lower Target		93		23		0	0				
Upper Target		100		45		5	1				
Mean	100.0	98.4	62.4	32.7	1.6	0.3					
StdDev	0.0	0.7	5.1	4.7	0.6	0.2					
No. of samples	139	139	139	139	139	139	0	0	0	0	
RFTB Factor		0.0		0.0		0.0	0.0				
Score		0.0		0.0		0.0	0.0				100.0

Source Number and Name: 054C		Aggregate Rating for 1/1/2011 to 6/30/2011									
Product: 0089		Martin Marietta Aggregates, Ruby, GA							Number of Reports: 181		
WU:	Washed	Sampled From: Belt					Used In: B - 400				
Screen Size	1/2" 3/8"	No. 4	No. 8	No. 16	No. 50	No. 200					
Lower Spec	100 90	20	0	0	0	0					
Upper Spec	100 100	55	15	10	5	100					
Lower Target		93	23	0	0	0					
Upper Target		100	43	7	5	1					
Mean	100.0 99.9	30.5	2.5	0.7	0.6	0.3					
StdDev	0.0 0.2	4.9	1.2	0.4	0.4	0.1					
No. of samples	181 181	181	181	181	181	5	0	0	0		
RFTB Factor Score	0.0 0.2	4.9	1.2	0.4	0.4	0.1	0.0	0.0	0.0	95.2	

Source Number and Name: 054C		Martin Marietta Aggregates, Ruby, GA										
Product: 0M10		Sampled From: Stockpile							Used In: B - 400		Number of Reports: 21	
WU:	Unwashed											
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200				
Lower Spec	0 0	0	0	0	0	0	0	0				
Upper Spec	100 100	100	100	100	100	100	100	100				
Lower Target												
Upper Target												
Mean	100.0 95.3	73.6	54.9	42.3	32.3	23.7	15.7					
StdDev	0.0 0.9	2.5	2.7	2.4	2.4	1.8	1.4					
No. of samples	21 21	21	21	21	21	21	21	21	0	0		
RFTB Factor Score	0.0 0.9	2.5	3.7	3.3	3.3	2.4	1.9	0.0	0.0	88.0		

Source Number and Name: 054C		Martin Marietta Aggregates, Ruby, GA										
Product: 15CR-2		Sampled From: Stockpile							Used In: H - 310 Gab		Number of Reports: 105	
WU:	Unwashed											
Screen Size	2" 1 1/2"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 10	No. 60	No. 200			
Lower Spec	100 97	60	0	0	0	0	25	5	4			
Upper Spec	100 100	90	100	100	100	100	45	30	11			
Lower Target		98	70				32	8	6			
Upper Target		100	86				40	25	9			
Mean	100.0 100.0	79.3	62.7	57.6	50.2		35.6	15.9	7.8			
StdDev	0.0 0.0	4.4	5.4	5.3	5.4		3.5	1.8	0.9			
No. of samples	105 105	105	105	105	105	0	105	23	23			
RFTB Factor Score		0.0	0.0				0.0	0.0	0.0			
		0.0	0.0				0.0	0.0	0.0			
		0.0	0.0				0.0	0.0	0.0	100.0		

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 054C		Martin Marietta Aggregates, Ruby, GA								
Product: 15CR-2B	WU: Unwashed	Sampled From: Belt			Used In: H - 310 Gab			Number of Reports: 25		
Screen Size	2" 1 1/2"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 10	No. 60	No. 200	
Lower Spec	100	97	60	0	0	0	25	5	4	
Upper Spec	100	100	90	100	100	100	45	35	11	
Lower Target		98	70				30	8	6	
Upper Target		100	86				38	25	9	
Mean	100.0	100.0	81.4	62.5	56.6	48.0	33.7	15.1	7.6	
StdDev	0.0	0.0	3.3	4.1	4.0	4.0	3.2	1.7	0.7	
No. of samples	25	25	25	25	25	25	0	25	22	22
RFTB		0.0	0.0				0.0	0.0	0.0	
Factor		0.0	0.0				0.0	0.0	0.0	
Score		0.0	0.0				0.0	0.0	0.0	100.0

Source Number and Name: 054C		Martin Marietta Aggregates, Ruby, GA									
Product: AW10	WU: Washed	Sampled From: Stockpile			Used In: B - 400			Number of Reports: 21			
Screen Size	3/8" No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200				
Lower Spec	0	0	0	0	0	0	0				
Upper Spec	100	100	100	100	100	100	100				
Lower Target											
Upper Target											
Mean	100.0	94.5	68.3	45.7		19.6	9.2	3.8			
StdDev	0.0	1.6	2.0	1.7		1.1	0.8	0.5			
No. of samples	21	21	21	21	0	21	21	21	0	0	
RFTB											
Factor											
Score	0.0	1.6	2.0	2.5	0.0	1.6	1.2	0.7	0.0	0.0	93.6

Source Number and Name: 054V		Reames & Son, Valdosta, GA								
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: A - 500			Number of Reports: 11		
Screen Size	1 1/2" 1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100		
Lower Target		97		32		0	0			
Upper Target		100		48		5	1			
Mean	100.0	97.7		34.5		2.8	0.6			
StdDev	0.0	0.7		4.1		0.7	0.6			
No. of samples	11	11	0	11	0	11	11	0	0	0
RFTB		0.0		1.6		0.0	0.2			
Factor		0.0		5.0		0.0	0.0			
Score		0.0		8.0		0.0	0.0			92.0

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 055V		Martin Marietta Aggregates, Savannah, GA							Number of Reports: 57		
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: A - 500						
Screen Size	1 1/2" 1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100 95	0	25	0	0	0	0				
Upper Spec	100 100	100	60	100	10	5	100				
Lower Target			32		0	0					
Upper Target			48		5	1					
Mean	100.0 99.1	80.6	39.7	19.8	2.6	0.9					
StdDev	0.0 0.5	8.4	5.1	6.8	1.3	0.3					
No. of samples	57 57	57	57	57	57	57	0	0	0		
RFTB			0.0		0.0	0.2					
Factor			0.0		0.0	0.0					
Score			0.0		0.0	0.0		100.0			

Source Number and Name: 055V		Martin Marietta Aggregates, Savannah, GA							Number of Reports: 57		
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: B - 400						
Screen Size	1 1/2" 1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100 95	0	25	0	0	0	0				
Upper Spec	100 100	100	60	100	10	5	100				
Lower Target			32		0	0					
Upper Target			48		5	1					
Mean	100.0 99.1	80.6	39.7	19.8	2.6	0.9					
StdDev	0.0 0.5	8.4	5.1	6.8	1.3	0.3					
No. of samples	57 57	57	57	57	57	57	0	0	0		
RFTB											
Factor											
Score	0.0 0.5	8.4	5.1	6.8	1.3	0.3	0.0	0.0	0.0	85.1	

Source Number and Name: 055V		Martin Marietta Aggregates, Savannah, GA							Number of Reports: 10		
Product: 0067	WU: Washed	Sampled From: Stockpile			Used In: A - 500						
Screen Size	1" 3/4"	1/2"	3/8"	No. 4	No. 8	No. 200					
Lower Spec	100 90	0	20	0	0	0					
Upper Spec	100 100	100	55	10	5	100					
Lower Target			23		0	0					
Upper Target			45		5	1					
Mean	100.0 99.1	65.9	37.6	3.0	0.8						
StdDev	0.0 0.5	11.1	6.3	2.0	0.3						
No. of samples	10 10	10	10	10	10	0	0	0	0		
RFTB			0.0	0.0	0.1						
Factor			0.0	0.0	0.0						
Score			0.0	0.0	0.0		100.0				

Source Number and Name: 055V		Aggregate Rating for 1/1/2011 to 6/30/2011									
Product: 0067		Martin Marietta Aggregates, Savannah, GA									
WU:	Washed	Sampled From: Stockpile					Used In: B - 400			Number of Reports: 10	
Screen Size	1" 3/4"	1/2"	3/8"	No. 4	No. 8	No. 200					
Lower Spec	100	90	0	20	0	0					
Upper Spec	100	100	100	55	10	5	100				
Lower Target		93		23	0	0					
Upper Target		100		45	5	1					
Mean	100.0	99.1	65.9	37.6	3.0	0.8					
StdDev	0.0	0.5	11.1	6.3	2.0	0.3					
No. of samples	10	10	10	10	10	10	0	0	0	0	
RFTB Factor Score	0.0	0.5	11.1	6.3	2.0	0.3	0.0	0.0	0.0	0.0	86.5

Source Number and Name: 055V		Martin Marietta Aggregates, Savannah, GA									
Product: 0089		Martin Marietta Aggregates, Savannah, GA									
WU:	Washed	Sampled From: Stockpile					Used In: B - 400			Number of Reports: 10	
Screen Size	1/2" 3/8"	No. 4	No. 8	No. 16	No. 50	No. 200					
Lower Spec	100	90	20	0	0	0					
Upper Spec	100	100	55	15	10	5	100				
Lower Target		93	23	0	0	0					
Upper Target		100	43	7	5	1					
Mean	100.0	98.9	43.3	8.7	4.0	1.2					
StdDev	0.0	0.2	5.3	2.2	1.3	0.4					
No. of samples	10	10	10	10	10	10	0	0	0	0	
RFTB Factor Score	0.0	0.2	5.3	2.2	1.3	0.4	0.0	0.0	0.0	0.0	93.7

Source Number and Name: 055V		Martin Marietta Aggregates, Savannah, GA									
Product: 15CR-2		Martin Marietta Aggregates, Savannah, GA									
WU:	Unwashed	Sampled From: Stockpile					Used In: H - 310 Gab			Number of Reports: 40	
Screen Size	2" 1 1/2"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 10	No. 60	No. 200		
Lower Spec	100	97	60	0	0	0	25	5	4		
Upper Spec	100	100	90	100	100	100	45	30	11		
Lower Target		98	70				32	8	6		
Upper Target		100	86				40	25	9		
Mean	100.0	100.0	82.6	69.8	63.3	51.2	37.3	15.7	6.4		
StdDev	0.0	0.0	3.3	4.4	4.9	5.1	2.9	2.6	0.9		
No. of samples	40	40	40	40	40	40	0	40	13	13	
RFTB Factor Score		0.0	0.0				0.2	0.0	0.5		
		0.0	0.0				5.0	0.0	0.0		
		0.0	0.0				1.0	0.0	0.0		99.0

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 057V

Aggregates USA, Springfield, GA

Product:	0057	WU:	Washed	Sampled From:	Stockpile	Used In:	A - 500	Number of Reports:	20
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200	
Lower Spec	100	95	0	25	0	0	0	0	
Upper Spec	100	100	100	60	100	10	5	100	
Lower Target		97		32		0	0		
Upper Target		100		48		5	1		
Mean	100.0	99.8	86.8	33.7	16.4	2.2	0.9		
StdDev	0.0	0.3	1.7	1.0	1.1	0.3	0.2		
No. of samples	20	20	20	20	20	20	20	0	0
RFTB		0.0		0.0		0.0	0.1		
Factor		0.0		0.0		0.0	0.0		
Score		0.0		0.0		0.0	0.0		100.0

Source Number and Name: 058F

Vulcan Materials Co., Rabun Co., GA

Product:	10SM	WU:	Washed	Sampled From:	Stockpile	Used In:	A - 500	Number of Reports:	45
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200	
Lower Spec	100	95	0	45	0	8	1	0	
Upper Spec	100	100	100	95	100	30	10	4	
Lower Target		97		51		12	2	0	
Upper Target		100		90		24	9	3	
Mean	100.0	98.1	77.6	58.4	41.6	22.6	7.4	1.9	
StdDev	0.0	0.5	1.5	2.0	1.9	1.5	1.1	0.4	
No. of samples	45	45	45	45	45	45	45	45	0
RFTB		0.0		0.0		0.1	0.0	0.0	0
Factor		0.0		0.0		5.0	0.0	0.0	0
Score		0.0		0.0		0.5	0.0	0.0	99.5

Source Number and Name: 058V

Martin Marietta Aggregates, Brunswick

Product:	0067	WU:	Washed	Sampled From:	Stockpile	Used In:	A - 500	Number of Reports:	71
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200		
Lower Spec	100	90	0	20	0	0	0		
Upper Spec	100	100	100	55	10	5	100		
Lower Target		93		23		0	0		
Upper Target		100		45		5	1		
Mean	100.0	96.8	56.9	31.8	3.6	1.1			
StdDev	0.0	1.8	5.6	6.2	1.2	0.3			
No. of samples	71	71	71	71	71	71	0	0	0
RFTB		0.0		0.0	0.0	0.4			
Factor		0.0		0.0	0.0	0.0			
Score		0.0		0.0	0.0	0.0			100.0

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 062V		Aggregates USA, Surrency, GA							Number of Reports: 34		
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: A - 500						
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target		97		32		0	0				
Upper Target		100		48		5	1				
Mean	100.0	99.9	89.4	41.4	18.1	2.6	0.9				
StdDev	0.0	0.2	2.4	4.3	2.3	0.7	0.3				
No. of samples	34	34	34	34	34	34	34	0	0	0	
RFTB		0.0		0.0		0.0	0.2				
Factor		0.0		0.0		0.0	0.0				
Score		0.0		0.0		0.0	0.0		100.0		

Source Number and Name: 062V		Aggregates USA, Surrency, GA							Number of Reports: 39		
Product: 0067	WU: Washed	Sampled From: Stockpile			Used In: A - 500						
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	0	20	0	0	0				
Upper Spec	100	100	100	55	10	5	100				
Lower Target		93		23	0	0					
Upper Target		100		45	5	1					
Mean	100.0	95.8	65.0	33.1	3.2	1.1	0.5				
StdDev	0.0	1.3	4.7	4.6	1.3	0.2	0.2				
No. of samples	39	39	39	39	39	39	1	0	0	0	
RFTB		0.0		0.0	0.0	0.3					
Factor		0.0		0.0	0.0	0.0					
Score		0.0		0.0	0.0	0.0		100.0			

Source Number and Name: 063V		Aggregates USA, Ellabell, GA							Number of Reports: 12		
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: A - 500						
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target		97		32		0	0				
Upper Target		100		48		5	1				
Mean	100.0	99.9	89.1	42.1	19.3	3.4	1.0				
StdDev	0.0	0.2	2.3	4.1	3.5	1.5	0.4				
No. of samples	12	12	12	12	12	12	12	0	0	0	
RFTB		0.0		0.0		0.0	0.4				
Factor		0.0		0.0		0.0	0.0				
Score		0.0		0.0		0.0	0.0		100.0		

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 065C			Vulcan Materials Co., McCollum, GA					Number of Reports: 15			
Product: 0007	WU: Washed		Sampled From: Belt			Used In: B - 400					
Screen Size	3/4"	1/2"	3/8"	No. 4	No. 8	No. 16	No. 200				
Lower Spec	100	90	40	0	0	0	0				
Upper Spec	100	100	70	15	5	100	100				
Lower Target		93	45	0	0						
Upper Target		100	60	9	1						
Mean	100.0	92.8	45.3	2.3	0.7						
StdDev	0.0	0.8	1.2	0.4	0.1						
No. of samples	13	13	13	13	13	0	0	0	0	0	
RFTB Factor											
Score	0.0	0.8	1.2	0.4	0.1	0.0	0.0	0.0	0.0	0.0	98.3

Source Number and Name: 065C			Vulcan Materials Co., McCollum, GA					Number of Reports: 110			
Product: 0057	WU: Washed		Sampled From: Belt			Used In: A - 500					
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target		97		32		0	0				
Upper Target		100		48		5	1				
Mean	100.0	98.1	81.6	34.7	17.5	2.5	1.3				
StdDev	0.0	0.3	1.6	1.4	1.5	0.2	0.2				
No. of samples	102	102	102	102	102	102	102	0	0	0	
RFTB Factor		0.0		0.0		0.0	0.5				
Score		0.0		0.0		0.0	0.0		100.0		

Source Number and Name: 065C			Vulcan Materials Co., McCollum, GA					Number of Reports: 110			
Product: 0057	WU: Washed		Sampled From: Belt			Used In: B - 400					
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target		97		32		0	0				
Upper Target		100		48		5	1				
Mean	100.0	98.1	81.6	34.7	17.5	2.5	1.3				
StdDev	0.0	0.3	1.6	1.4	1.5	0.2	0.2				
No. of samples	102	102	102	102	102	102	102	0	0	0	
RFTB Factor											
Score	0.0	0.3	1.6	1.4	1.5	0.2	0.2	0.0	0.0	0.0	96.5

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 071C		Vulcan Materials Co., Siloam, GA							Number of Reports: 41	
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: B - 400					
Screen Size	1 1/2" 1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100 95	0	25	0	0	0	0			
Upper Spec	100 100	100	60	100	10	5	100			
Lower Target			32		0	0				
Upper Target			48		5	1				
Mean	100.0 98.4	83.1	37.2	17.0	1.5	0.8	0.0			
StdDev	0.0 0.4	3.0	1.8	3.3	0.4	0.2	0.0			
No. of samples	41 41	41	41	41	41	40	3	0	0	
RFTB Factor Score	0.0 0.4	3.0	1.8	3.3	0.4	0.2	0.0	0.0	0.0	93.9

Source Number and Name: 071C		Vulcan Materials Co., Siloam, GA							Number of Reports: 20	
Product: 0089	WU: Washed	Sampled From: Stockpile			Used In: B - 400					
Screen Size	1/2" 3/8"	No. 4	No. 8	No. 16	No. 50	No. 200				
Lower Spec	100 90	20	0	0	0	0				
Upper Spec	100 100	55	15	10	5	100				
Lower Target			23	0	0	0				
Upper Target			43	7	5	1				
Mean	100.0 99.4	29.1	3.7	1.7	0.0					
StdDev	0.0 0.1	2.6	0.6	0.4	0.0					
No. of samples	20 20	20	20	20	20	0	0	0	0	
RFTB Factor Score	0.0 0.1	2.6	0.6	0.4	0.0	0.0	0.0	0.0	0.0	97.5

Source Number and Name: 071C		Vulcan Materials Co., Siloam, GA							Number of Reports: 14	
Product: AW10	WU: Washed	Sampled From: Stockpile			Used In: B - 400					
Screen Size	3/8" No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0 0	0	0	0	0	0	0			
Upper Spec	100 100	100	100	100	100	100	100			
Lower Target										
Upper Target										
Mean	100.0 99.8	79.4	53.4	33.9	18.3	6.1	1.5			
StdDev	0.0 0.1	1.9	0.9	0.6	0.9	0.6	0.1			
No. of samples	14 14	14	14	14	14	14	14	0	0	
RFTB Factor Score	0.0 0.1	1.9	1.1	0.8	1.1	0.8	0.1	0.0	0.0	96.1

Source Number and Name: 075C		Aggregate Rating for 1/1/2011 to 6/30/2011								
Product: 0057		Vulcan Materials Co., LaGrange, GA								
WU: Washed		Sampled From: Belt			Used In: A - 500			Number of Reports: 112		
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200		
Lower Spec	100	95	0	25	0	0	0	0		
Upper Spec	100	100	100	60	100	10	5	100		
Lower Target		97		32		0	0			
Upper Target		100		48		5	1			
Mean	100.0	98.5	87.6	41.0	18.4	1.5	0.7			
StdDev	0.0	0.6	2.8	4.5	3.5	0.6	0.3			
No. of samples	104	104	104	104	104	104	104	0	0	0
RFTB		0.0		0.0		0.0	0.0			
Factor		0.0		0.0		0.0	0.0			
Score		0.0		0.0		0.0	0.0			100.0

Source Number and Name: 075C		Vulcan Materials Co., LaGrange, GA								
Product: AW10		Sampled From: Stockpile								
WU: Washed		Used In: B - 400			Number of Reports: 29					
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200		
Lower Spec	0	0	0	0	0	0	0	0		
Upper Spec	100	100	100	100	100	100	100	100		
Lower Target										
Upper Target										
Mean	100.0	100.0	86.2	65.3	46.9	29.2	13.1	3.4		
StdDev	0.0	0.1	1.5	1.9	1.9	1.8	1.3	0.5		
No. of samples	24	24	24	24	24	24	24	24	0	0
RFTB										
Factor										
Score	0.0	0.1	1.5	2.2	2.2	2.1	1.5	0.6	0.0	0.0

Source Number and Name: 077C		Vulcan Materials Company, Griffin, GA								
Product: 0007		Sampled From: Stockpile								
WU: Washed		Used In: B - 400			Number of Reports: 46					
Screen Size	3/4"	1/2"	3/8"	No. 4	No. 8	No. 16	No. 200			
Lower Spec	100	90	40	0	0	0	0			
Upper Spec	100	100	70	15	5	100	100			
Lower Target		93	45	0	0					
Upper Target		100	60	9	1					
Mean	100.0	92.4	51.5	2.7	1.3	0.7				
StdDev	0.0	1.5	4.7	1.0	0.6	0.5				
No. of samples	46	46	46	46	46	46	0	0	0	0
RFTB										
Factor										
Score	0.0	1.5	4.7	1.0	0.6	0.5	0.0	0.0	0.0	0.0

Source Number and Name: 077C		Aggregate Rating for 1/1/2011 to 6/30/2011									
Product: 0008		Vulcan Materials Company, Griffin, GA									
WU: Washed		Sampled From: Stockpile					Used In: B - 400			Number of Reports: 46	
Screen Size	1/2"	3/8"	No. 4	No. 8	No. 16	No. 50	No. 200				
Lower Spec	100	85	10	0	0	0	0				
Upper Spec	100	100	40	10	5	100	100				
Lower Target											
Upper Target											
Mean	100.0	97.6	14.4	2.6	1.7	0.8					
StdDev	0.0	1.4	3.6	0.9	0.8	0.5					
No. of samples	46	46	46	46	46	46	0	0	0	0	
RFTB											
Factor											
Score	0.0	1.4	3.6	0.9	0.8	0.5	0.0	0.0	0.0	0.0	95.2

Source Number and Name: 077C		Vulcan Materials Company, Griffin, GA									
Product: 0057		Sampled From: Stockpile									
WU: Washed		Used In: A - 500					Number of Reports: 160				
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target											
Upper Target											
Mean	100.0	99.3	86.1	36.2	16.8	2.3	1.2				
StdDev	0.0	1.1	3.7	3.4	3.5	0.7	0.6				
No. of samples	160	160	160	160	160	160	160	0	0	0	
RFTB											
Factor											
Score	0.0		0.0		0.0		0.0		0.0		100.0

Source Number and Name: 077C		Vulcan Materials Company, Griffin, GA									
Product: 15CR-2		Sampled From: Stockpile									
WU: Unwashed		Used In: H - 310 Gab					Number of Reports: 38				
Screen Size	2"	1 1/2"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 10	No. 60	No. 200	
Lower Spec	100	97	60	0	0	0	0	25	5	4	
Upper Spec	100	100	90	100	100	100	100	45	30	11	
Lower Target											
Upper Target											
Mean	100.0	99.8	74.3	62.1	57.4	47.6	38.4		15.6	6.2	
StdDev	0.0	0.3	3.1	3.2	3.1	2.4	1.6		1.2	0.7	
No. of samples	38	38	38	38	38	38	0	38	24	24	
RFTB											
Factor											
Score	0.0		0.0		0.0		0.0		0.0		100.0

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 077C		Vulcan Materials Company, Griffin, GA							Number of Reports: 45		
Product:	M810	WU:	Unwashed	Sampled From: Stockpile			Used In: B - 400				
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	96.8	78.3	62.0	45.6	28.5	16.3	8.9			
StdDev	0.0	0.8	2.2	2.6	2.8	2.6	2.1	1.2			
No. of samples	45	45	45	45	45	45	45	44	0	0	
RFTB Factor											
Score	0.0	0.8	2.2	3.3	3.6	3.3	2.7	1.5	0.0	0.0	88.4

Source Number and Name: 081C		Martin Marietta Aggregates, Warrenton, GA							Number of Reports: 17		
Product:	0006	WU:	Washed	Sampled From: Stockpile			Used In: B - 400				
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	20	0	0	0	0				
Upper Spec	100	100	55	15	5	100	100				
Lower Target											
Upper Target											
Mean	100.0	95.2	30.5	4.7	1.1						
StdDev	0.0	2.5	4.9	1.1	0.2						
No. of samples	17	17	17	17	17	0	0	0	0	0	
RFTB Factor											
Score	0.0	2.5	4.9	1.1	0.2	0.0	0.0	0.0	0.0	0.0	94.2

Source Number and Name: 081C		Martin Marietta Aggregates, Warrenton, GA							Number of Reports: 45		
Product:	0007	WU:	Washed	Sampled From: Stockpile			Used In: B - 400				
Screen Size	3/4"	1/2"	3/8"	No. 4	No. 8	No. 16	No. 200				
Lower Spec	100	90	40	0	0	0	0				
Upper Spec	100	100	70	15	5	100	100				
Lower Target											
Upper Target											
Mean	100.0	93.0	52.5	4.1	1.2			0.2			
StdDev	0.0	0.9	2.6	1.1	0.2			0.0			
No. of samples	45	45	45	45	45	0	2	0	0	0	
RFTB Factor											
Score	0.0	0.9	2.6	1.1	0.2	0.0	0.0	0.0	0.0	0.0	96.8

Source Number and Name: 081C		Aggregate Rating for 1/1/2011 to 6/30/2011									
Product: 0057		WU: Washed		Sampled From: Stockpile			Used In: A - 500		Number of Reports: 133		
		1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200		
Lower Spec		100	95	0	25	0	0	0	0		
Upper Spec		100	100	100	60	100	10	5	100		
Lower Target			97		32		0	0			
Upper Target			100		48		5	1			
Mean		100.0	98.8	80.4	35.5	16.0	2.1	1.0			
StdDev		0.0	0.3	1.9	1.4	1.3	0.4	0.2			
No. of samples		133	133	133	133	133	133	133	0	0	0
RFTB			0.0		0.0		0.0	0.2			
Factor			0.0		0.0		0.0	0.0			
Score			0.0		0.0		0.0	0.0		100.0	

Source Number and Name: 081C		Aggregate Rating for 1/1/2011 to 6/30/2011									
Product: 0067		WU: Washed		Sampled From: Stockpile			Used In: A - 500		Number of Reports: 122		
		1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec		100	90	0	20	0	0	0			
Upper Spec		100	100	100	55	10	5	100			
Lower Target			93		23	0	0				
Upper Target			100		45	5	1				
Mean		100.0	98.3	60.4	30.5	2.3	1.0				
StdDev		0.0	0.4	2.4	2.7	0.4	0.2				
No. of samples		122	122	122	122	122	122	0	0	0	0
RFTB			0.0		0.0	0.0	0.2				
Factor			0.0		0.0	0.0	0.0				
Score			0.0		0.0	0.0	0.0		100.0		

Source Number and Name: 081C		Aggregate Rating for 1/1/2011 to 6/30/2011									
Product: 0078		WU: Washed		Sampled From: Stockpile			Used In: B - 400		Number of Reports: 40		
		3/4"	1/2"	3/8"	No. 4	No. 8	No. 16	No. 200			
Lower Spec		100	90	40	5	0	0	0			
Upper Spec		100	100	75	25	10	5	100			
Lower Target											
Upper Target											
Mean		100.0	92.8	62.9	14.4	4.3	2.4				
StdDev		0.0	1.0	1.8	1.7	0.8	0.6				
No. of samples		40	40	40	40	40	40	0	0	0	0
RFTB											
Factor											
Score		0.0	1.0	1.8	1.7	0.8	0.6	0.0	0.0	0.0	96.1

Source Number and Name: 081C		Aggregate Rating for 1/1/2011 to 6/30/2011										
Product: 0089		WU: Washed		Sampled From: Stockpile			Used In: B - 400		Number of Reports: 70			
Screen Size	1/2"	3/8"	No. 4	No. 8	No. 16	No. 50	No. 200					
Lower Spec	100	90	20	0	0	0	0					
Upper Spec	100	100	55	15	10	5	100					
Lower Target		93	23	0	0	0						
Upper Target		100	43	7	5	1						
Mean	100.0	98.5	35.2	6.1	3.3	1.2						
StdDev	0.0	0.5	1.7	0.6	0.5	0.2						
No. of samples	70	70	70	70	70	70	0	0	0	0		
RFTB Factor Score	0.0	0.5	1.7	0.6	0.5	0.2	0.0	0.0	0.0	0.0	97.7	

Source Number and Name: 081C		Aggregate Rating for 1/1/2011 to 6/30/2011										
Product: 0M10		WU: Unwashed		Sampled From: Stockpile			Used In: B - 400		Number of Reports: 62			
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200				
Lower Spec	0	0	0	0	0	0	0	0				
Upper Spec	100	100	100	100	100	100	100	100				
Lower Target												
Upper Target												
Mean	100.0	98.1	82.5	63.1	48.0	30.5	17.5	9.6				
StdDev	0.0	0.4	1.7	1.1	1.5	1.6	0.9	0.7				
No. of samples	62	62	62	62	62	62	62	62	0	0		
RFTB Factor Score	0.0	0.4	1.7	1.3	1.8	1.9	1.1	0.8	0.0	0.0	93.9	

Source Number and Name: 081C		Aggregate Rating for 1/1/2011 to 6/30/2011										
Product: 15CR-2		WU: Unwashed		Sampled From: Stockpile			Used In: H - 310 Gab		Number of Reports: 155			
Screen Size	2"	1 1/2"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 10	No. 60	No. 200		
Lower Spec	100	97	60	0	0	0	0	25	5	4		
Upper Spec	100	100	90	100	100	100	100	45	30	11		
Lower Target		98	70					32	8	6		
Upper Target		100	86					40	25	9		
Mean	100.0	100.0	77.8	62.3	55.6	46.1	37.8	36.1	13.9	6.2		
StdDev	0.0	0.0	1.9	2.1	1.9	1.4	1.2	1.2	0.7	0.3		
No. of samples	155	155	155	155	155	155	155	155	38	38		
RFTB Factor Score		0.0	0.0					0.0	0.0	0.1		
		0.0	0.0					0.0	0.0	0.0		
		0.0	0.0					0.0	0.0	0.0	100.0	

Source Number and Name: 081C		Aggregate Rating for 1/1/2011 to 6/30/2011									
Product: AW10		WU: Washed		Sampled From: Stockpile			Used In: B - 400		Number of Reports: 63		
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	98.3	82.2	59.2	40.7	23.2	8.9	3.4			
StdDev	0.0	0.3	1.9	1.6	2.4	0.9	0.6	0.4			
No. of samples	63	63	63	63	63	63	63	63	0	0	
RFTB											
Factor											
Score	0.0	0.3	1.9	1.9	2.9	1.1	0.7	0.5	0.0	0.0	93.7

Source Number and Name: 082C		Columbus Quarry, LLC, Columbus, GA									
Product: 0057		WU: Washed		Sampled From: Belt			Used In: A - 500		Number of Reports: 39		
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target											
Upper Target											
Mean	100.0	98.3	86.2	42.1	21.7	4.0	0.9				
StdDev	0.0	0.9	4.0	3.6	1.7	0.5	0.1				
No. of samples	39	39	39	39	39	39	39	0	0	0	
RFTB											
Factor											
Score	0.0		0.0		0.0		0.0		100.0		

Source Number and Name: 082C		Columbus Quarry, LLC, Columbus, GA									
Product: 0067		WU: Washed		Sampled From: Belt			Used In: A - 500		Number of Reports: 117		
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	0	20	0	0	0				
Upper Spec	100	100	100	55	10	5	100				
Lower Target											
Upper Target											
Mean	100.0	95.1	49.9	27.7	4.1	0.9					
StdDev	0.0	0.5	1.6	1.4	0.3	0.1					
No. of samples	117	117	117	117	117	117	0	0	0	0	
RFTB											
Factor											
Score	0.0		0.0		0.0		0.0		100.0		

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 088C		Vulcan Materials Co., Lithonia, GA							Number of Reports: 82		
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: A - 500						
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target		97		32		0	0				
Upper Target		100		48		5	1				
Mean	100.0	99.2	80.8	40.6	22.6	2.6	1.1	0.4			
StdDev	0.0	0.4	2.7	3.6	2.9	0.6	0.2	0.1			
No. of samples	82	82	82	82	82	82	82	5	0	0	
RFTB		0.0		0.0		0.0	0.3				
Factor		0.0		0.0		0.0	0.0				
Score		0.0		0.0		0.0	0.0		100.0		

Source Number and Name: 088C		Vulcan Materials Co., Lithonia, GA							Number of Reports: 56		
Product: 0067	WU: Washed	Sampled From: Stockpile			Used In: A - 500						
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	0	20	0	0	0				
Upper Spec	100	100	100	55	10	5	100				
Lower Target		93		23	0	0					
Upper Target		100		45	5	1					
Mean	100.0	99.2	62.2	33.6	3.2	1.2	0.3				
StdDev	0.0	0.4	4.7	4.1	0.7	0.3	0.1				
No. of samples	56	56	56	56	56	56	5	0	0	0	
RFTB		0.0		0.0	0.0	0.5					
Factor		0.0		0.0	0.0	0.0					
Score		0.0		0.0	0.0	0.0		100.0			

Source Number and Name: 088C		Vulcan Materials Co., Lithonia, GA							Number of Reports: 34		
Product: 0089	WU: Washed	Sampled From: Stockpile			Used In: B - 400						
Screen Size	1/2"	3/8"	No. 4	No. 8	No. 16	No. 50	No. 200				
Lower Spec	100	90	20	0	0	0	0				
Upper Spec	100	100	55	15	10	5	100				
Lower Target		93	23	0	0	0					
Upper Target		100	43	7	5	1					
Mean	100.0	99.5	31.0	3.0	1.5	0.1	0.3				
StdDev	0.0	0.1	4.4	0.8	0.5	0.3	0.1				
No. of samples	34	34	34	34	34	34	2	0	0	0	
RFTB											
Factor											
Score	0.0	0.1	4.4	0.8	0.5	0.3	0.1	0.0	0.0	0.0	95.9

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 088C		Vulcan Materials Co., Lithonia, GA								
Product: 15CR-2	WU: Unwashed	Sampled From: Stockpile			Used In: H - 310 Gab			Number of Reports: 46		
Screen Size	2" 1 1/2"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 10	No. 60	No. 200	
Lower Spec	100 97	60	0	0	0	0	25	5	4	
Upper Spec	100 100	90	100	100	100	100	45	30	11	
Lower Target		98	70				32	8	6	
Upper Target		100	86				40	25	9	
Mean	100.0 99.8	76.4	63.4	56.9	45.4		36.1	15.5	6.9	
StdDev	0.0 0.3	3.4	3.4	3.0	2.4		1.8	0.7	0.5	
No. of samples	46 46	46	46	46	46	0	46	12	12	
RFTB		0.0	0.0				0.0	0.0	0.0	
Factor		0.0	0.0				0.0	0.0	0.0	
Score		0.0	0.0				0.0	0.0	0.0	100.0

Source Number and Name: 089C		Vulcan Materials Co., Villa Rica, GA								
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: A - 500			Number of Reports: 68		
Screen Size	1 1/2" 1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100 95	0	25	0	0	0	0			
Upper Spec	100 100	100	60	100	10	5	100			
Lower Target			97				0	0		
Upper Target			100				5	1		
Mean	100.0 98.4	86.2	37.8	17.2	1.7	0.7	0.0			
StdDev	0.0 0.6	4.2	2.8	4.8	0.8	0.2	0.0			
No. of samples	68 68	68	68	68	68	68	4	0	0	
RFTB		0.0	0.0		0.0	0.0				
Factor		0.0	0.0		0.0	0.0				
Score		0.0	0.0		0.0	0.0				100.0

Source Number and Name: 089C		Vulcan Materials Co., Villa Rica, GA								
Product: 0067	WU: Washed	Sampled From: Stockpile			Used In: A - 500			Number of Reports: 61		
Screen Size	1" 3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100 90	0	20	0	0	0				
Upper Spec	100 100	100	55	10	5	100				
Lower Target			93				0	0		
Upper Target			100				5	1		
Mean	100.0 97.6	61.9	28.1	1.9	0.7	0.0				
StdDev	0.0 1.1	7.8	3.6	0.8	0.2	0.0				
No. of samples	61 61	61	61	61	61	3	0	0	0	
RFTB		0.0	0.0	0.0	0.0					
Factor		0.0	0.0	0.0	0.0					
Score		0.0	0.0	0.0	0.0					100.0

Source Number and Name: 090C		Aggregate Rating for 1/1/2011 to 6/30/2011									
Product: 0067		Vulcan Materials Co., Blairsville, GA									
WU: Washed		Sampled From: Stockpile			Used In: A - 500			Number of Reports: 14			
Screen Size	1" 3/4"	1/2"	3/8"	No. 4	No. 8	No. 200					
Lower Spec	100 90	0	20	0	0	0					
Upper Spec	100 100	100	55	10	5	100					
Lower Target		93	23	0	0						
Upper Target		100	45	5	1						
Mean	100.0 94.0	51.1	28.8	2.7	0.9	0.0					
StdDev	0.0 2.2	2.1	1.9	0.7	0.3						
No. of samples	14 14	14	14	14	14	1	0	0	0		
RFTB		1.2	0.0	0.0	0.2						
Factor		5.0	0.0	0.0	0.0						
Score		6.0	0.0	0.0	0.0		94.0				

Source Number and Name: 099C		Hanson Aggregates, Fayette Co., GA									
Product: 0005		Sampled From: Stockpile						Used In: B - 400			
WU: Unwashed		Sampled From: Stockpile			Used In: B - 400			Number of Reports: 13			
Screen Size	1 1/2" 1"	3/4"	1/2"	3/8"	No. 4	No. 200					
Lower Spec	100 90	20	0	0	0	0					
Upper Spec	100 100	55	10	5	100	100					
Lower Target	100 93	23	0	0							
Upper Target		100	45	5	1						
Mean	100.0 94.7	37.1	4.3	2.7	2.4						
StdDev	0.0 1.9	4.7	1.6	1.2	1.2						
No. of samples	13 13	13	13	13	13	0	0	0	0		
RFTB											
Factor											
Score	0.0 1.9	4.7	1.6	1.2	1.2	0.0	0.0	0.0	0.0	0.0	92.9

Source Number and Name: 099C		Hanson Aggregates, Fayette Co., GA									
Product: 0006		Sampled From: Stockpile						Used In: B - 400			
WU: Unwashed		Sampled From: Stockpile			Used In: B - 400			Number of Reports: 21			
Screen Size	1" 3/4"	1/2"	3/8"	No. 4	No. 8	No. 200					
Lower Spec	100 90	20	0	0	0	0					
Upper Spec	100 100	55	15	5	100	100					
Lower Target		93	23	0	0						
Upper Target		100	40	7	1						
Mean	100.0 97.6	28.8	6.7	2.6	2.2						
StdDev	0.0 1.5	6.7	2.6	1.1	1.1						
No. of samples	21 21	21	21	21	20	0	0	0	0		
RFTB											
Factor											
Score	0.0 1.5	6.7	2.6	1.1	1.1	0.0	0.0	0.0	0.0	0.0	91.3

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 099C		Hanson Aggregates, Fayette Co., GA						Number of Reports: 42			
Product: 0007	WU: Unwashed	Sampled From: Stockpile				Used In: B - 400					
Screen Size	3/4"	1/2"	3/8"	No. 4	No. 8	No. 16	No. 200				
Lower Spec	100	90	40	0	0	0	0				
Upper Spec	100	100	70	15	5	100	100				
Lower Target		93	45	0	0						
Upper Target		100	60	9	1						
Mean	100.0	94.8	51.9	4.3	2.7	2.4					
StdDev	0.0	1.7	6.3	2.2	1.0	0.9					
No. of samples	42	42	42	42	42	42	0	0	0	0	
RFTB Factor Score	0.0	1.7	6.3	2.2	1.0	0.9	0.0	0.0	0.0	0.0	91.9

Source Number and Name: 099C		Hanson Aggregates, Fayette Co., GA						Number of Reports: 119			
Product: 0057	WU: Washed	Sampled From: Stockpile				Used In: A - 500					
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target		97		32		0	0				
Upper Target		100		48		5	1				
Mean	100.0	99.4	91.8	39.1	17.9	2.9	1.8	0.2			
StdDev	0.0	0.6	3.3	6.0	6.0	1.1	0.7	0.0			
No. of samples	119	119	119	119	119	118	118	3	0	0	
RFTB Factor Score		0.0		0.0		0.0	1.5				
		0.0		0.0		0.0	5.0				
		0.0		0.0		0.0	7.5				
											92.5

Source Number and Name: 099C		Hanson Aggregates, Fayette Co., GA						Number of Reports: 45			
Product: 0089	WU: Unwashed	Sampled From: Stockpile				Used In: B - 400					
Screen Size	1/2"	3/8"	No. 4	No. 8	No. 16	No. 50	No. 200				
Lower Spec	100	90	20	0	0	0	0				
Upper Spec	100	100	55	15	10	5	100				
Lower Target		93	23	0	0	0					
Upper Target		100	43	7	5	1					
Mean	100.0	99.9	41.8	8.9	5.6	3.1					
StdDev	0.0	0.3	6.9	3.1	1.9	1.1					
No. of samples	45	45	45	45	45	45	0	0	0	0	
RFTB Factor Score	0.0	0.3	6.9	3.1	1.9	1.1	0.0	0.0	0.0	0.0	91.1

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 099C		Hanson Aggregates, Fayette Co., GA							Number of Reports: 17			
Product:	AW10	WU:	Washed			Sampled From: Stockpile			Used In: B - 400			
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200				
Lower Spec	0	0	0	0	0	0	0	0				
Upper Spec	100	100	100	100	100	100	100	100				
Lower Target												
Upper Target												
Mean	100.0	99.7	84.1	64.1	45.5	24.9	9.3	3.0				
StdDev	0.0	0.1	2.3	3.6	3.5	3.1	1.7	0.5				
No. of samples	17	17	17	17	17	17	17	17	0	0		
RFTB Factor												
Score	0.0	0.1	2.3	4.3	4.2	3.7	2.0	0.6	0.0	0.0	88.6	

Source Number and Name: 101C		Hanson Aggregates, Demorest, GA							Number of Reports: 92			
Product:	0057	WU:	Washed			Sampled From: Stockpile			Used In: A - 500			
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	95	0	25	0	0	0	0				
Upper Spec	100	100	100	60	100	10	5	100				
Lower Target												
Upper Target												
Mean	100.0	99.3	82.1	41.6	22.9	3.1	1.4	0.5				
StdDev	0.0	0.5	4.7	4.3	4.1	0.9	0.8	0.3				
No. of samples	92	92	92	92	92	92	92	11	0	0		
RFTB Factor												
Score	0.0		0.0		0.0		5.0		6.0		94.0	

Source Number and Name: 101C		Hanson Aggregates, Demorest, GA							Number of Reports: 31			
Product:	0089	WU:	Washed			Sampled From: Stockpile			Used In: B - 400			
Screen Size	1/2"	3/8"	No. 4	No. 8	No. 16	No. 50	No. 200					
Lower Spec	100	90	20	0	0	0	0					
Upper Spec	100	100	55	15	10	5	100					
Lower Target												
Upper Target												
Mean	100.0	99.4	34.9	4.1	2.9	1.9	0.3					
StdDev	0.0	1.0	4.9	1.3	0.8	0.4	0.2					
No. of samples	31	31	31	31	31	31	2	0	0	0		
RFTB Factor												
Score	0.0	1.0	4.9	1.3	0.8	0.4	0.2	0.0	0.0	0.0	94.3	

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 102C		LaFarge Aggregates Inc., Buford, GA						Number of Reports: 10			
Product: 0007	WU: Unwashed	Sampled From: Stockpile			Used In: B - 400						
Screen Size	3/4" 1/2"	3/8"	No. 4	No. 8	No. 16	No. 200					
Lower Spec	100	90	40	0	0	0	0				
Upper Spec	100	100	70	15	5	100	100				
Lower Target		93	45	0	0						
Upper Target		100	60	9	1						
Mean	100.0	93.1	42.3	2.6	1.4						
StdDev	0.0	1.8	2.7	1.3	0.9						
No. of samples	4	10	10	10	10	0	0	0	0	0	
RFTB Factor											
Score	0.0	1.8	2.7	1.3	0.9	0.0	0.0	0.0	0.0	0.0	95.5

Source Number and Name: 102C		LaFarge Aggregates Inc., Buford, GA						Number of Reports: 79			
Product: 0057	WU: Washed	Sampled From: Belt			Used In: A - 500						
Screen Size	1 1/2" 1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	95	0	25	0	0	0				
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target		97		32		0	0				
Upper Target		100		48		5	1				
Mean	100.0	97.8	79.6	40.3	20.0	2.4	1.1				
StdDev	0.0	0.8	3.9	2.8	2.1	0.5	0.3				
No. of samples	55	79	79	79	79	79	79	0	0	0	
RFTB Factor		0.0		0.0		0.0	0.4				
Score		0.0		0.0		0.0	0.0				100.0

Source Number and Name: 102C		LaFarge Aggregates Inc., Buford, GA						Number of Reports: 16			
Product: 0089	WU: Unwashed	Sampled From: Stockpile			Used In: B - 400						
Screen Size	1/2" 3/8"	No. 4	No. 8	No. 16	No. 50	No. 200					
Lower Spec	100	90	20	0	0	0	0				
Upper Spec	100	100	55	15	10	5	100				
Lower Target		93	23	0	0	0					
Upper Target		100	43	7	5	1					
Mean	100.0	98.5	33.4	5.0	3.8	3.2	1.9				
StdDev	0.0	1.0	5.1	2.1	1.4	1.2	0.8				
No. of samples	7	16	16	16	16	16	16	0	0	0	
RFTB Factor											
Score	0.0	1.0	5.1	2.1	1.4	1.2	0.8	0.0	0.0	0.0	92.3

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 102C		LaFarge Aggregates Inc., Buford, GA								
Product: 15CR-2	WU: Unwashed	Sampled From: Stockpile					Used In: H - 310 Gab			Number of Reports: 97
Screen Size	2" 1 1/2"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 10	No. 60	No. 200	
Lower Spec	100	97	60	0	0	0	25	5	4	
Upper Spec	100	100	90	100	100	100	45	30	11	
Lower Target		98	70				32	8	6	
Upper Target		100	86				40	25	9	
Mean	100.0	98.4	77.1	64.4	58.4	45.5	34.9	20.1	9.3	
StdDev	0.0	1.1	3.4	3.9	3.9	3.4	2.8	1.6	0.6	
No. of samples	59	96	97	97	97	97	0	97	18	18
RFTB		0.7	0.0				0.0	0.0	0.9	
Factor		3.0	0.0				0.0	0.0	0.0	
Score		2.1	0.0				0.0	0.0	0.0	97.9

Source Number and Name: 104C		Aggregates USA, Appling, GA								
Product: 0006	WU: Unwashed	Sampled From: Stockpile					Used In: B - 400		Number of Reports: 50	
Screen Size	1" 3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	20	0	0	0	0			
Upper Spec	100	100	55	15	5	100	100			
Lower Target		93	23	0	0					
Upper Target		100	40	7	1					
Mean	100.0	86.0	19.8	6.8	2.8	2.2				
StdDev	0.0	3.9	4.3	2.8	1.3	1.1				
No. of samples	50	50	50	50	50	50	0	0	0	0
RFTB										
Factor										
Score	0.0	3.9	4.3	2.8	1.3	1.1	0.0	0.0	0.0	91.1

Source Number and Name: 104C		Aggregates USA, Appling, GA								
Product: 0007	WU: Unwashed	Sampled From: Stockpile					Used In: B - 400		Number of Reports: 50	
Screen Size	3/4" 1/2"	3/8"	No. 4	No. 8	No. 16	No. 200				
Lower Spec	100	90	40	0	0	0	0			
Upper Spec	100	100	70	15	5	100	100			
Lower Target		93	45	0	0					
Upper Target		100	60	9	1					
Mean	100.0	81.2	39.2	7.6	3.6	2.8				
StdDev	0.0	3.3	5.0	2.3	1.1	1.0				
No. of samples	50	50	50	50	50	50	0	0	0	0
RFTB										
Factor										
Score	0.0	3.3	5.0	2.3	1.1	1.0	0.0	0.0	0.0	91.5

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 104C		Aggregates USA, Appling, GA							Number of Reports: 25		
Product: 0M10	WU: Unwashed	Sampled From: Stockpile					Used In: B - 400				
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	97.2	77.5	58.4	42.5	27.3	17.0	9.7			
StdDev	0.0	0.8	2.8	2.7	2.1	1.9	1.6	1.0			
No. of samples	25	25	25	25	25	25	25	25	0	0	
RFTB Factor											
Score	0.0	0.8	2.8	3.5	2.7	2.5	2.1	1.3	0.0	0.0	89.6

Source Number and Name: 105C		LaFarge Aggregates Inc., Newton Co., GA							Number of Reports: 28		
Product: 0007	WU: Unwashed	Sampled From: Stockpile					Used In: B - 400				
Screen Size	3/4"	1/2"	3/8"	No. 4	No. 8	No. 16	No. 200				
Lower Spec	100	90	40	0	0	0	0				
Upper Spec	100	100	70	15	5	100	100				
Lower Target											
Upper Target											
Mean	100.0	89.9	41.7	5.1	2.6						
StdDev	0.0	1.5	3.3	2.2	1.0						
No. of samples	28	28	28	28	28	0	0	0	0	0	
RFTB Factor											
Score	0.0	1.5	3.3	2.2	1.0	0.0	0.0	0.0	0.0	0.0	94.7

Source Number and Name: 105C		LaFarge Aggregates Inc., Newton Co., GA							Number of Reports: 23	
Product: 0057	WU: Washed	Sampled From: Stockpile					Used In: A - 500			
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200		
Lower Spec	100	95	0	25	0	0	0	0		
Upper Spec	100	100	100	60	100	10	5	100		
Lower Target										
Upper Target										
Mean	100.0	98.1	79.7	41.1	19.5	2.6	0.7	0.0		
StdDev	0.0	0.6	5.1	2.3	4.7	1.1	0.1			
No. of samples	23	23	23	23	23	23	23	1	0	0
RFTB Factor										
Score	0.0		0.0		0.0		0.0		100.0	

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 105C		LaFarge Aggregates Inc., Newton Co., GA							Number of Reports: 11		
Product: 0089	WU: Unwashed	Sampled From: Stockpile					Used In: B - 400				
Screen Size	1/2"	3/8"	No. 4	No. 8	No. 16	No. 50	No. 200				
Lower Spec	100	90	20	0	0	0	0				
Upper Spec	100	100	55	15	10	5	100				
Lower Target		93	23	0	0	0					
Upper Target		100	43	7	5	1					
Mean	100.0	97.4	25.0	7.2	6.1	4.1	2.2				
StdDev	0.0	2.6	7.0	2.9	2.4	1.3	0.7				
No. of samples	11	11	11	11	11	11	11	0	0	0	
RFTB Factor Score	0.0	2.6	7.0	2.9	2.4	1.3	0.7	0.0	0.0	0.0	88.7

Source Number and Name: 105C		LaFarge Aggregates Inc., Newton Co., GA							Number of Reports: 22		
Product: 0M10	WU: Unwashed	Sampled From: Stockpile					Used In: B - 400				
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	99.0	80.0	64.0	48.5	33.6	20.6	10.7			
StdDev	0.0	0.7	2.9	3.6	4.3	2.9	4.3	1.4			
No. of samples	22	22	22	22	22	22	22	22	0	0	
RFTB Factor Score	0.0	0.7	2.9	4.5	5.4	3.6	5.4	1.8	0.0	0.0	83.8

Source Number and Name: 105C		LaFarge Aggregates Inc., Newton Co., GA							Number of Reports: 11		
Product: AW10	WU: Washed	Sampled From: Stockpile					Used In: B - 400				
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	98.5	77.6	57.3	37.9	19.2	6.1	2.0			
StdDev	0.0	0.8	5.8	5.1	1.7	2.0	1.6	0.6			
No. of samples	11	11	11	11	11	11	11	11	0	0	
RFTB Factor Score	0.0	0.8	5.8	6.6	2.2	2.6	2.1	0.8	0.0	0.0	86.1

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 107F		Vulcan Materials Co., Norcross, GA							Number of Reports: 103	
Product: 10SM	WU: Washed	Sampled From: Stockpile			Used In: A - 500					
Screen Size	3/8" No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	100 95	0	45	0	8	1	0			
Upper Spec	100 100	100	95	100	30	10	4			
Lower Target	97		51		12	2	0			
Upper Target	100		90		24	9	3			
Mean	100.0 98.8	77.9	58.5	41.3	22.1	7.9	2.8			
StdDev	0.0 0.4	2.3	2.7	2.7	2.1	1.0	0.4			
No. of samples	103 103	103	103	103	103	103	103	0	0	
RFTB	0.0		0.0		0.2	0.0	0.2			
Factor	0.0		0.0		5.0	0.0	0.0			
Score	0.0		0.0		1.0	0.0	0.0	99.0		

Source Number and Name: 107F		Vulcan Materials Co., Norcross, GA							Number of Reports: 103	
Product: 10SM	WU: Washed	Sampled From: Stockpile			Used In: B - 400					
Screen Size	3/8" No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	100 95	0	45	0	8	1	0			
Upper Spec	100 100	100	95	100	30	10	4			
Lower Target	97		51		12	2	0			
Upper Target	100		90		24	9	3			
Mean	100.0 98.8	77.9	58.5	41.3	22.1	7.9	2.8			
StdDev	0.0 0.4	2.3	2.7	2.7	2.1	1.0	0.4			
No. of samples	103 103	103	103	103	103	103	103	0	0	
RFTB	0.0		0.0		0.2	0.0	0.2			
Factor	0.0		0.0		5.0	0.0	0.0			
Score	0.0 0.4	2.3	3.5	3.5	2.7	1.3	0.5	0.0	0.0	90.6

Source Number and Name: 108F		Vulcan Materials Co., Stockbridge, GA							Number of Reports: 11	
Product: 10FM-2	WU: Washed	Sampled From: Stockpile			Used In: A - 500					
Screen Size	3/8" No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	100 95	0	45	0	15	6	0			
Upper Spec	100 100	100	95	100	42	22	9			
Lower Target	97		51		19	7	2			
Upper Target	100		90		36	18	7			
Mean	100.0 99.7	88.3	65.0	46.9	29.2	14.0	6.3			
StdDev	0.0 0.2	3.9	4.8	2.4	2.0	1.3	0.5			
No. of samples	11 11	11	11	11	11	11	11	0	0	
RFTB	0.0		0.0		0.0	0.0	0.0			
Factor	0.0		0.0		0.0	0.0	0.0			
Score	0.0		0.0		0.0	0.0	0.0	100.0		

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 108F			Vulcan Materials Co., Stockbridge, GA						Number of Reports: 66	
Product:	WU:		Sampled From: Stockpile			Used In: A - 500				
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200		
Lower Spec	100	95	0	45	0	8	1	0		
Upper Spec	100	100	100	95	100	30	10	4		
Lower Target		97		51		12	2	0		
Upper Target		100		90		24	9	3		
Mean	100.0	99.8	81.3	54.7	37.1	19.7	6.6	1.3		
StdDev	0.0	0.2	3.3	3.0	2.7	1.8	0.8	0.3		
No. of samples	66	66	66	66	66	66	66	66	0	0
RFTB		0.0		0.0		0.0	0.0	0.0		
Factor		0.0		0.0		0.0	0.0	0.0		
Score		0.0		0.0		0.0	0.0	0.0		100.0

Source Number and Name: 108F			Vulcan Materials Co., Stockbridge, GA						Number of Reports: 66	
Product:	WU:		Sampled From: Stockpile			Used In: B - 400				
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200		
Lower Spec	100	95	0	45	0	8	1	0		
Upper Spec	100	100	100	95	100	30	10	4		
Lower Target		97		51		12	2	0		
Upper Target		100		90		24	9	3		
Mean	100.0	99.8	81.3	54.7	37.1	19.7	6.6	1.3		
StdDev	0.0	0.2	3.3	3.0	2.7	1.8	0.8	0.3		
No. of samples	66	66	66	66	66	66	66	66	0	0
RFTB		0.0		0.0		0.0	0.0	0.0		
Factor		0.0		0.0		0.0	0.0	0.0		
Score	0.0	0.2	3.3	3.7	3.3	2.2	1.0	0.4	0.0	0.0

Source Number and Name: 112C			LaFarge Aggregates Inc., Ball Ground, GA						Number of Reports: 83	
Product:	WU:		Sampled From: Stockpile			Used In: A - 500				
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200		
Lower Spec	100	95	0	25	0	0	0	0		
Upper Spec	100	100	100	60	100	10	5	100		
Lower Target		97		32		0	0			
Upper Target		100		48		5	1			
Mean	100.0	98.5	85.4	37.6	16.6	1.8	1.0			
StdDev	0.0	0.9	3.3	3.5	2.7	0.8	0.5			
No. of samples	83	83	83	83	83	83	83	0	0	0
RFTB		0.0		0.0		0.0	0.5			
Factor		0.0		0.0		0.0	0.0			
Score		0.0		0.0		0.0	0.0			100.0

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 117C		Hanson Aggregates, Lithonia, GA							Number of Reports: 113	
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: A - 500					
Screen Size	1 1/2" 1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100 95	0	25	0	0	0	0			
Upper Spec	100 100	100	60	100	10	5	100			
Lower Target		97	32		0	0				
Upper Target		100	48		5	1				
Mean	100.0 98.0	79.2	36.6	16.8	3.1	1.3	0.4			
StdDev	0.0 0.5	4.4	3.4	2.6	1.0	0.6	0.2			
No. of samples	113 113	113	113	113	113	113	5	0	0	
RFTB		0.0	0.0		0.0	0.9				
Factor		0.0	0.0		0.0	0.0				
Score		0.0	0.0		0.0	0.0		100.0		

Source Number and Name: 117C		Hanson Aggregates, Lithonia, GA							Number of Reports: 19	
Product: 0089	WU: Unwashed	Sampled From: Stockpile			Used In: B - 400					
Screen Size	1/2" 3/8"	No. 4	No. 8	No. 16	No. 50	No. 200				
Lower Spec	100 90	20	0	0	0	0				
Upper Spec	100 100	55	15	10	5	100				
Lower Target		93	23	0	0	0				
Upper Target		100	43	7	5	1				
Mean	100.0 99.1	30.0	7.4	4.8	2.6					
StdDev	0.0 0.5	4.7	3.4	2.8	1.8					
No. of samples	19 19	19	19	19	19	0	0	0	0	
RFTB										
Factor										
Score	0.0 0.5	4.7	3.4	2.8	1.8	0.0	0.0	0.0	0.0	91.2

Source Number and Name: 117C		Hanson Aggregates, Lithonia, GA							Number of Reports: 39	
Product: AW10	WU: Washed	Sampled From: Stockpile			Used In: B - 400					
Screen Size	3/8" No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0 0	0	0	0	0	0	0			
Upper Spec	100 100	100	100	100	100	100	100			
Lower Target										
Upper Target										
Mean	100.0 98.2	76.5	56.0	37.5	18.3	5.5	1.7			
StdDev	0.0 0.6	2.2	2.6	2.7	1.8	1.0	0.5			
No. of samples	39 39	39	39	39	39	39	39	0	0	
RFTB										
Factor										
Score	0.0 0.6	2.2	3.4	3.5	2.4	1.3	0.7	0.0	0.0	90.6

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 117F			Hanson Aggregates, Fayette Co., GA						Number of Reports: 106	
Product:	WU:		Sampled From: Stockpile			Used In: A - 500				
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200		
Lower Spec	100	95	0	45	0	15	6	0		
Upper Spec	100	100	100	95	100	42	22	9		
Lower Target		97		51		19	7	2		
Upper Target		100		90		36	18	7		
Mean	100.0	99.8	86.9	66.9	47.2	24.3	8.0	2.6		
StdDev	0.0	0.1	2.1	3.2	4.1	2.9	1.3	0.5		
No. of samples	106	106	106	106	106	106	106	106	0	0
RFTB		0.0		0.0		0.0	0.3	0.0		
Factor		0.0		0.0		0.0	0.0	0.0		
Score		0.0		0.0		0.0	0.0	0.0		100.0

Source Number and Name: 118C			LaFarge Aggregates Inc., Columbus, GA						Number of Reports: 19	
Product:	WU:		Sampled From: Stockpile			Used In: A - 500				
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200		
Lower Spec	100	95	0	25	0	0	0	0		
Upper Spec	100	100	100	60	100	10	5	100		
Lower Target		97		32		0	0			
Upper Target		100		48		5	1			
Mean	100.0	98.2	79.1	39.6	17.9	3.8	0.8			
StdDev	0.0	0.5	3.2	2.9	3.1	0.8	0.1			
No. of samples	19	19	19	19	19	19	19	0	0	0
RFTB		0.0		0.0		0.0	0.0			
Factor		0.0		0.0		0.0	0.0			
Score		0.0		0.0		0.0	0.0			100.0

Source Number and Name: 118C			LaFarge Aggregates Inc., Columbus, GA						Number of Reports: 28	
Product:	WU:		Sampled From: Stockpile			Used In: A - 500				
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	90	0	20	0	0	0			
Upper Spec	100	100	100	55	10	5	100			
Lower Target		93		23		0	0			
Upper Target		100		45		5	1			
Mean	100.0	98.8	66.0	31.4	3.2	0.8	0.1			
StdDev	0.1	0.4	5.4	3.0	1.0	0.4				
No. of samples	28	28	28	28	28	28	1	0	0	0
RFTB		0.0		0.0	0.0	0.2				
Factor		0.0		0.0	0.0	0.0				
Score		0.0		0.0	0.0	0.0				100.0

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 120C		Vulcan Materials Co., Adairsville, GA							Number of Reports: 135	
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: A - 500					
Screen Size	1 1/2" 1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100 95	0	25	0	0	0	0			
Upper Spec	100 100	100	60	100	10	5	100			
Lower Target			97		0	0				
Upper Target			100		5	1				
Mean	100.0 99.6	86.3	43.5	17.4	0.7	0.3	0.2			
StdDev	0.0 0.1	1.2	2.5	2.0	0.2	0.1	0.1			
No. of samples	135 135	135	135	135	135	135	10	0	0	
RFTB			0.0		0.0	0.0				
Factor			0.0		0.0	0.0				
Score			0.0		0.0	0.0		100.0		

Source Number and Name: 120C		Vulcan Materials Co., Adairsville, GA							Number of Reports: 135	
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: B - 400					
Screen Size	1 1/2" 1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100 95	0	25	0	0	0	0			
Upper Spec	100 100	100	60	100	10	5	100			
Lower Target			97		0	0				
Upper Target			100		5	1				
Mean	100.0 99.6	86.3	43.5	17.4	0.7	0.3	0.2			
StdDev	0.0 0.1	1.2	2.5	2.0	0.2	0.1	0.1			
No. of samples	135 135	135	135	135	135	135	10	0	0	
RFTB										
Factor										
Score	0.0 0.1	1.2	2.5	2.0	0.2	0.1	0.1	0.0	0.0	95.9

Source Number and Name: 120C		Vulcan Materials Co., Adairsville, GA							Number of Reports: 29	
Product: 0067	WU: Washed	Sampled From: Stockpile			Used In: A - 500					
Screen Size	1" 3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100 90	0	20	0	0	0				
Upper Spec	100 100	100	55	10	5	100				
Lower Target			93		0	0				
Upper Target			100		5	1				
Mean	100.0 99.6	69.7	30.2	1.4	0.4	0.2				
StdDev	0.0 0.1	2.5	2.2	0.7	0.1	0.1				
No. of samples	29 29	29	29	29	29	6	0	0	0	
RFTB			0.0		0.0	0.0				
Factor			0.0		0.0	0.0				
Score			0.0		0.0	0.0	100.0			

Source Number and Name: 120C		Aggregate Rating for 1/1/2011 to 6/30/2011 Vulcan Materials Co., Adairsville, GA							Number of Reports: 29		
Product:0067	WU: Washed	Sampled From: Stockpile					Used In: B - 400				
Screen Size	1" 3/4"	1/2"	3/8"	No. 4	No. 8	No. 200					
Lower Spec	100	90	0	20	0	0	0				
Upper Spec	100	100	100	55	10	5	100				
Lower Target		93		23	0	0					
Upper Target		100		45	5	1					
Mean	100.0	99.6	69.7	30.2	1.4	0.4	0.2				
StdDev	0.0	0.1	2.5	2.2	0.7	0.1	0.1				
No. of samples	29	29	29	29	29	29	6	0	0	0	
RFTB Factor Score	0.0	0.1	2.5	2.2	0.7	0.1	0.1	0.0	0.0	0.0	96.2

Source Number and Name: 120C		Vulcan Materials Co., Adairsville, GA							Number of Reports: 51		
Product:0089	WU: Washed	Sampled From: Stockpile					Used In: B - 400				
Screen Size	1/2" 3/8"	No. 4	No. 8	No. 16	No. 50	No. 200					
Lower Spec	100	90	20	0	0	0	0				
Upper Spec	100	100	55	15	10	5	100				
Lower Target		93	23	0	0	0					
Upper Target		100	43	7	5	1					
Mean	100.0	99.4	28.9	2.7	0.6	0.0					
StdDev	0.0	0.0	2.5	0.5	0.0	0.0					
No. of samples	51	51	51	51	51	51	0	0	0	0	
RFTB Factor Score	0.0	0.0	2.5	0.5	0.0	0.0	0.0	0.0	0.0	0.0	98.0

Source Number and Name: 120C		Vulcan Materials Co., Adairsville, GA							Number of Reports: 25		
Product:M810	WU: Unwashed	Sampled From: Stockpile					Used In: B - 400				
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	86.0	54.5	38.8	28.3	20.9	16.6	13.1			
StdDev	0.0	1.5	2.6	2.1	2.5	2.3	1.8	1.6			
No. of samples	25	25	25	25	25	25	25	25	0	0	
RFTB Factor Score	0.0	1.5	2.6	3.9	4.6	4.2	3.3	2.9	0.0	0.0	84.7

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 121C		Martin Marietta Aggregates, Junction City, GA							Number of Reports: 131		
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: A - 500						
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target		97		32		0	0				
Upper Target		100		48		5	1				
Mean	100.0	97.9	89.5	42.4	13.8	0.7	0.3				
StdDev	0.0	0.9	3.0	4.4	3.1	0.5	0.2				
No. of samples	131	131	131	131	131	131	131	0	0	0	
RFTB		0.0		0.0		0.0	0.0				
Factor		0.0		0.0		0.0	0.0				
Score		0.0		0.0		0.0	0.0		100.0		

Source Number and Name: 121C		Martin Marietta Aggregates, Junction City, GA							Number of Reports: 143		
Product: 0067	WU: Washed	Sampled From: Belt			Used In: A - 500						
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	0	20	0	0	0				
Upper Spec	100	100	100	55	10	5	100				
Lower Target		93		23	0	0					
Upper Target		100		45	5	1					
Mean	100.0	99.8	69.1	30.0	1.3	0.4					
StdDev	0.0	0.3	5.5	4.8	0.7	0.2					
No. of samples	143	143	143	143	143	143	0	0	0	0	
RFTB		0.0		0.0		0.0	0.0				
Factor		0.0		0.0		0.0	0.0				
Score		0.0		0.0		0.0	0.0		100.0		

Source Number and Name: 121C		Martin Marietta Aggregates, Junction City, GA							Number of Reports: 143		
Product: 0067	WU: Washed	Sampled From: Belt			Used In: B - 400						
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	0	20	0	0	0				
Upper Spec	100	100	100	55	10	5	100				
Lower Target		93		23	0	0					
Upper Target		100		45	5	1					
Mean	100.0	99.8	69.1	30.0	1.3	0.4					
StdDev	0.0	0.3	5.5	4.8	0.7	0.2					
No. of samples	143	143	143	143	143	143	0	0	0	0	
RFTB		0.0		0.0		0.0	0.0				
Factor		0.0		0.0		0.0	0.0				
Score	0.0	0.3	5.5	4.8	0.7	0.2	0.0	0.0	0.0	0.0	92.3

Source Number and Name: 121C		Aggregate Rating for 1/1/2011 to 6/30/2011										
Product: 0089		WU: Washed		Sampled From: Belt			Used In: B - 400		Number of Reports: 64			
Screen Size	1/2"	3/8"	No. 4	No. 8	No. 16	No. 50	No. 200					
Lower Spec	100	90	20	0	0	0	0					
Upper Spec	100	100	55	15	10	5	100					
Lower Target		93	23	0	0	0						
Upper Target		100	43	7	5	1						
Mean	100.0	98.9	25.0	3.1	1.7	0.7						
StdDev	0.0	0.9	4.3	1.5	0.6	0.2						
No. of samples	64	64	64	64	64	64	0	0	0	0		
RFTB Factor Score	0.0	0.9	4.3	1.5	0.6	0.2	0.0	0.0	0.0	0.0	95.0	

Source Number and Name: 121C		Aggregate Rating for 1/1/2011 to 6/30/2011										
Product: 0M10		WU: Unwashed		Sampled From: Stockpile			Used In: B - 400		Number of Reports: 25			
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200				
Lower Spec	0	0	0	0	0	0	0	0				
Upper Spec	100	100	100	100	100	100	100	100				
Lower Target												
Upper Target												
Mean	100.0	91.2	61.8	41.5		22.7	16.6					
StdDev	0.0	2.5	4.2	3.3		2.6	1.4					
No. of samples	25	25	25	25	0	25	25	0	0	0		
RFTB Factor Score	0.0	2.5	4.2	5.3	0.0	4.2	2.3	0.0	0.0	0.0	87.7	

Source Number and Name: 121C		Aggregate Rating for 1/1/2011 to 6/30/2011										
Product: AW10		WU: Washed		Sampled From: Stockpile			Used In: B - 400		Number of Reports: 26			
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200				
Lower Spec	0	0	0	0	0	0	0	0				
Upper Spec	100	100	100	100	100	100	100	100				
Lower Target												
Upper Target												
Mean	100.0	91.7	59.4	35.8		13.4	6.5					
StdDev	0.0	1.1	2.0	1.5		1.6	0.9					
No. of samples	26	26	26	26	0	26	26	0	0	0		
RFTB Factor Score	0.0	1.1	2.0	2.5	0.0	2.7	1.5	0.0	0.0	0.0	93.4	

Source Number and Name: 122C		Aggregate Rating for 1/1/2011 to 6/30/2011									
Product:0067		WU: Washed		Sampled From: Stockpile			Used In: A - 500		Number of Reports: 46		
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	0	20	0	0	0				
Upper Spec	100	100	100	55	10	5	100				
Lower Target		93		23	0	0					
Upper Target		100		45	5	1					
Mean	100.0	95.1	58.8	34.9	3.6	1.0					
StdDev	0.0	1.9	6.7	5.9	1.1	0.2					
No. of samples	46	46	46	46	46	46	0	0	0	0	
RFTB		0.0		0.0	0.0	0.2					
Factor		0.0		0.0	0.0	0.0					
Score		0.0		0.0	0.0	0.0		100.0			

Source Number and Name: 125C		Hanson Aggregates, Sparta, GA									
Product:0057		WU: Washed		Sampled From: Stockpile			Used In: A - 500		Number of Reports: 124		
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target		97		32		0	0				
Upper Target		100		48		5	1				
Mean	100.0	98.9	80.9	38.0	20.2	2.4	1.3	0.4			
StdDev	0.0	0.5	3.1	3.2	3.4	0.6	0.3	0.2			
No. of samples	124	124	124	124	124	124	124	5	0	0	
RFTB		0.0		0.0		0.0	0.6				
Factor		0.0		0.0		0.0	0.0				
Score		0.0		0.0		0.0	0.0		100.0		

Source Number and Name: 125C		Hanson Aggregates, Sparta, GA									
Product:0067		WU: Washed		Sampled From: Stockpile			Used In: A - 500		Number of Reports: 106		
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	0	20	0	0	0				
Upper Spec	100	100	100	55	10	5	100				
Lower Target		93		23	0	0					
Upper Target		100		45	5	1					
Mean	100.0	98.5	55.9	30.6	2.9	1.3	0.3				
StdDev	0.0	0.7	5.3	5.4	1.0	0.3	0.2				
No. of samples	106	106	106	106	106	106	5	0	0	0	
RFTB		0.0		0.0	0.0	0.6					
Factor		0.0		0.0	0.0	0.0					
Score		0.0		0.0	0.0	0.0		100.0			

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 128C		Vulcan Materials Co., Rockmart, GA							Number of Reports: 91	
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: A - 500					
Screen Size	1 1/2" 1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100 95	0	25	0	0	0	0			
Upper Spec	100 100	100	60	100	10	5	100			
Lower Target			97		0	0				
Upper Target			100		5	1				
Mean	100.0 100.0	93.9	43.0	15.8	1.9	0.9	0.4			
StdDev	0.0 0.1	1.6	2.3	2.0	0.7	0.4	0.1			
No. of samples	91 91	91	91	91	91	91	15	0	0	
RFTB			0.0		0.0	0.3				
Factor			0.0		0.0	0.0				
Score			0.0		0.0	0.0		100.0		

Source Number and Name: 128C		Vulcan Materials Co., Rockmart, GA							Number of Reports: 91	
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: B - 400					
Screen Size	1 1/2" 1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100 95	0	25	0	0	0	0			
Upper Spec	100 100	100	60	100	10	5	100			
Lower Target			97		0	0				
Upper Target			100		5	1				
Mean	100.0 100.0	93.9	43.0	15.8	1.9	0.9	0.4			
StdDev	0.0 0.1	1.6	2.3	2.0	0.7	0.4	0.1			
No. of samples	91 91	91	91	91	91	91	15	0	0	
RFTB										
Factor										
Score	0.0 0.1	1.6	2.3	2.0	0.7	0.4	0.1	0.0	0.0	95.2

Source Number and Name: 128C		Vulcan Materials Co., Rockmart, GA							Number of Reports: 98	
Product: 0067	WU: Washed	Sampled From: Stockpile			Used In: A - 500					
Screen Size	1" 3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100 90	0	20	0	0	0				
Upper Spec	100 100	100	55	10	5	100				
Lower Target			93		0	0				
Upper Target			100		5	1				
Mean	100.0 96.3	56.9	28.5	3.5	1.2	0.4				
StdDev	0.0 1.0	3.4	2.7	0.9	0.5	0.2				
No. of samples	98 98	98	98	98	98	12	0	0	0	
RFTB			0.0	0.0	0.7					
Factor			0.0	0.0	0.0					
Score			0.0	0.0	0.0		100.0			

Source Number and Name: 128C		Aggregate Rating for 1/1/2011 to 6/30/2011 Vulcan Materials Co., Rockmart, GA							Number of Reports: 98		
Product:0067	WU: Washed	Sampled From: Stockpile					Used In: B - 400				
Screen Size	1" 3/4"	1/2"	3/8"	No. 4	No. 8	No. 200					
Lower Spec	100	90	0	20	0	0	0				
Upper Spec	100	100	100	55	10	5	100				
Lower Target		93		23	0	0					
Upper Target		100		45	5	1					
Mean	100.0	96.3	56.9	28.5	3.5	1.2	0.4				
StdDev	0.0	1.0	3.4	2.7	0.9	0.5	0.2				
No. of samples	98	98	98	98	98	98	12	0	0	0	
RFTB Factor Score	0.0	1.0	3.4	2.7	0.9	0.5	0.2	0.0	0.0	0.0	94.2

Source Number and Name: 128C		Vulcan Materials Co., Rockmart, GA							Number of Reports: 32		
Product:0089	WU: Washed	Sampled From: Stockpile					Used In: B - 400				
Screen Size	1/2" 3/8"	No. 4	No. 8	No. 16	No. 50	No. 200					
Lower Spec	100	90	20	0	0	0	0				
Upper Spec	100	100	55	15	10	5	100				
Lower Target		93	23	0	0	0					
Upper Target		100	43	7	5	1					
Mean	100.0	96.6	32.5	4.7	1.7	0.0					
StdDev	0.0	1.4	3.8	1.3	0.6	0.1					
No. of samples	32	32	32	32	32	32	0	0	0	0	
RFTB Factor Score	0.0	1.4	3.8	1.3	0.6	0.1	0.0	0.0	0.0	0.0	95.2

Source Number and Name: 128C		Vulcan Materials Co., Rockmart, GA							Number of Reports: 21		
Product:M810	WU: Unwashed	Sampled From: Stockpile					Used In: B - 400				
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	88.1	59.6	38.2	25.5	18.5	14.2	11.7			
StdDev	0.0	1.7	3.0	2.4	1.8	1.7	1.3	1.1			
No. of samples	21	21	21	21	21	21	21	21	0	0	
RFTB Factor Score	0.0	1.7	3.0	4.0	3.0	2.9	2.2	1.8	0.0	0.0	87.6

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 128F		LaFarge Aggregates Inc., Newton Co., GA							Number of Reports: 21	
Product: 10SM	WU: Washed	Sampled From: Stockpile			Used In: A - 500					
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200		
Lower Spec	100	95	0	45	0	8	1	0		
Upper Spec	100	100	100	95	100	30	10	4		
Lower Target		97		51		12	2	0		
Upper Target		100		90		24	9	3		
Mean	100.0	98.6	76.8	57.2	38.9	20.0	6.6	1.6		
StdDev	0.0	0.7	4.9	4.6	3.9	2.5	1.5	0.5		
No. of samples	21	21	21	21	21	21	21	21	0	0
RFTB		0.0		0.0		0.0	0.0	0.0		
Factor		0.0		0.0		0.0	0.0	0.0		
Score		0.0		0.0		0.0	0.0	0.0	100.0	

Source Number and Name: 129C		Martin Marietta Aggregates, Forsyth Co., GA							Number of Reports: 13		
Product: 0005	WU: Washed	Sampled From: Stockpile			Used In: B - 400						
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 200				
Lower Spec	100	90	20	0	0	0	0				
Upper Spec	100	100	55	10	5	100	100				
Lower Target	100	93	23	0	0						
Upper Target		100	45	5	1						
Mean	100.0	96.5	39.2	4.3	2.3						
StdDev	0.0	1.4	5.9	1.8	0.9						
No. of samples	13	13	13	13	13	0	0	0	0	0	
RFTB											
Factor											
Score	0.0	1.4	5.9	1.8	0.9	0.0	0.0	0.0	0.0	0.0	93.3

Source Number and Name: 129C		Martin Marietta Aggregates, Forsyth Co., GA							Number of Reports: 28		
Product: 0006	WU: Washed	Sampled From: Stockpile			Used In: B - 400						
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	20	0	0	0	0				
Upper Spec	100	100	55	15	5	100	100				
Lower Target		93	23	0	0						
Upper Target		100	40	7	1						
Mean	100.0	95.1	29.4	9.6	2.3						
StdDev	0.0	1.1	5.4	3.5	1.2						
No. of samples	28	28	28	28	28	0	0	0	0	0	
RFTB											
Factor											
Score	0.0	1.1	5.4	3.5	1.2	0.0	0.0	0.0	0.0	0.0	92.5

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 129C		Martin Marietta Aggregates, Forsyth Co., GA									
Product: 15CR-2	WU: Unwashed	Sampled From: Stockpile					Used In: H - 310 Gab			Number of Reports: 78	
Screen Size	2" 1 1/2"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 10	No. 60	No. 200		
Lower Spec	100	97	60	0	0	0	0	25	5	4	
Upper Spec	100	100	90	100	100	100	100	45	30	11	
Lower Target		98	70					32	8	6	
Upper Target		100	86					40	25	9	
Mean		100.0	82.6	67.4	60.5	47.5		35.9	18.8	8.1	
StdDev		0.0	3.3	4.3	4.2	3.7		2.8	1.6	0.8	
No. of samples	0	78	78	78	78	78	0	78	71	71	
RFTB		0.0	0.0					0.0	0.0	0.0	
Factor		0.0	0.0					0.0	0.0	0.0	
Score		0.0	0.0					0.0	0.0	0.0	100.0

Source Number and Name: 129C		Martin Marietta Aggregates, Forsyth Co., GA									
Product: AW10	WU: Washed	Sampled From: Stockpile					Used In: B - 400			Number of Reports: 40	
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0	0		
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	98.8	75.8	55.7	42.0	27.5	12.1	3.4			
StdDev	0.0	0.4	3.7	4.6	4.6	4.8	3.4	1.0			
No. of samples	40	40	40	40	40	40	40	40	0	0	
RFTB											
Factor											
Score	0.0	0.4	3.7	6.1	6.1	6.3	4.5	1.3	0.0	0.0	81.1

Source Number and Name: 129C		Martin Marietta Aggregates, Forsyth Co., GA									
Product: M810	WU: Unwashed	Sampled From: Stockpile					Used In: B - 400			Number of Reports: 18	
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	87.6	68.2	54.4	44.6	34.0	22.8	12.6			
StdDev	0.0	2.0	3.5	3.8	3.5	3.0	2.2	1.3			
No. of samples	18	18	18	18	18	18	18	18	0	0	
RFTB											
Factor											
Score	0.0	2.0	3.5	5.6	5.1	4.4	3.2	1.9	0.0	0.0	82.8

Source Number and Name: 131C		Aggregate Rating for 1/1/2011 to 6/30/2011										
Product:0067		WU: Washed		Sampled From: Belt			Used In: B - 400		Number of Reports: 14			
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200					
Lower Spec	100	90	0	20	0	0	0					
Upper Spec	100	100	100	55	10	5	100					
Lower Target		93		23	0	0						
Upper Target		100		45	5	1						
Mean	100.0	96.0	53.3	33.3	4.5	1.5						
StdDev	0.0	1.2	3.3	3.4	1.3	0.7						
No. of samples	14	14	14	14	14	14	0	0	0	0		
RFTB												
Factor												
Score	0.0	1.2	3.3	3.4	1.3	0.7	0.0	0.0	0.0	0.0	0.0	93.4

Source Number and Name: 133C		Martin Marietta Aggregates, Appling, GA										
Product:0057		WU: Washed		Sampled From: Stockpile			Used In: A - 500		Number of Reports: 118			
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	95	0	25	0	0	0	0				
Upper Spec	100	100	100	60	100	10	5	100				
Lower Target		97		32		0	0					
Upper Target		100		48		5	1					
Mean	100.0	99.2	86.9	41.6	12.7	1.7	0.7					
StdDev	0.0	0.6	4.6	4.7	4.0	0.8	0.3					
No. of samples	118	118	118	118	118	118	118	0	0	0		
RFTB		0.0		0.0		0.0	0.0					
Factor		0.0		0.0		0.0	0.0					
Score		0.0		0.0		0.0	0.0					100.0

Source Number and Name: 133C		Martin Marietta Aggregates, Appling, GA										
Product:0067		WU: Washed		Sampled From: Stockpile			Used In: A - 500		Number of Reports: 92			
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200					
Lower Spec	100	90	0	20	0	0	0					
Upper Spec	100	100	100	55	10	5	100					
Lower Target		93		23	0	0						
Upper Target		100		45	5	1						
Mean	100.0	95.9	64.4	34.1	3.1	0.9						
StdDev	0.0	1.6	6.7	5.9	1.2	0.3						
No. of samples	92	92	92	92	92	92	0	0	0	0		
RFTB		0.0		0.0	0.0	0.2						
Factor		0.0		0.0	0.0	0.0						
Score		0.0		0.0	0.0	0.0						100.0

Source Number and Name: 133C		Aggregate Rating for 1/1/2011 to 6/30/2011										
Product:0067		WU: Washed		Sampled From: Stockpile			Used In: B - 400		Number of Reports: 47			
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200					
Lower Spec	100	90	0	20	0	0	0					
Upper Spec	100	100	100	55	10	5	100					
Lower Target		93		23	0	0						
Upper Target		100		45	5	1						
Mean	100.0	95.9	65.0	34.9	3.9	1.4						
StdDev	0.0	2.1	8.8	7.6	2.0	0.7						
No. of samples	47	47	47	47	47	47	0	0	0	0		
RFTB Factor Score	0.0	2.1	8.8	7.6	2.0	0.7	0.0	0.0	0.0	0.0	85.9	

Source Number and Name: 133C		Aggregate Rating for 1/1/2011 to 6/30/2011										
Product:0078		WU: Washed		Sampled From: Stockpile			Used In: B - 400		Number of Reports: 46			
Screen Size	3/4"	1/2"	3/8"	No. 4	No. 8	No. 16	No. 200					
Lower Spec	100	90	40	5	0	0	0					
Upper Spec	100	100	75	25	10	5	100					
Lower Target												
Upper Target												
Mean	100.0	92.0	66.5	10.0	3.3	1.4						
StdDev	0.0	1.3	5.6	3.0	1.3	1.2						
No. of samples	46	46	46	46	46	46	0	0	0	0		
RFTB Factor Score	0.0	1.3	5.6	3.0	1.3	1.2	0.0	0.0	0.0	0.0	91.7	

Source Number and Name: 133C		Aggregate Rating for 1/1/2011 to 6/30/2011										
Product:0089		WU: Washed		Sampled From: Stockpile			Used In: B - 400		Number of Reports: 44			
Screen Size	1/2"	3/8"	No. 4	No. 8	No. 16	No. 50	No. 200					
Lower Spec	100	90	20	0	0	0	0					
Upper Spec	100	100	55	15	10	5	100					
Lower Target		93	23	0	0	0						
Upper Target		100	43	7	5	1						
Mean	100.0	93.0	30.3	6.4	3.6	1.8						
StdDev	0.0	2.5	5.8	2.7	1.5	1.2						
No. of samples	44	44	44	44	44	44	0	0	0	0		
RFTB Factor Score	0.0	2.5	5.8	2.7	1.5	1.2	0.0	0.0	0.0	0.0	90.9	

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 133C		Martin Marietta Aggregates, Appling, GA								Number of Reports: 43	
Product: 0M10	WU: Unwashed	Sampled From: Stockpile				Used In: B - 400					
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	91.8	70.7	53.6	38.6	25.9	15.5	9.1			
StdDev	0.0	2.0	3.3	3.0	2.7	2.0	1.3	0.8			
No. of samples	43	43	43	43	43	43	43	43	0	0	
RFTB Factor Score	0.0	2.0	3.3	4.2	3.8	2.8	1.8	1.1	0.0	0.0	87.2

Source Number and Name: 133C		Martin Marietta Aggregates, Appling, GA								Number of Reports: 43	
Product: AW10	WU: Washed	Sampled From: Stockpile				Used In: B - 400					
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	89.0	64.0	45.4	30.1	18.1	7.9	2.7			
StdDev	0.0	2.3	3.7	3.8	3.5	2.8	1.6	0.6			
No. of samples	43	43	43	43	43	43	43	43	0	0	
RFTB Factor Score	0.0	2.3	3.7	5.9	5.5	4.4	2.5	0.9	0.0	0.0	83.2

Source Number and Name: 134C		Vulcan Materials Co., Bartow Co., GA								Number of Reports: 13	
Product: 0007	WU: Unwashed	Sampled From: Stockpile				Used In: B - 400					
Screen Size	3/4"	1/2"	3/8"	No. 4	No. 8	No. 16	No. 200				
Lower Spec	100	90	40	0	0	0	0				
Upper Spec	100	100	70	15	5	100	100				
Lower Target											
Upper Target											
Mean	100.0	87.9	45.9	3.5	2.0	0.9					
StdDev	0.0	2.1	1.7	1.0	0.6	0.5					
No. of samples	13	13	13	13	13	13	0	0	0	0	
RFTB Factor Score	0.0	2.1	1.7	1.0	0.6	0.5	0.0	0.0	0.0	0.0	96.1

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 134C		Vulcan Materials Co., Bartow Co., GA					Number of Reports: 11				
Product:0056	WU: Unwashed	Sampled From: Stockpile					Used In: B - 400				
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 200				
Lower Spec	100	90	40	15	0	0	0				
Upper Spec	100	100	75	35	15	5	100				
Lower Target											
Upper Target											
Mean	100.0	98.1	75.4	16.9	5.0	2.1					
StdDev	0.0	0.3	1.4	0.8	0.8	0.3					
No. of samples	11	11	11	11	11	11	0	0	0	0	
RFTB Factor											
Score	0.0	0.3	1.4	0.8	0.8	0.3	0.0	0.0	0.0	0.0	97.6

Source Number and Name: 134C		Vulcan Materials Co., Bartow Co., GA					Number of Reports: 44				
Product:0057	WU: Washed	Sampled From: Stockpile					Used In: A - 500				
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target							0	0			
Upper Target							5	1			
Mean	100.0	98.8	86.1	44.1	18.9	1.3	0.8				
StdDev	0.0	0.6	2.6	1.9	1.1	0.2	0.2				
No. of samples	44	44	44	44	44	44	44	0	0	0	
RFTB Factor							0.0	0.0			
Score							0.0	0.0			
											100.0

Source Number and Name: 134C		Vulcan Materials Co., Bartow Co., GA					Number of Reports: 13				
Product:0089	WU: Washed	Sampled From: Stockpile					Used In: B - 400				
Screen Size	1/2"	3/8"	No. 4	No. 8	No. 16	No. 50	No. 200				
Lower Spec	100	90	20	0	0	0	0				
Upper Spec	100	100	55	15	10	5	100				
Lower Target							0				
Upper Target							1				
Mean	100.0	99.0	27.0	4.1	1.7	0.0					
StdDev	0.0	0.4	1.8	0.7	0.4	0.0					
No. of samples	13	13	13	13	13	13	0	0	0	0	
RFTB Factor											
Score	0.0	0.4	1.8	0.7	0.4	0.0	0.0	0.0	0.0	0.0	97.8

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 134C		Vulcan Materials Co., Bartow Co., GA							Number of Reports: 17		
Product:	M810	WU:	Unwashed	Sampled From: Stockpile			Used In: B - 400				
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	87.7	65.1	44.5	30.9	20.9	13.2	8.6			
StdDev	0.0	1.7	6.6	3.5	2.0	1.5	0.8	0.9			
No. of samples	17	17	17	17	17	17	17	17	0	0	
RFTB Factor											
Score	0.0	1.7	6.6	5.4	3.1	2.3	1.2	1.4	0.0	0.0	85.6

Source Number and Name: 134T		Vulcan Materials Co., Helena, AL							Number of Reports: 22		
Product:	0067	WU:	Washed	Sampled From: Stockpile			Used In: A - 500				
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	0	20	0	0	0				
Upper Spec	100	100	100	55	10	5	100				
Lower Target			93	23	0	0					
Upper Target			100	45	5	1					
Mean	100.0	97.2	55.1	31.8	3.7	1.0	0.4				
StdDev	0.0	0.9	5.5	3.6	1.1	0.2	0.1				
No. of samples	22	22	22	22	22	22	5	0	0	0	
RFTB Factor			0.0	0.0	0.0	0.2					
Score			0.0	0.0	0.0	0.0					
											100.0

Source Number and Name: 135F		Vulcan Materials Co., Lithonia, GA							Number of Reports: 29		
Product:	10FM-2	WU:	Washed	Sampled From: Stockpile			Used In: A - 500				
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	100	95	0	45	0	15	6	0			
Upper Spec	100	100	100	95	100	42	22	9			
Lower Target			97	51		19	7	2			
Upper Target			100	90		36	18	7			
Mean	100.0	99.4	82.2	61.0	43.7	25.5	12.2	5.5			
StdDev	0.0	0.4	2.5	2.5	2.3	2.3	2.2	1.3			
No. of samples	29	29	29	29	29	29	29	29	0	0	
RFTB Factor			0.0	0.0		0.0	0.0	0.0			
Score			0.0	0.0		0.0	0.0	0.0			
											100.0

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 135F		Vulcan Materials Co., Lithonia, GA							Number of Reports: 67	
Product: 10SM	WU: Washed	Sampled From: Stockpile			Used In: A - 500					
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200		
Lower Spec	100	95	0	45	0	8	1	0		
Upper Spec	100	100	100	95	100	30	10	4		
Lower Target		97		51		12	2	0		
Upper Target		100		90		24	9	3		
Mean	100.0	99.3	79.6	57.2	38.7	19.3	6.0	1.5		
StdDev	0.0	0.4	2.1	2.2	2.2	1.9	1.0	0.4		
No. of samples	67	67	67	67	67	67	67	67	0	0
RFTB		0.0		0.0		0.0	0.0	0.0		
Factor		0.0		0.0		0.0	0.0	0.0		
Score		0.0		0.0		0.0	0.0	0.0	100.0	

Source Number and Name: 138C		LaFarge Aggregates Inc., Clayton Co., GA							Number of Reports: 11		
Product: 0005	WU: Unwashed	Sampled From: Stockpile			Used In: B - 400						
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 200				
Lower Spec	100	90	20	0	0	0	0				
Upper Spec	100	100	55	10	5	100	100				
Lower Target	100	93	23	0	0						
Upper Target		100	45	5	1						
Mean	100.0	92.6	29.1	4.6	3.5	2.8					
StdDev	0.0	1.4	5.0	1.0	0.8	0.8					
No. of samples	11	11	11	11	11	11	0	0	0	0	
RFTB											
Factor											
Score	0.0	1.4	5.0	1.0	0.8	0.8	0.0	0.0	0.0	0.0	94.0

Source Number and Name: 138C		LaFarge Aggregates Inc., Clayton Co., GA							Number of Reports: 26		
Product: 0006	WU: Unwashed	Sampled From: Stockpile			Used In: B - 400						
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	20	0	0	0	0				
Upper Spec	100	100	55	15	5	100	100				
Lower Target		93	23	0	0						
Upper Target		100	40	7	1						
Mean	100.0	93.5	30.1	7.5	3.3	2.4					
StdDev	0.0	1.5	3.4	1.8	0.9	0.7					
No. of samples	26	26	26	26	26	26	0	0	0	0	
RFTB											
Factor											
Score	0.0	1.5	3.4	1.8	0.9	0.7	0.0	0.0	0.0	0.0	94.5

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 138C		LaFarge Aggregates Inc., Clayton Co., GA						Number of Reports: 27			
Product: 0007	WU: Unwashed	Sampled From: Stockpile			Used In: B - 400						
Screen Size	3/4" 1/2"	3/8"	No. 4	No. 8	No. 16	No. 200					
Lower Spec	100 90	40	0	0	0	0					
Upper Spec	100 100	70	15	5	100	100					
Lower Target		93	45	0	0						
Upper Target		100	60	9	1						
Mean	100.0 96.8	52.8	3.8	2.6							
StdDev	0.0 1.3	5.5	1.3	1.0							
No. of samples	27 27	27	27	27	0	0	0	0	0		
RFTB Factor											
Score	0.0 1.3	5.5	1.3	1.0	0.0	0.0	0.0	0.0	0.0	93.9	

Source Number and Name: 138C		LaFarge Aggregates Inc., Clayton Co., GA						Number of Reports: 22			
Product: 0057	WU: Washed	Sampled From: Belt			Used In: A - 500						
Screen Size	1 1/2" 1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100 95	0	25	0	0	0	0				
Upper Spec	100 100	100	60	100	10	5	100				
Lower Target			97	32	0	0					
Upper Target			100	48	5	1					
Mean	100.0 97.8	70.0	36.8	20.4	1.9	0.9					
StdDev	0.0 0.6	4.2	2.8	2.8	0.3	0.1					
No. of samples	22 22	22	22	22	22	22	0	0	0		
RFTB Factor			0.0	0.0	0.0	0.0					
Score			0.0	0.0	0.0	0.0				100.0	

Source Number and Name: 138C		LaFarge Aggregates Inc., Clayton Co., GA						Number of Reports: 65			
Product: 0067	WU: Washed	Sampled From: Belt			Used In: A - 500						
Screen Size	1" 3/4"	1/2"	3/8"	No. 4	No. 8	No. 200					
Lower Spec	100 90	0	20	0	0	0					
Upper Spec	100 100	100	55	10	5	100					
Lower Target			93	23	0	0					
Upper Target			100	45	5	1					
Mean	100.0 95.6	56.1	30.0	1.9	0.9						
StdDev	0.0 0.9	2.7	2.9	0.3	0.1						
No. of samples	65 65	65	65	65	65	0	0	0	0		
RFTB Factor			0.0	0.0	0.0	0.0					
Score			0.0	0.0	0.0	0.0				100.0	

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 138C		LaFarge Aggregates Inc., Clayton Co., GA							Number of Reports: 55		
Product: 0089	WU: Unwashed	Sampled From: Stockpile					Used In: B - 400				
Screen Size	1/2"	3/8"	No. 4	No. 8	No. 16	No. 50	No. 200				
Lower Spec	100	90	20	0	0	0	0				
Upper Spec	100	100	55	15	10	5	100				
Lower Target		93	23	0	0	0					
Upper Target		100	43	7	5	1					
Mean	100.0	100.0	35.3	7.0	5.3	3.3	1.8				
StdDev	0.0	0.0	4.2	1.7	1.4	0.9	0.8				
No. of samples	55	55	55	55	55	55	55	0	0	0	
RFTB Factor											
Score	0.0	0.0	4.2	1.7	1.4	0.9	0.8	0.0	0.0	0.0	94.0

Source Number and Name: 138C		LaFarge Aggregates Inc., Clayton Co., GA							Number of Reports: 51		
Product: 0M10	WU: Unwashed	Sampled From: Stockpile					Used In: B - 400				
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	97.9	79.7	64.0	52.0	37.8	21.5	10.8			
StdDev	0.0	0.6	2.1	2.2	2.4	2.2	1.5	1.2			
No. of samples	51	51	51	51	51	51	51	51	0	0	
RFTB Factor											
Score	0.0	0.6	2.1	2.8	3.0	2.8	1.9	1.5	0.0	0.0	90.3

Source Number and Name: 138C		LaFarge Aggregates Inc., Clayton Co., GA							Number of Reports: 53		
Product: AW10	WU: Washed	Sampled From: Stockpile					Used In: B - 400				
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	97.0	77.7	58.9	45.8	30.0	12.3	3.7			
StdDev	0.0	0.9	2.4	2.6	2.5	2.2	1.4	0.7			
No. of samples	53	53	53	53	53	53	53	53	0	0	
RFTB Factor											
Score	0.0	0.9	2.4	3.3	3.2	2.8	1.8	0.9	0.0	0.0	89.7

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 139C		Martin Marietta Aggregates, Jefferson, GA							Number of Reports: 102		
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: A - 500						
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target		97		32		0	0				
Upper Target		100		48		5	1				
Mean	100.0	99.7	89.0	39.8		2.5	1.7				
StdDev	0.0	0.3	5.4	7.5		1.1	0.7				
No. of samples	102	102	102	102	0	102	102	0	0	0	
RFTB		0.0		0.0		0.0	1.4				
Factor		0.0		0.0		0.0	5.0				
Score		0.0		0.0		0.0	7.0		93.0		

Source Number and Name: 139C		Martin Marietta Aggregates, Jefferson, GA							Number of Reports: 12		
Product: 0067	WU: Washed	Sampled From: Stockpile			Used In: A - 500						
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	0	20	0	0	0				
Upper Spec	100	100	100	55	10	5	100				
Lower Target		93		23	0	0					
Upper Target		100		45	5	1					
Mean	100.0	96.9	53.6	25.4	3.3	2.1					
StdDev	0.0	1.9	12.4	4.1	1.1	0.9					
No. of samples	12	12	12	12	12	12	0	0	0	0	
RFTB		0.0		1.7	0.0	2.0					
Factor		0.0		5.0	0.0	15.0					
Score		0.0		8.5	0.0	30.0		61.5			

Source Number and Name: 139C		Martin Marietta Aggregates, Jefferson, GA							Number of Reports: 34		
Product: 0089	WU: Washed	Sampled From: Stockpile			Used In: B - 400						
Screen Size	1/2"	3/8"	No. 4	No. 8	No. 16	No. 50	No. 200				
Lower Spec	100	90	20	0	0	0	0				
Upper Spec	100	100	55	15	10	5	100				
Lower Target		93	23	0	0	0					
Upper Target		100	43	7	5	1					
Mean	100.0	98.7	30.5	3.4	2.1	1.3					
StdDev	0.0	1.0	6.6	1.7	1.1	0.6					
No. of samples	34	34	34	34	34	34	0	0	0	0	
RFTB											
Factor											
Score	0.0	1.0	6.6	1.7	1.1	0.6	0.0	0.0	0.0	0.0	92.7

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 139C		Martin Marietta Aggregates, Jefferson, GA							Number of Reports: 12		
Product: M810	WU: Unwashed	Sampled From: Stockpile			Used In: B - 400						
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	99.8	89.8	73.4	59.3	41.7	23.1	11.6			
StdDev	0.0	0.1	2.5	4.7	4.6	3.5	2.1	0.9			
No. of samples	12	12	12	12	12	12	12	12	0	0	
RFTB Factor											
Score	0.0	0.1	2.5	5.2	5.1	3.9	2.3	1.0	0.0	0.0	86.5

Source Number and Name: 143C		Vulcan Materials Co., Cherokee Co., GA							Number of Reports: 64	
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: A - 500					
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200		
Lower Spec	100	95	0	25	0	0	0	0		
Upper Spec	100	100	100	60	100	10	5	100		
Lower Target										
Upper Target										
Mean	100.0	98.1	85.0	39.4	17.1	1.5	1.0	0.5		
StdDev	0.0	0.4	1.1	2.0	1.9	0.4	0.2	0.3		
No. of samples	64	64	64	64	64	64	64	7	0	0
RFTB Factor										
Score	0.0		0.0		0.0		0.0		100.0	

Source Number and Name: 143C		Vulcan Materials Co., Cherokee Co., GA							Number of Reports: 64		
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: B - 400						
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target											
Upper Target											
Mean	100.0	98.1	85.0	39.4	17.1	1.5	1.0	0.5			
StdDev	0.0	0.4	1.1	2.0	1.9	0.4	0.2	0.3			
No. of samples	64	64	64	64	64	64	64	7	0	0	
RFTB Factor											
Score	0.0	0.4	1.1	2.0	1.9	0.4	0.2	0.3	0.0	0.0	95.8

Source Number and Name: 144C		Aggregate Rating for 1/1/2011 to 6/30/2011										
Product:0007		WU: Washed		Sampled From: Stockpile			Used In: B - 400		Number of Reports: 33			
Screen Size	3/4"	1/2"	3/8"	No. 4	No. 8	No. 16	No. 200					
Lower Spec	100	90	40	0	0	0	0					
Upper Spec	100	100	70	15	5	100	100					
Lower Target		93	45	0	0							
Upper Target		100	60	9	1							
Mean	100.0	80.6	51.4	9.5	2.2							
StdDev	0.0	4.6	9.8	5.1	1.2							
No. of samples	33	33	33	33	33	0	0	0	0	0		
RFTB Factor												
Score	0.0	4.6	9.8	5.1	1.2	0.0	0.0	0.0	0.0	0.0	86.2	

Source Number and Name: 144C		Aggregate Rating for 1/1/2011 to 6/30/2011										
Product:0057		WU: Washed		Sampled From: Stockpile			Used In: A - 500		Number of Reports: 88			
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	95	0	25	0	0	0	0				
Upper Spec	100	100	100	60	100	10	5	100				
Lower Target		97		32		0	0					
Upper Target		100		48		5	1					
Mean	100.0	97.8	76.1	37.6	20.7	2.9	0.8	0.3				
StdDev	0.0	0.8	4.2	4.7	3.8	0.9	0.3	0.5				
No. of samples	88	88	88	88	88	88	88	2	0	0		
RFTB Factor		0.0		0.0		0.0	0.1					
Score		0.0		0.0		0.0	0.0				100.0	

Source Number and Name: 144C		Aggregate Rating for 1/1/2011 to 6/30/2011										
Product:0057		WU: Washed		Sampled From: Stockpile			Used In: B - 400		Number of Reports: 31			
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	95	0	25	0	0	0	0				
Upper Spec	100	100	100	60	100	10	5	100				
Lower Target		97		32		0	0					
Upper Target		100		48		5	1					
Mean	100.0	95.8	70.3	30.7	15.3	2.0	0.7					
StdDev	0.0	1.7	6.1	6.5	4.4	1.0	0.4					
No. of samples	31	31	31	31	31	31	31	0	0	0		
RFTB Factor												
Score	0.0	1.7	6.1	6.5	4.4	1.0	0.4	0.0	0.0	0.0	86.6	

Source Number and Name: 144C		Aggregate Rating for 1/1/2011 to 6/30/2011									
Product:0067		WU: Washed		Sampled From: Stockpile			Used In: A - 500		Number of Reports: 20		
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	0	20	0	0	0				
Upper Spec	100	100	100	55	10	5	100				
Lower Target		93		23	0	0					
Upper Target		100		45	5	1					
Mean	100.0	93.6	52.9	29.4	3.3	0.7					
StdDev	0.0	1.4	7.1	5.3	1.4	0.4					
No. of samples	20	20	20	20	20	20	0	0	0	0	
RFTB		0.8		0.0	0.0	0.1					
Factor		5.0		0.0	0.0	0.0					
Score		4.0		0.0	0.0	0.0		96.0			

Source Number and Name: 144C		Martin Marietta Aggregates, Paulding Co., GA									
Product:0067		WU: Washed		Sampled From: Stockpile			Used In: B - 400		Number of Reports: 23		
Screen Size	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	90	0	20	0	0	0				
Upper Spec	100	100	100	55	10	5	100				
Lower Target		93		23	0	0					
Upper Target		100		45	5	1					
Mean	100.0	90.2	45.3	23.7	3.1	1.0					
StdDev	0.0	3.9	8.2	6.2	1.2	0.5					
No. of samples	23	23	23	23	23	23	0	0	0	0	
RFTB											
Factor											
Score	0.0	3.9	8.2	6.2	1.2	0.5	0.0	0.0	0.0	0.0	86.7

Source Number and Name: 144C		Martin Marietta Aggregates, Paulding Co., GA									
Product:0089		WU: Washed		Sampled From: Stockpile			Used In: B - 400		Number of Reports: 31		
Screen Size	1/2"	3/8"	No. 4	No. 8	No. 16	No. 50	No. 200				
Lower Spec	100	90	20	0	0	0	0				
Upper Spec	100	100	55	15	10	5	100				
Lower Target		93	23	0	0	0					
Upper Target		100	43	7	5	1					
Mean	100.0	97.4	36.8	4.9	2.4	1.4					
StdDev	0.0	2.2	11.4	4.0	2.1	1.3					
No. of samples	31	31	31	31	31	31	0	0	0	0	
RFTB											
Factor											
Score	0.0	2.2	11.4	4.0	2.1	1.3	0.0	0.0	0.0	0.0	86.0

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 144C		Martin Marietta Aggregates, Paulding Co., GA								Number of Reports: 17	
Product: 0M10	WU: Unwashed	Sampled From: Stockpile				Used In: B - 400					
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	99.0	83.8	64.0		34.1	23.0	13.5			
StdDev	0.0	0.5	1.9	1.8		4.3	3.4	2.9			
No. of samples	17	17	17	9	0	17	17	17	0	0	
RFTB Factor Score	0.0	0.5	1.9	2.1	0.0	5.1	4.1	3.5	0.0	0.0	88.5

Source Number and Name: 144C		Martin Marietta Aggregates, Paulding Co., GA								Number of Reports: 79	
Product: 15CR-2	WU: Unwashed	Sampled From: Stockpile				Used In: H - 310 Gab					
Screen Size	2"	1 1/2"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 10	No. 60	No. 200	
Lower Spec	100	97	60	0	0	0	0	25	5	4	
Upper Spec	100	100	90	100	100	100	100	45	30	11	
Lower Target		98	70					32	8	6	
Upper Target		100	86					40	25	9	
Mean		99.9	80.9	68.2	61.5	47.4		35.0	17.6	7.5	
StdDev		0.2	3.0	3.5	3.3	3.2		2.6	3.9	0.6	
No. of samples	0	79	79	79	79	79	0	79	17	16	
RFTB Factor Score		0.0	0.0					0.0	0.0	0.0	100.0

Source Number and Name: 144C		Martin Marietta Aggregates, Paulding Co., GA								Number of Reports: 32	
Product: AW10	WU: Washed	Sampled From: Stockpile				Used In: B - 400					
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	0	0	0	0	0	0	0	0			
Upper Spec	100	100	100	100	100	100	100	100			
Lower Target											
Upper Target											
Mean	100.0	99.2	76.1	50.5	33.0	16.8	5.8	2.4			
StdDev	0.0	0.4	3.4	3.9	3.6	2.7	1.4	1.2			
No. of samples	32	32	32	32	29	32	32	32	0	0	
RFTB Factor Score	0.0	0.4	3.4	5.1	4.7	3.5	1.8	1.6	0.0	0.0	86.3

Source Number and Name: 148C		Aggregate Rating for 1/1/2011 to 6/30/2011 Vulcan Materials Co., Ellijay, GA							Number of Reports: 16			
Product:0089	WU: Washed	Sampled From: Stockpile			Used In: B - 400							
Screen Size	1/2"	3/8"	No. 4	No. 8	No. 16	No. 50	No. 200					
Lower Spec	100	90	20	0	0	0	0					
Upper Spec	100	100	55	15	10	5	100					
Lower Target		93	23	0	0	0						
Upper Target		100	43	7	5	1						
Mean	100.0	100.0	35.6	4.1	1.4	0.7						
StdDev	0.0	0.0	1.2	0.8	0.4	0.2						
No. of samples	16	16	16	16	16	16	0	0	0	0		
RFTB Factor Score	0.0	0.0	1.2	0.8	0.4	0.2	0.0	0.0	0.0	0.0	0.0	98.3

Source Number and Name: 153C		Martin Marietta Aggregates, Six Mile, GA							Number of Reports: 20			
Product:0007	WU: Washed	Sampled From: Stockpile			Used In: B - 400							
Screen Size	3/4"	1/2"	3/8"	No. 4	No. 8	No. 16	No. 200					
Lower Spec	100	90	40	0	0	0	0					
Upper Spec	100	100	70	15	5	100	100					
Lower Target		93	45	0	0							
Upper Target		100	60	9	1							
Mean	100.0	92.8	54.2	1.5	0.0							
StdDev	0.0	3.4	10.4	1.2	0.0							
No. of samples	20	20	20	20	20	0	0	0	0	0		
RFTB Factor Score	0.0	3.4	10.4	1.2	0.0	0.0	0.0	0.0	0.0	0.0	0.0	90.0

Source Number and Name: 153C		Martin Marietta Aggregates, Six Mile, GA							Number of Reports: 40			
Product:0057	WU: Washed	Sampled From: Stockpile			Used In: A - 500							
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200				
Lower Spec	100	95	0	25	0	0	0	0				
Upper Spec	100	100	100	60	100	10	5	100				
Lower Target		97		32		0	0					
Upper Target		100		48		5	1					
Mean	100.0	99.8	88.1	38.8	17.3	1.7	0.3					
StdDev	0.0	0.4	4.5	4.6	4.0	0.9	0.3					
No. of samples	40	40	40	40	40	40	40	0	0	0		
RFTB Factor Score		0.0		0.0		0.0	0.0					100.0

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 158C		Hanson Aggregates, Walton Co.							Number of Reports: 12		
Product: 0057	WU: Washed	Sampled From: Stockpile			Used In: A - 500						
Screen Size	1 1/2"	1"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 200			
Lower Spec	100	95	0	25	0	0	0	0			
Upper Spec	100	100	100	60	100	10	5	100			
Lower Target		97		32		0	0				
Upper Target		100		48		5	1				
Mean	100.0	99.8	84.9	36.3	14.1	2.9	2.1				
StdDev	0.0	0.3	4.8	4.6	4.8	1.0	0.5				
No. of samples	12	12	12	12	12	12	12	0	0	0	
RFTB		0.0		0.3		0.0	1.6				
Factor		0.0		5.0		0.0	15.0				
Score		0.0		1.5		0.0	24.0		74.5		

Source Number and Name: 158C		Hanson Aggregates, Walton Co.							Number of Reports: 10		
Product: 0089	WU: Washed	Sampled From: Stockpile			Used In: B - 400						
Screen Size	1/2"	3/8"	No. 4	No. 8	No. 16	No. 50	No. 200				
Lower Spec	100	90	20	0	0	0	0				
Upper Spec	100	100	55	15	10	5	100				
Lower Target		93	23	0	0	0					
Upper Target		100	43	7	5	1					
Mean	100.0	98.8	32.1	7.2	4.6	2.7					
StdDev	0.0	0.5	6.8	2.3	1.3	0.8					
No. of samples	10	10	10	10	10	10	0	0	0	0	
RFTB											
Factor											
Score	0.0	0.5	6.8	2.3	1.3	0.8	0.0	0.0	0.0	0.0	92.2

Source Number and Name: 158F		Vulcan Materials Co., Adairsville, GA							Number of Reports: 98		
Product: 10SM	WU: Washed	Sampled From: Stockpile			Used In: A - 500						
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	100	95	0	45	0	8	1	0			
Upper Spec	100	100	100	95	100	30	10	4			
Lower Target		97		51		12	2	0			
Upper Target		100		90		24	9	3			
Mean	100.0	99.9	94.3	54.2	30.5	14.6	6.3	2.4			
StdDev	0.0	0.1	0.8	2.0	3.5	1.5	1.1	0.2			
No. of samples	98	98	98	98	98	98	98	98	0	0	
RFTB		0.0		0.0		0.0	0.0	0.0			
Factor		0.0		0.0		0.0	0.0	0.0			
Score		0.0		0.0		0.0	0.0	0.0	100.0		

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 158F		Vulcan Materials Co., Adairsville, GA							Number of Reports: 98		
Product: 10SM	WU: Washed	Sampled From: Stockpile			Used In: B - 400						
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	100	95	0	45	0	8	1	0			
Upper Spec	100	100	100	95	100	30	10	4			
Lower Target		97		51		12	2	0			
Upper Target		100		90		24	9	3			
Mean	100.0	99.9	94.3	54.2	30.5	14.6	6.3	2.4			
StdDev	0.0	0.1	0.8	2.0	3.5	1.5	1.1	0.2			
No. of samples	98	98	98	98	98	98	98	98	0	0	
RFTB											
Factor											
Score	0.0	0.1	0.8	2.1	3.7	1.6	1.2	0.2	0.0	0.0	93.5

Source Number and Name: 159C		Hanson Aggregates, Monroe Co.							Number of Reports: 139		
Product: 15CR-2	WU: Unwashed	Sampled From: Stockpile			Used In: H - 310 Gab						
Screen Size	2"	1 1/2"	3/4"	1/2"	3/8"	No. 4	No. 8	No. 10	No. 60	No. 200	
Lower Spec	100	97	60	0	0	0	0	25	5	4	
Upper Spec	100	100	90	100	100	100	100	45	30	11	
Lower Target		98	70					32	8	6	
Upper Target		100	86					40	25	9	
Mean	100.0	99.9	81.0	61.8	54.1	41.9		34.3	23.1	7.2	
StdDev	0.0	0.2	3.8	4.3	3.8	2.8		2.1	2.0	0.9	
No. of samples	139	139	139	139	139	139	0	139	17	17	
RFTB		0.0	0.0					0.0	0.1	0.0	
Factor		0.0	0.0					0.0	5.0	0.0	
Score		0.0	0.0					0.0	0.5	0.0	99.5

Source Number and Name: 161F		Hanson Aggregates, Lithonia, GA							Number of Reports: 112		
Product: 10SM	WU: Washed	Sampled From: Stockpile			Used In: A - 500						
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	100	95	0	45	0	8	1	0			
Upper Spec	100	100	100	95	100	30	10	4			
Lower Target		97		51		12	2	0			
Upper Target		100		90		24	9	3			
Mean	100.0	98.2	76.7	56.4	38.2	18.4	5.5	1.6			
StdDev	0.0	0.6	2.6	3.1	3.9	2.3	1.2	0.5			
No. of samples	112	112	112	112	112	112	112	112	0	0	
RFTB		0.0		0.0		0.0	0.0	0.0			
Factor		0.0		0.0		0.0	0.0	0.0			
Score		0.0		0.0		0.0	0.0	0.0			100.0

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 164F			LaFarge Aggregates Inc., Buford, GA						Number of Reports: 61	
Product:	WU:		Sampled From: Stockpile			Used In: A - 500				
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200		
Lower Spec	100	95	0	45	0	15	6	0		
Upper Spec	100	100	100	95	100	42	22	9		
Lower Target		97		51		19	7	2		
Upper Target		100		90		36	18	7		
Mean	100.0	99.4	75.7	53.1	40.7	30.5	16.3	6.1		
StdDev	0.0	0.4	2.4	2.8	3.5	3.4	2.3	0.8		
No. of samples	51	61	61	61	61	61	61	61	0	0
RFTB		0.0		0.7		0.0	0.6	0.0		
Factor		0.0		5.0		0.0	5.0	0.0		
Score		0.0		3.5		0.0	3.0	0.0	93.5	

Source Number and Name: 168F			Vulcan Materials Co., Lithia Springs, GA						Number of Reports: 63	
Product:	WU:		Sampled From: Stockpile			Used In: A - 500				
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200		
Lower Spec	100	95	0	45	0	15	6	0		
Upper Spec	100	100	100	95	100	42	22	9		
Lower Target		97		51		19	7	2		
Upper Target		100		90		36	18	7		
Mean	100.0	99.7	82.6	60.8	43.0	27.0	13.7	6.1		
StdDev	0.0	0.3	4.1	4.8	4.6	3.3	2.1	0.9		
No. of samples	60	60	60	60	60	60	60	60	0	0
RFTB		0.0		0.0		0.0	0.0	0.0		
Factor		0.0		0.0		0.0	0.0	0.0		
Score		0.0		0.0		0.0	0.0	0.0	100.0	

Source Number and Name: 171F			Vulcan Materials Co., Rockmart, GA						Number of Reports: 96	
Product:	WU:		Sampled From: Stockpile			Used In: A - 500				
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200		
Lower Spec	100	95	0	45	0	15	6	0		
Upper Spec	100	100	100	95	100	42	22	9		
Lower Target		97		51		19	7	2		
Upper Target		100		90		36	18	7		
Mean	100.0	99.9	88.6	57.7	34.7	19.3	9.4	5.0		
StdDev	0.0	0.1	1.6	2.4	2.3	1.7	1.0	0.6		
No. of samples	96	96	96	96	96	96	96	96	0	0
RFTB		0.0		0.0		1.4	0.0	0.0		
Factor		0.0		0.0		5.0	0.0	0.0		
Score		0.0		0.0		7.0	0.0	0.0	93.0	

Source Number and Name: 172F		Aggregate Rating for 1/1/2011 to 6/30/2011								
Product: 10FM-2 WU: Washed		LaFarge Aggregates Inc., Ball Ground, GA								
		Sampled From: Stockpile			Used In: A - 500			Number of Reports: 80		
Screen Size	3/8" No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	100 95	0	45	0	15	6	0			
Upper Spec	100 100	100	95	100	42	22	9			
Lower Target			97		51	19	7			
Upper Target			100		90	36	18			
Mean	100.0 99.7	81.0	54.8	36.4	23.8	14.1	5.1			
StdDev	0.0 0.3	2.4	2.9	3.0	2.5	1.8	1.0			
No. of samples	79 80	80	80	80	80	80	80	0	0	
RFTB			0.0		0.0	0.0	0.0			
Factor			0.0		0.0	0.0	0.0			
Score			0.0		0.0	0.0	0.0	100.0		

Source Number and Name: 174F		Martin Marietta Aggregates, Forsyth Co., GA										
Product: 10FM-2 WU: Washed		Sampled From: Stockpile							Used In: A - 500		Number of Reports: 99	
Screen Size	3/8" No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200					
Lower Spec	100 95	0	45	0	15	6	0					
Upper Spec	100 100	100	95	100	42	22	9					
Lower Target			97		51	19	7					
Upper Target			100		90	36	18					
Mean	100.0 98.7	75.8	55.7	41.9	27.0	11.9	3.3					
StdDev	0.0 0.5	3.6	4.2	4.1	3.9	2.9	0.9					
No. of samples	99 99	99	99	99	99	99	99	0	0			
RFTB			0.0		0.0	0.0	0.0					
Factor			0.0		0.0	0.0	0.0					
Score			0.0		0.0	0.0	0.0	100.0				

Source Number and Name: 180F		Hanson Aggregates, Demorest, GA										
Product: 10SM WU: Washed		Sampled From: Stockpile							Used In: A - 500		Number of Reports: 26	
Screen Size	3/8" No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200					
Lower Spec	100 95	0	45	0	8	1	0					
Upper Spec	100 100	100	95	100	30	10	4					
Lower Target			97		51	12	2					
Upper Target			100		90	24	9					
Mean	100.0 99.9	80.2	55.4	38.8	21.6	7.3	1.3					
StdDev	0.0 0.1	2.6	2.8	3.0	2.1	1.3	0.4					
No. of samples	26 26	26	26	26	26	26	26	0	0			
RFTB			0.0		0.0	0.0	0.0					
Factor			0.0		0.0	0.0	0.0					
Score			0.0		0.0	0.0	0.0	100.0				

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 181F			Martin Marietta Aggregates, Red Oak, GA						Number of Reports: 47	
Product:	WU:		Sampled From: Stockpile			Used In: A - 500				
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200		
Lower Spec	100	95	0	45	0	15	6	0		
Upper Spec	100	100	100	95	100	42	22	9		
Lower Target		97		51		19	7	2		
Upper Target		100		90		36	18	7		
Mean	100.0	99.8	84.2	63.0	47.0	28.5	11.3	3.1		
StdDev	0.0	0.1	2.1	2.9	3.2	3.1	2.0	0.5		
No. of samples	47	47	47	47	47	47	47	27	0	0
RFTB		0.0		0.0		0.0	0.0	0.0		
Factor		0.0		0.0		0.0	0.0	0.0		
Score		0.0		0.0		0.0	0.0	0.0	100.0	

Source Number and Name: 188F			Hanson Aggregates, Toccoa, GA						Number of Reports: 105	
Product:	WU:		Sampled From: Stockpile			Used In: A - 500				
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200		
Lower Spec	100	95	0	45	0	15	6	0		
Upper Spec	100	100	100	95	100	42	22	9		
Lower Target		97		51		19	7	2		
Upper Target		100		90		36	18	7		
Mean	100.0	99.8	80.5	58.5	44.1	28.5	12.3	3.7		
StdDev	0.0	0.1	1.4	2.0	2.0	2.0	1.6	0.7		
No. of samples	105	105	105	105	105	105	105	105	0	0
RFTB		0.0		0.0		0.0	0.0	0.0		
Factor		0.0		0.0		0.0	0.0	0.0		
Score		0.0		0.0		0.0	0.0	0.0	100.0	

Source Number and Name: 192F			Martin Marietta Aggregates, Jefferson, GA						Number of Reports: 21	
Product:	WU:		Sampled From: Stockpile			Used In: A - 500				
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200		
Lower Spec	100	95	0	45	0	15	6	0		
Upper Spec	100	100	100	95	100	42	22	9		
Lower Target		97		51		19	7	2		
Upper Target		100		90		36	18	7		
Mean	100.0	97.9	77.6	60.8	47.7	29.6	10.1	2.3		
StdDev	0.0	0.9	4.7	5.6	5.7	3.1	2.7	1.4		
No. of samples	21	21	21	21	21	21	21	21	0	0
RFTB		0.0		0.0		0.0	0.0	1.1		
Factor		0.0		0.0		0.0	0.0	30.0		
Score		0.0		0.0		0.0	0.0	33.0	67.0	

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 207F			Vulcan Materials Co., Villa Rica, GA						Number of Reports: 20	
Product:	WU:		Sampled From: Stockpile			Used In: A - 500				
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200		
Lower Spec	100	95	0	45	0	15	6	0		
Upper Spec	100	100	100	95	100	42	22	9		
Lower Target		97		51		19	7	2		
Upper Target		100		90		36	18	7		
Mean	100.0	99.3	82.8	58.6	43.0	29.0	12.7	3.6		
StdDev	0.0	1.1	4.1	4.3	4.5	3.6	1.7	0.9		
No. of samples	20	20	20	20	20	20	20	20	0	0
RFTB		0.0		0.0		0.0	0.0	0.0		
Factor		0.0		0.0		0.0	0.0	0.0		
Score		0.0		0.0		0.0	0.0	0.0	100.0	

Source Number and Name: 207F			Vulcan Materials Co., Villa Rica, GA						Number of Reports: 20		
Product:	WU:		Sampled From: Stockpile			Used In: B - 400					
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	100	95	0	45	0	15	6	0			
Upper Spec	100	100	100	95	100	42	22	9			
Lower Target		97		51		19	7	2			
Upper Target		100		90		36	18	7			
Mean	100.0	99.3	82.8	58.6	43.0	29.0	12.7	3.6			
StdDev	0.0	1.1	4.1	4.3	4.5	3.6	1.7	0.9			
No. of samples	20	20	20	20	20	20	20	20	0	0	
RFTB		0.0		0.0		0.0	0.0	0.0			
Factor		0.0		0.0		0.0	0.0	0.0			
Score	0.0	1.1	4.1	5.2	5.4	4.3	2.1	1.1	0.0	0.0	84.5

Source Number and Name: 210F			Martin Marietta Aggregates, Paulding Co., GA						Number of Reports: 61	
Product:	WU:		Sampled From: Stockpile			Used In: A - 500				
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200		
Lower Spec	100	95	0	45	0	8	1	0		
Upper Spec	100	100	100	95	100	30	10	4		
Lower Target		97		51		12	2	0		
Upper Target		100		90		24	9	3		
Mean	100.0	99.2	78.1	52.6	34.7	17.7	5.9	1.8		
StdDev	0.0	0.3	2.0	1.9	1.6	1.3	0.9	0.3		
No. of samples	61	61	61	61	59	61	61	61	0	0
RFTB		0.0		0.3		0.0	0.0	0.0		
Factor		0.0		5.0		0.0	0.0	0.0		
Score		0.0		1.5		0.0	0.0	0.0	98.5	

Aggregate Rating for 1/1/2011 to 6/30/2011

Source Number and Name: 216F			APAC Mid-South, Paulding Co., GA						Number of Reports: 58	
Product:	WU:		Sampled From: Stockpile			Used In: A - 500				
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200		
Lower Spec	100	95	0	45	0	8	1	0		
Upper Spec	100	100	100	95	100	30	10	4		
Lower Target		97		51		12	2	0		
Upper Target		100		90		24	9	3		
Mean	100.0	98.0	70.8	50.2	35.7	21.7	8.3	2.0		
StdDev	0.0	0.9	3.4	2.4	2.5	1.8	0.9	0.5		
No. of samples	58	58	58	58	58	58	58	58	0	0
RFTB		0.0		3.2		0.0	0.2	0.0		
Factor		0.0		5.0		0.0	0.0	0.0		
Score		0.0		16.0		0.0	0.0	0.0	84.0	

Source Number and Name: 222F			Vulcan Materials Company, Forest Park, GA						Number of Reports: 21	
Product:	WU:		Sampled From: Stockpile			Used In: A - 500				
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200		
Lower Spec	100	95	0	45	0	15	6	0		
Upper Spec	100	100	100	95	100	42	22	9		
Lower Target		97		51		19	7	2		
Upper Target		100		90		36	18	7		
Mean	100.0	97.9	78.4	63.6	50.4	32.5	14.1	4.3		
StdDev	0.0	0.4	3.6	4.4	4.3	2.9	2.0	1.0		
No. of samples	21	21	21	21	21	21	21	21	0	0
RFTB		0.0		0.0		0.0	0.0	0.0		
Factor		0.0		0.0		0.0	0.0	0.0		
Score		0.0		0.0		0.0	0.0	0.0	100.0	

Source Number and Name: 223F			Vulcan Materials Co., Cherokee Co., GA						Number of Reports: 33	
Product:	WU:		Sampled From: Stockpile			Used In: A - 500				
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200		
Lower Spec	100	95	0	45	0	15	6	0		
Upper Spec	100	100	100	95	100	42	22	9		
Lower Target		97		51		19	7	2		
Upper Target		100		90		36	18	7		
Mean	100.0	98.5	81.2	60.7	45.9	32.9	14.6	4.0		
StdDev	0.0	0.3	1.1	1.4	1.6	1.7	2.5	0.4		
No. of samples	33	33	33	33	33	33	33	33	0	0
RFTB		0.0		0.0		0.0	0.0	0.0		
Factor		0.0		0.0		0.0	0.0	0.0		
Score		0.0		0.0		0.0	0.0	0.0	100.0	

Aggregate Rating for 1/1/2011 to 6/30/2011

Vulcan Materials Co., Cherokee Co., GA

Source Number and Name: 223F

Product: 10FM-2 WU: Washed

Sampled From: Stockpile Used In: B - 400

Number of Reports: 33

	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Screen Size	3/8"	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200			
Lower Spec	100	95	0	45	0	15	6	0			
Upper Spec	100	100	100	95	100	42	22	9			
Lower Target		97		51		19	7	2			
Upper Target		100		90		36	18	7			
Mean	100.0	98.5	81.2	60.7	45.9	32.9	14.6	4.0			
StdDev	0.0	0.3	1.1	1.4	1.6	1.7	2.5	0.4			
No. of samples	33	33	33	33	33	33	33	33	0	0	
RFTB											
Factor											
Score	0.0	0.3	1.1	1.7	2.0	2.1	3.1	0.5	0.0	0.0	92.8